
Electrochemical Incremental Capacity (dQ/dV) Evolution: NASA Cell B0005
Cycle 10 (SOH: 91.2%)
Cycle 50 (SOH: 88.4%)
Cycle 100 (SOH: 74.3%)
Cycle 150 (SOH: 66.2%)
Loss of Lithium Inventory (LLI)
Peak Height Shrinkage (5.08 → 2.89 Ah/V)
Polarization & Ohmic Rise (ΔV_shift = +60 mV)
Incremental Capacity dQ/dV (Ah / V)
Terminal Cell Voltage V (Volts)
0
1
2
3
4
5
3.4
3.5
3.6
3.7
3.8
3.9
4.0
4.1