

¹ Graphical Abstract

² **Computational study of the glycolytic degradation of poly(ethylene tereph-**
³ **thalate catalyzed by N^1,N^2 -bis(2-aminobenzyl)-1,2-diaminoethane zinc (II)**

⁴ Pablo E. Alanis González, Isabel del Carmen Saenz Tavera, Victor Manuel Rosas
⁵ García

6 Highlights

7 **Computational study of the glycolytic degradation of poly(ethylene tereph-**
8 **thalate catalyzed by N^1,N^2 -bis(2-aminobenzyl)-1,2-diaminoethane zinc (II)**

9 Pablo E. Alanis González, Isabel del Carmen Saenz Tavera, Victor Manuel Rosas
10 García

11 • Research highlight 1

12 • Research highlight 2

13 Computational study of the glycolytic degradation of
14 poly(ethylene terephthalate catalyzed by
15 N^1, N^2 -bis(2-aminobenzyl)-1,2-diaminoethane zinc (II)

16 Pablo E. Alanis González^{a,*}, Isabel del Carmen Saenz Tavera^a, Victor Manuel
17 Rosas García^a

^aFacultad de Ciencias Químicas, Universidad Autónoma de Nuevo León, Av. Universidad s/n,
Cd. Universitaria, San Nicolás de los Garza, 66455, Nuevo León, México

18 **Abstract**

A possible reaction mechanism of the glycolytic degradation of poly(ethylene terephthalate) (PET) catalyzed with N^1, N^2 -bis(2-aminobenzyl)-1,2-diaminoethane zinc (II) (ABEN) was determined using Kohn-Sham density functional theory (KS-DFT) using the range-separated hybrid, generalized gradient approximation functional, ω B97X-V with DFT-D4 dispersion correction [1] using def2-TZVPP over the zinc, oxygen and nitrogen atoms and def2-SVP for the rest, Making use of an energy-weighted climbing image nudged elastic band (EW-CI-NEB) algorithm [2] to determine the minimum energy path (MEP) and then optimizing the converged climbing image (CI) using eigenvector-following partitioned rational function optimization (EF P-RFO) to obtain the transition state (TS). The non-covalent interactions were obtained using an averaged independent gradient model (aIGM) algorithm [3]

19 *Keywords:*


20 KS-DFT, Polymer degradation, Catalysis

21 PACS: 82.20.Pm, 82.35.-x, 82.65.Jn

*Corresponding author
Preprint submitted to Polymer
Email address: pabloalanis1998@gmail.com (Pablo E. Alanis González) April 5, 2022

1. Introduction

By 2015, the annual global production of plastics surpassed 367 million tonnes; 55 % of all plastic waste was discarded, 25.5 % incinerated and just 19.5 % was recycled [4]. Poly(ethylene terephthalate) (PET) is one of the most widely traded polymer there is on the market. It's mainly used in the fabrication of bottles, packages and fibers. The widespread usage of this plastic is due to its properties, like an excellent tensile strength, chemical resistance, clarity, processability and a reasonable thermal stability, It is also very cheap to produce [5, 6]. Albeit all its properties, PET is also becoming a global problem, since a lot of it is not recycled at all. It is becoming a waste problem. Even though PET by itself is not harmful to humans and by itself does not impose an environmental damage, because of its substantial presence in bodies of water and its high resistance to biological and atmospheric agents, PET is classified as a nocive material [7] Chemical recycling of PET has become an important topic since this is the most sustainable way of recycling plastic, and produces *de novo* the starting materials of the synthesis of PET. There is an extensive amount of literature on the topic of chemical degradation of PET, processes such as methanolysis, hydrolysis and glycolysis have been thoroughly studied [8, 9, 10]. The most sustainable reaction of degradation of PET is the glycolysis since this reaction produces Bis(2-hydroxyethyl) terephthalate (BHET), one of the precursors of PET itself. PET glycolysis, nevertheless is not a very effective process if no catalyst is used. Plenty of studies have been made on the reaction of the degradation of PET via catalyzed glycolysis. Some transition metals such as zinc lead to a good yield in this type of reactions with the benefit that zinc is not a very toxic metal. For the chemical recycling of PET, numerous protocols involving hydrolysis, methanolysis and glycolysis among many



Scheme 1: Reported synthesis of ABEN [13]. The structure of ABEN (II) was derived from the electronic structure computations obtained in this study.

47 others [8, 9, 10] have been reported. The uncatalyzed glycolysis of PET is not an
 48 effective process; transition metal (TM) salts have been determined to aid in this
 49 reaction. The oldest report of the catalyzed glycolytic degradation of PET was
 50 reported by Vaidya and Nadkarni [11] in which they carried the reaction using dif-
 51 ferent metal acetates as catalysts. Then it was determined that Zn^{II} has a great in
 52 comparison to other TM (Mn^{II}, Co^{II} and Pb^{II}) activity as a catalyst in the glycolysis
 53 of PET [12]. Alongside the numerous zinc catalysts studied to date, a novel zinc
 54 catalyst, *N*¹,*N*²-bis(2-aminobenzyl)-1,2-diaminoethane zinc(II) (ABEN) [13] has
 55 shown to have a great catalytic activity in the glycolytic degradation of PET yield-
 56 ing around 78 % of BHET[14]. The main purpose of this article is to evaluate the
 57 possible reaction mechanism involved in this catalyzed glycolytic depolymeriza-
 58 tion of PET with ABEN and determine the covalent or non-covalent interactions
 59 involved.[15, 16]

60 2. Experimental

61 2.1. Computational details

62 The software ORCA 5.0.2 [17] was used to perform all the geometry optimiza-
63 tions, single point energy, energy-weighted climbing image nudged elastic band
64 followed by transition state optimization (NEB-TS) and multidimensional relaxed
65 surface scans. For all of the geometry optimizations and vibrational analysis, the
66 meta-generalized-gradient approximation (mGGA) functional r^2 SCAN-3c which
67 uses the dispersion correction DFT-D4 [18] was used; and for all the single point
68 energy and NEB-TS computations, the range-separated hybrid, generalized gradi-
69 ent approximation functional, ω B97X-V with DFT-D4 dispersion correction was
70 employed.¹

71 2.2. Modeling of the intermediates

72 The starting configurations for EG and ABEN were defined and pre-optimized
73 using XTB, [19] with the force field GFN2-xTB [20]. After this crude pre-optimization
74 a conformational and rotamer search was done using CREST [21] In the case of
75 ABEN just one configuration was possible. For EG, six of the lowest energy con-
76 formers were re-optimized as described in 2.1 and the lowest in energy was used
77 for this study. The starting configuration for DBHET was proposed using crystallo-
78 graphic data for PET [22] and extending the unit cell to two units, then re-optimizing
79 this coordinates using r^2 SCAN-3c def2/TZVP.

¹Unless otherwise stated, all computations were made using basis set (BS) def2-SVP with def2-TZVPP over the zinc, oxygen and nitrogen atoms and using def2/J as an auxiliary BS.

80 2.3. NEB-TS method to elucidate the glycolysis mechanisms

81 The optimized structures were then merged onto the same Cartesian coordi-
82 nates and then re-optimized in r^2 SCAN-3c def2/SVP. Then, a multidimensional
83 relaxed surface scan was performed keeping constrained, and varying the bond
84 distances in 20 steps to obtain the products of the reactions depicted in . The opti-
85 mized product and the starting geometry of the relaxed surface scan were the input
86 for an Energy-Weighted Climbing image Nudged Elastic Band (EW-CI-NEB) [2]
87 algorithm to find the path of minimum energy connecting both ends, followed by
88 a P-RFO optimization to find a TS performed onto the climbing image (CI).

89 In order to determine covalent and non-covalent interactions regions between
90 the molecules, an analysis based on Hirshfeld partition of molecular density (IGMH)
91 algorithm within multiwfn was performed [23] onto the optimized reactant. To
92 minimize computation time, aIGM was performed with the MEP obtained by
93 NEB-TS.

94 With JANPA [24], CLPOs and bond orders for the reactants, products and
95 transition states were obtained.

96 3. Results

97 4. Discussion

98 5. Conclusion

99 References

- 100 [1] N. Mardirossian, M. Head-Gordon, ω B97X-V: A 10-parameter, range-
101 separated hybrid, generalized gradient approximation density functional with




Figure 1: Minimum energy path obtained by NEB-TS on the uncatalyzed system.

- 102 nonlocal correlation, designed by a survival-of-the-fittest strategy, Phys.
 103 Chem. Chem. Phys. 16 (2014) 9904. doi:10/gf9n3d.
- 104 [2] V. Ásgeirsson, B. O. Birgisson, R. Bjornsson, U. Becker, F. Neese,
 105 C. Riplinger, H. Jónsson, Nudged elastic band method for molecular reac-
 106 tions using energy-weighted springs combined with eigenvector following,
 107 J. Chem. Theory Comput. 17 (2021) 4929–4945. doi:10/gnm7x.
- 108 [3] C. Lefebvre, H. Khartabil, J.-C. Boisson, J. Contreras-García, J.-P. Piquemal,
 109 E. Hénon, The Independent Gradient Model: A New Approach for Probing
 110 Strong and Weak Interactions in Molecules from Wave Function Calcula-
 111 tions, ChemPhysChem 19 (2018) 724–735. doi:10/gpng7f.
- 112 [4] R. Geyer, J. R. Jambeck, K. L. Law, Production, use, and fate of all plastics
 113 ever made, Sci. Adv. 3 (2017) e1700782. doi:10/b9sp.

- 114 [5] R. J. Caldicott, The basics of stretch blow molding PET containers, *Plast.*
115 *Eng.* 55 (1999) 35–39.
- 116 [6] R. C. Thompson, S. H. Swan, C. J. Moore, F. S. vom Saal, Our plastic age,
117 *Philosophical Transactions of the Royal Society B: Biological Sciences* 364
118 (2009) 1973–1976. doi:10/dqvcxx.
- 119 [7] D. Paszun, T. Szychaj, Chemical recycling of poly(ethylene terephthalate),
120 *Ind. Eng. Chem. Res.* 36 (1997) 1373–1383. doi:10/b2t5nm.
- 121 [8] J. R. Campanelli, M. R. Kamal, D. G. Cooper, A kinetic study of the hy-
122 drolytic degradation of polyethylene terephthalate at high temperatures, *J.*
123 *Appl. Polym. Sci.* 48 (1993) 443–451. doi:10/ch9q4p.
- 124 [9] J. R. Campanelli, M. R. Kamal, D. G. Cooper, Kinetics of glycolysis of
125 poly(ethylene terephthalate) melts, *J. Appl. Polym. Sci.* 54 (1994) 1731–
126 1740. doi:10/bhq8n4.
- 127 [10] J. R. Campanelli, D. G. Cooper, M. R. Kamal, Catalyzed hydrolysis of
128 polyethylene terephthalate melts, *J. Appl. Polym. Sci.* 53 (1994) 985–991.
129 doi:10/fcgbkg.
- 130 [11] U. R. Vaidya, V. M. Nadkarni, Polyester polyols for polyurethanes from pet
131 waste: Kinetics of polycondensation, *J. Appl. Polym. Sci.* 35 (1988) 775–
132 785. doi:10/fkszjj.
- 133 [12] M. Ghaemy, K. Mossaddegh, Depolymerisation of poly(ethylene tereph-
134 thalate) fibre wastes using ethylene glycol, *Polym. Degrad. Stab.* 90 (2005)
135 570–576. doi:10/fhmv7.

- 136 [13] P. Elizondo-Martínez, B. Nájera-Martínez, N. Pérez-Rodríguez, L. Hinojosa-
137 Reyes, I. Gómez Del Río, Polyaza macroligands as potential agents for heavy
138 metal removal from wastewater, *J. Serb. Chem. Soc.* 78 (2013) 591–602.
139 doi:10/gjqg6j.
- 140 [14] A. Ovalle-Sánchez, P. Elizondo-Martínez, N. Pérez-Rodríguez,
141 E. Hernández-Fernández, M. G. Sánchez-Anguiano, Degradation of
142 poly(ethyleneterephthalate) waste to obtain oligomers using a zinc complex
143 as catalyst, *J. Chil. Chem. Soc.* 62 (2017) 3741–3745. doi:10/gjqg6r.
- 144 [15] M. Y. Abdelaal, T. R. Sobahi, M. S. I. Makki, Chemical degradation of
145 poly(ethylene terephthalate), *International Journal of Polymeric Materials*
146 57 (2008) 73–80. doi:10/b55x8v.
- 147 [16] M. M. A. Nikje, F. Nazari, Microwave-assisted depolymerization of
148 poly(ethylene terephthalate) [PET] at atmospheric pressure, *Adv. Polym.*
149 *Tech.* 25 (2006) 242–246. doi:10/c62nvj.
- 150 [17] F. Neese, Software update: The ORCA program system—Version 5.0,
151 *WIREs Comput Mol Sci* (2022). doi:10/gpsrmd.
- 152 [18] E. Caldeweyher, J.-M. Mewes, S. Ehlert, S. Grimme, Extension and evalu-
153 ation of the d4 london-dispersion model for periodic systems, *Phys. Chem.*
154 *Chem. Phys.* 22 (2020) 8499–8512. doi:10/gjqg6h.
- 155 [19] C. Bannwarth, E. Caldeweyher, S. Ehlert, A. Hansen, P. Pracht, J. Seibert,
156 S. Spicher, S. Grimme, Extended TIGHT-BINDING quantum chemistry meth-
157 ods, *WIREs Comput Mol Sci* 11 (2021). doi:10/gh76jn.

- 158 [20] C. Bannwarth, S. Ehlert, S. Grimme, GFN2-xTB—An Accurate and Broadly
159 Parametrized Self-Consistent Tight-Binding Quantum Chemical Method
160 with Multipole Electrostatics and Density-Dependent Dispersion Contribu-
161 tions, *J. Chem. Theory Comput.* 15 (2019) 1652–1671. doi:10/gfvk82.
- 162 [21] P. Pracht, F. Bohle, S. Grimme, Automated exploration of the low-energy
163 chemical space with fast quantum chemical methods, *Phys. Chem. Chem.*
164 *Phys.* 22 (2020) 7169–7192. doi:10/ghfvk8.
- 165 [22] R. D. P. Daubeney, Bunn Charles William, C. J. Brown, The crystal structure
166 of polyethylene terephthalate, *Proc. R. Soc. Lond. A* 226 (1954) 531–542.
167 doi:10/bcnzd2.
- 168 [23] T. Lu, Q. Chen, Interaction Region Indicator: A Simple Real Space Func-
169 tion Clearly Revealing Both Chemical Bonds and Weak Interactions, *Chem.*
170 *Methods* 1 (2021) 231–239. doi:10/gpjzzh.
- 171 [24] T. Y. Nikolaienko, L. A. Bulavin, D. M. Hovorun, JANPA: An open source
172 cross-platform implementation of the natural population analysis on the java
173 platform, *Comput Theor Chem* 1050 (2014) 15–22. doi:10/f6t75z.