

# Computational study of the glycolytic degradation of poly(ethylene terephthalate) catalyzed by $N^1,N^2$ -bis(2-aminobenzyl)-1,2-diaminoethane zinc(II)

Pablo E. Alanis González,<sup>\*,†,¶</sup> Isabel del Carmen Saenz Tavera,<sup>‡,¶</sup> and Victor Manuel Rosas García<sup>‡,¶</sup>

<sup>†</sup>*Universidad Autónoma de Nuevo León, San Nicolás de los Garza, N.L.*

<sup>‡</sup>*Facultad de Ciencias Químicas, Universidad Autónoma de Nuevo León, San Nicolás de los Garza, N.L.*

<sup>¶</sup>*Facultad de Ciencias Químicas, UANL*

E-mail: pabloalanis1998@gmail.com

Phone: +52 (81) 1177 3600

## Abstract


1 A possible reaction mechanism of the glycolytic degradation of poly(ethylene tereph-  
2 thalate) (PET) catalyzed with  $N^1,N^2$ -bis(2-aminobenzyl)-1,2-diaminoethane zinc(II)-  
3 (ABEN) was determined using KS-DFT using the meta-NGA global-hybrid functional,  
4 MN15<sup>1</sup> up to def2-SVP/def2-TZVP level of theory making use of an energy-weighted  
5 climbing image nudged elastic band (EW-CI-NEB) algorithm<sup>2</sup> to determine the min-  
6 imum energy path (MEP) and then optimizing the converged climbing image (CI)

using eigenvector-following partitioned rational function optimization (EF P-RFO) to obtain the transition state (TS). The non-covalent interactions were obtained using and averaged independent gradient model (aIGM) algorithm<sup>3</sup>

## Introduction

By 2015, the annual global production of plastics surpassed 367 million tonnes; 55 % of all plastic waste was discarded, 25.5 % incinerated and just 19.5 % was recycled.<sup>4</sup> Poly(ethylene terephthalate) (PET) is one of the most widely traded polymer there is on the market. It's mainly used in the fabrication of bottles, packages and fibers. The widespread usage of this plastic is due to its properties, like an excellent tensile strength, chemical resistance, clarity, processability and a reasonable thermal stability. It is also very cheap to produce.<sup>5,6</sup> Albeit all its properties, PET is also becoming a global problem, since a lot of it is not recycled at all. It is becoming a waste problem. Even though PET by itself is not harmful to humans and by itself does not impose an environmental damage, because of its substantial presence in bodies of water and its high resistance to biological and atmospheric agents, PET is classified as a noxious material<sup>7</sup> Chemical recycling of PET has become an important topic since this is the most sustainable way of recycling plastic, and produces *de novo* the starting materials of the synthesis of PET. There is an extensive amount of literature on the topic of chemical degradation of PET, processes such as methanolysis, hydrolysis and glycolysis have been thoroughly studied.<sup>8-10</sup> The most sustainable reaction of degradation of PET is the glycolysis since this reaction produces Bis(2-hydroxyethyl) terephthalate (BHET), one of the precursors of PET itself. PET glycolysis, nevertheless is not a very effective process if no catalyst is used. Plenty of studies have been made on the reaction of the degradation of PET via catalyzed glycolysis. Some transition metals such as zinc lead to a good yield in this type of reactions with the benefit that zinc is not a very toxic metal. For the chemical recycling of PET, numerous protocols involving hydrolysis, methanolysis and glycolysis among many others<sup>8-10</sup> have been

reported. The uncatalyzed glycolysis of PET is not an effective process; transition metal (TM) salts have been determined to aid in this reaction. The oldest report of the catalyzed glycolytic degradation of PET was reported by Vaidya and Nadkarni in 1988<sup>11</sup> in which they carried the reaction using different metal acetates as catalysts. Then it was determined that  $\text{Zn}^{\text{II}}$  has a great in comparison to other TM ( $\text{Mn}^{\text{II}}$ ,  $\text{Co}^{\text{II}}$  and  $\text{Pb}^{\text{II}}$ ) activity as a catalyst in the glycolysis of PET.<sup>12</sup> Alongside the numerous zinc catalysts studied to date, a novel zinc catalyst,  $N^1,N^2$ -bis(2-aminobenzyl)-1,2-diaminoethane zinc(II) (ABEN)<sup>13</sup> has shown to have a great catalytic activity in the glycolytic degradation of PET yielding around 78 % of BHET.<sup>14</sup> The main purpose of this article is to evaluate the possible reaction mechanism involved in this catalyzed glycolytic depolymerization of PET with ABEN and determine the covalent or non-covalent interactions involved.<sup>15,16</sup>



Scheme 1: Reported synthesis of ABEN.<sup>13</sup>

## Methods

The starting configurations for EG and ABEN were proposed and optimized using XTB<sup>17</sup> with the force field GFN2-xTB.<sup>18</sup> The starting configuration for DBHET was proposed using crystallographic data,<sup>19</sup> then reoptimized using  $r^2$ SCAN-3cdef2/SVP. The final point energies were obtained all obtained using  $\omega$ -B97X-D4/def2-SVP and def2-TZVPP on just the oxygen, nitrogen, and zinc atoms. The optimized structures were then merged onto the same Cartesian coordinates and then re-optimized in  $r^2$ SCAN-3cdef2/SVP. Then, a multidimensional relaxed surface scan was performed keeping constrained, and varying the bond distances in 20 steps to obtain the products

of the reactions depicted in . The optimized product and the starting geometry of the relaxed surface scan where the input for an Energy-Weighted Climbing image Nudged Elastic Band (EW-CI-NEB)<sup>2</sup> algorithm to find the path of minimum energy connecting both ends, followed by a P-RFO optimization to find a TS performed onto the climbing image (CI).

In order to determine covalent and non-covalent interactions regions between the molecules, an analysis based on Hirshfeld partition of molecular density (IGMH) algorithm within multiwfn was performed<sup>20</sup> onto the optimized reactant. To minimize computation time, aIGM was performed with the MEP obtained by NEB-TS.

With JANPA,<sup>21</sup> CLPOs and bond orders for the reactants, products and transition states were obtained.

## References

- (1) Yu, H. S.; He, X.; Li, S. L.; Truhlar, D. G. MN15: A Kohn–Sham Global-Hybrid Exchange–Correlation Density Functional with Broad Accuracy for Multi-Reference and Single-Reference Systems and Noncovalent Interactions. *Chem. Sci.* **2016**, *7*, 5032–5051.
- (2) Ásgeirsson, V.; Birgisson, B. O.; Bjornsson, R.; Becker, U.; Neese, F.; Riplinger, C.; Jónsson, H. Nudged Elastic Band Method for Molecular Reactions Using Energy-Weighted Springs Combined with Eigenvector Following. *J. Chem. Theory Comput.* **2021**, *17*, 4929–4945.
- (3) Lefebvre, C.; Khartabil, H.; Boisson, J.-C.; Contreras-García, J.; Piquemal, J.-P.; Hénon, E. The Independent Gradient Model: A New Approach for Probing Strong and Weak Interactions in Molecules from Wave Function Calculations. *ChemPhysChem* **2018**, *19*, 724–735.
- (4) Geyer, R.; Jambeck, J. R.; Law, K. L. Production, Use, and Fate of All Plastics Ever Made. *Sci. Adv.* **2017**, *3*, e1700782.

- (5) Caldicott, R. J. The Basics of Stretch Blow Molding PET Containers. *Plast. Eng.* **1999**, *55*, 35–39.
- (6) Thompson, R. C.; Swan, S. H.; Moore, C. J.; vom Saal, F. S. Our Plastic Age. *Philosophical Transactions of the Royal Society B: Biological Sciences* **2009**, *364*, 1973–1976.
- (7) Paszun, D.; Szychaj, T. Chemical Recycling of Poly(Ethylene Terephthalate). *Ind. Eng. Chem. Res.* **1997**, *36*, 1373–1383.
- (8) Campanelli, J. R.; Kamal, M. R.; Cooper, D. G. A Kinetic Study of the Hydrolytic Degradation of Polyethylene Terephthalate at High Temperatures. *J. Appl. Polym. Sci.* **1993**, *48*, 443–451.
- (9) Campanelli, J. R.; Kamal, M. R.; Cooper, D. G. Kinetics of Glycolysis of Poly(Ethylene Terephthalate) Melts. *J. Appl. Polym. Sci.* **1994**, *54*, 1731–1740.
- (10) Campanelli, J. R.; Cooper, D. G.; Kamal, M. R. Catalyzed Hydrolysis of Polyethylene Terephthalate Melts. *J. Appl. Polym. Sci.* **1994**, *53*, 985–991.
- (11) Vaidya, U. R.; Nadkarni, V. M. Polyester Polyols for Polyurethanes from Pet Waste: Kinetics of Polycondensation. *J. Appl. Polym. Sci.* **1988**, *35*, 775–785.
- (12) Ghaemy, M.; Mossaddegh, K. Depolymerisation of Poly(Ethylene Terephthalate) Fibre Wastes Using Ethylene Glycol. *Polym. Degrad. Stab.* **2005**, *90*, 570–576.
- (13) Elizondo-Martínez, P.; Nájera-Martínez, B.; Pérez-Rodríguez, N.; Hinojosa-Reyes, L.; Gómez Del Río, I. Polyaza Macroligands as Potential Agents for Heavy Metal Removal from Wastewater. *J. Serb. Chem. Soc.* **2013**, *78*, 591–602.
- (14) Ovalle-Sánchez, A.; Elizondo-Martínez, P.; Pérez-Rodríguez, N.; Hernández-Fernández, E.; Sánchez-Anguiano, M. G. Degradation of Poly(Ethyleneterephthalate) Waste to Obtain Oligomers Using a Zinc Complex as Catalyst. *J. Chil. Chem. Soc.* **2017**, *62*, 3741–3745.

- (15) Abdelaal, M. Y.; Sobahi, T. R.; Makki, M. S. I. Chemical Degradation of Poly(Ethylene Terephthalate). *International Journal of Polymeric Materials* **2008**, *57*, 73–80.
- (16) Nikje, M. M. A.; Nazari, F. Microwave-Assisted Depolymerization of Poly(Ethylene Terephthalate) [PET] at Atmospheric Pressure. *Adv. Polym. Tech.* **2006**, *25*, 242–246.
- (17) Bannwarth, C.; Caldeweyher, E.; Ehlert, S.; Hansen, A.; Pracht, P.; Seibert, J.; Spicher, S.; Grimme, S. Extended TIGHT-BINDING Quantum Chemistry Methods. *WIREs Comput Mol Sci* **2021**, *11*.
- (18) Bannwarth, C.; Ehlert, S.; Grimme, S. GFN2-xTB—An Accurate and Broadly Parametrized Self-Consistent Tight-Binding Quantum Chemical Method with Multipole Electrostatics and Density-Dependent Dispersion Contributions. *J. Chem. Theory Comput.* **2019**, *15*, 1652–1671.
- (19) Daubeny, R. D. P.; Bunn Charles William,; Brown, C. J. The Crystal Structure of Polyethylene Terephthalate. *Proc. R. Soc. Lond. A* **1954**, *226*, 531–542.
- (20) Lu, T.; Chen, Q. Interaction Region Indicator: A Simple Real Space Function Clearly Revealing Both Chemical Bonds and Weak Interactions. *Chem. Methods* **2021**, *1*, 231–239.
- (21) Nikolaienko, T. Y.; Bulavin, L. A.; Hovorun, D. M. JANPA: An Open Source Cross-Platform Implementation of the Natural Population Analysis on the Java Platform. *Comput Theor Chem* **2014**, *1050*, 15–22.