DESIGN SYSTEMS

TECHNICAL DATA SHEET FERPAV

LIQUID HARDENER FOR THE RENOVATION OR COLOUR CHANGE OF FLOORS

TOPCOAT

Top Coat is a specially formulated very low-thickness system (coating), and the product used is called Ferpav.

The Ferpav product is used for the reconstruction of stamped concrete floors, coatings (bathrooms, kitchens, living rooms, furniture, doors, etc.), smooth or textured indoor floors, outdoor floors, etc.

Easy to apply. Excellent adhesion both in the presence of resin and in direct contact with the dry-shake hardener or concrete.

Quick installation at low cost. Can be overcoated with DS-CS protective resin, Epox 645, DS-Poltec, Cera MT, etc.

DESCRIPTION

The Ferpav product is two-component: Ferpav plus Acril FP; Acril FP is a coloured resin available in 24 colours, specially formulated for the Top Coat product line.

The substrate must be sound, clean, dry and free of dust or grease. Friable parts, laitance or other foreign substances must be carefully removed. The concrete forming the contact surface must also be statically stable and strong.

Any gravel nests, cavities or large holes must be levelled with Corpav dry-shake hardener mixed with water and Polimero 20 in a ratio of 1 to 2. If there is resin on the floor, carefully apply the “Diluente-DS” solvent and work it in with a roller in order to consolidate the substrate; once the floor is dry, apply the Uni-primer 280 New product with a roller and, after at least 48 hours, proceed with the application of Ferpav.

The Ferpav product is spray-applied, taking great care to spread it evenly without leaving streaks.

For the treatment of stamped concrete, the Ferpav product must be allowed to dry thoroughly for at least 5 days (temperatures may alter the timing) and must then be antiqued with the Antique product (depending on the type of finish to be obtained), to create a mottled effect on the surface.

Once the Antique product is dry, protect the floor with DS-CS resin.

If the Ferpav product is used for coatings or decorated floors, it can be coloured, shaded, painted, etc. in various ways. It must then be protected with DS-CS resin, or Epox 645, or Cera MT, or DS-Poltec.

Ferpav is a product supplied in packs, with pre-dosed quantities of the two components: Comp. A (Ferpav) 20 kg + Comp. B (Acril FP) 7,450 kg (the quantity may vary according to the colours).

PREPARATION

Add component A to component B, taking all of the product.

Mix thoroughly; when the resulting mixture is homogeneous throughout, proceed with spray application. The application can be repeated several times, after sanding.

Theoretical consumption: 0,500 kg per m^2

Application temperature: from + 5°C to + 35°C

Pot life at 20°C, in the pack: 60 minutes

Touch-dry: 5-7 hours

Light traffic: 3 days

Full curing: 7 days

Overcoating time: after 96 hours

Ferpav colour: WHITE

In the original, hermetically sealed packs, in cool, dry places, at temperatures between +5°C and +35°C, the product keeps for 12 months.

Cleaning of tools: work tools must be cleaned immediately with water after use.

Do not apply on substrates with standing water.

Do not apply at temperatures below +5°C. The product is frost-sensitive.

The product is solvent-free and physiologically harmless. It is nevertheless advisable to wear normal rubber gloves.

The use of protective gloves and masks is recommended. Keep out of reach of children. In the presence of rising salts, the product could detach from the substrate; first carry out a treatment with an anti-salt product, having previously removed the resin from the floor. Carry out a test before doing the job, to check the adhesion of Ferpav to the anti-salt product.

The information contained in this data sheet is based on the best practical or laboratory experience as at the date shown above. We cannot therefore guarantee that it is exhaustive, since the use of the product is not under our direct control. It is the Customer's responsibility to verify that the product is suitable for its intended use. Design Systems reserves the right to change this information without notice. The user is required to ensure that this information is suitable and complete in relation to the specific use to be made of it. This data sheet cancels and replaces all previous editions. Design Systems recommends always carrying out tests before applying the product, in order to ensure the suitability of the product itself.