DESIGN SYSTEMS

TECHNICAL DATA SHEET PRIMER A300
TWO-COMPONENT EPOXY PRIMER

DESCRIPTION

Solvent-free two-component epoxy primer with high bonding power.

CHARACTERISTICS

Primer A300 is a two-component primer consisting of special solvent-free epoxy resins, characterised by excellent adhesion to ceramic products and high consolidating and protective power.

FIELDS OF USE

Primer A300 is a product developed specifically for the ceramics sector to solve the problem of bonding to critical substrates such as ceramic.

Primer A300 is used as a primer for the treatment of tiles, stoneware and glazed surfaces that are to be coated with enamel paints, for example when painting walls, laboratory tiles, bathrooms, showers, swimming pools, etc.

TECHNICAL CHARACTERISTICS

Colour	Straw yellow (can be tinted on request)
Brookfield viscosity at 25°C	400 - 800 cps
Density at 20°C	1.05 kg/l +/- 0.05
Mixing ratio A : B (A = base, B = hardener)	10 : 3
Pot life at 20°C 60% R.H.	40 minutes
Dust-free time at 20°C 60% R.H.	1 hour
Recoating time at 20°C	8 - 12 hours
Adhesion with medium-build epoxy enamel	> 7 MPa (Adhesion Tester)
Adhesion with self-levelling epoxy	> 8 MPa (Adhesion Tester)
Flammability	non-flammable

APPLICATION

Primer A300 can be applied by brush, roller or spray as required. The substrate to be treated must be thoroughly clean, dry, degreased and free from oil or contaminants that would compromise the success of the work.

DILUTION

The product, suitably catalysed, can be applied as it is or diluted with DILUENTE PE thinner at a rate of 10-15%.

To clean tools, use DILUENTE PE thinner.

THEORETICAL COVERAGE

It depends on the type of substrate to be treated. On average, 1 kg of product (A+B) treats approximately 8 - 10 m^2 of surface.

PACKAGING

Plastic pails of:	10 kg (part A) + 3 kg (part B)
	5 kg (part A) + 1,5 kg (part B)
	1 kg (part A) + 0,3 kg (part B)

STORAGE

In original, intact containers, protected from frost and excessive heat, the product is stable for at least 24 months.

WARNINGS

Under normal conditions of use, the product is not harmful to those handling it. Do not eat, drink or smoke during application. Wear protective clothing such as gloves, goggles and a mask.

Note for the user: The information contained in this data sheet is based on the knowledge available to us at the date of the latest version. The user must ensure the suitability and completeness of the information in relation to the specific use of the product. This document must not be interpreted as a guarantee of any specific property of the product. Since the use of the product is not under our direct control, it is the user's obligation to observe, under their own responsibility, the laws and regulations in force on health and safety. No responsibility is accepted for improper use.