DESIGN SYSTEMS

TECHNICAL DATA SHEET SASSO LAVATO (WASHED STONE)

COLOURED FIBRE-REINFORCED PRE-MIXED PRODUCT

DESCRIPTION

BETON-MIX has been specifically formulated for the washed “STONE EFFECT”. Added to gravel, with its variety of particle sizes, and to cement, it gives an elegant effect, thanks also to the different choice of colours and patterns. It is applied at a thickness of 2 cm to 4 cm.

The product is suitable for pedestrian and vehicular traffic, with excellent resistance to weathering. Suitable for driveways, squares, walkways, ramps, etc.

GENERAL INFORMATION

The Beton Mix product is supplied in the colours Neutral, Ochre, Sand Yellow and Orange.

APPLICATION METHOD

WET-ON-WET APPLICATION

Lay a concrete slab with an average thickness of 8/10 cm with welded wire mesh, keeping 2 to 4 cm below the final level. As soon as it can be walked on, roughen the surface with a toothed tool (rake or broom) and then apply the BETON-MIX + CEMENT + GRAVEL mix.

WET-ON-HARDENED APPLICATION

SUBSTRATE PREPARATION: for substrates such as ceramics, marble and natural stone, apply the UNI-PRIMER 300A product by roller 12 hours before laying the BETON-MIX + CEMENT + GRAVEL mix.

CONCRETE SUBSTRATE: the concrete substrate can be prepared in 2 ways:

- Application of UNI-PRIMER 280 NEW 12 hours before laying the BETON-MIX + CEMENT + GRAVEL.
- Composition of the PRIMER to be spread on the already cured concrete, after washing:
- POLIMERO 20 (1 part)
- WATER (1 part)
- CEMENT (in the quantity required to obtain a fluid mix)

This mix is applied with a brush or roller, etc., after wetting the surface.

After this, the BETON-MIX + CEMENT + GRAVEL mix is applied wet-on-wet.

APPLICATION OF THE SURFACE RETARDER

The Disacal product (surface retarder) comes in different grades according to the depth to be obtained. The choice of Disacal must be determined according to the particle size of the gravel, 2/3 of which must remain embedded in the slab. Apply the product evenly over the surface and remove the surface layer after several hours, depending on the temperature, with a pressure washer. Once the floor is dry, protect it with DS-CS resin.

MIX

- 25 kg of BETON-MIX
- 55 kg of white or grey CEMENT
- 125 kg of GRAVEL

PACKAGING

Beton-Mix 25 kg bag

Disacal 25 kg canister

Gravel 25 kg bag

The technical data given in this bulletin were obtained using standardised tests and standards, or modifications thereof, according to Design Systems systems. The methods applied may be requested from our technical service. The contents of this technical bulletin represent the best of our knowledge and experience. However, for uses other than those indicated, preliminary tests are recommended. In any case, Design Systems Srl accepts no responsibility for damage or defects caused by the use of its products, since the conditions of use are not under its control. It also advises that its technical service is available to customers for any information concerning the correct use of its products.