DESIGN SYSTEMS

TECHNICAL DATA SHEET DS-CS
SINGLE-COMPONENT METHACRYLIC RESIN

DESCRIPTION

DS-CS “Clear Sealer” is a methacrylic resin specifically designed for consolidating and protecting concrete products. It is a liquid product that penetrates deeply into the concrete by capillary absorption. DS-CS “Clear Sealer” contains special thermoplastic polymers that have a consolidating, water-repellent and protective action on the treated materials. Concrete treated with DS-CS “Clear Sealer” shows no tendency to yellowing, is resistant to washing, is not sticky and therefore does not retain dirt, increases compactness, mechanical strength and wear resistance, and gives floors greater protection against oils, acids (hydrochloric acid) and atmospheric agents (rain, frost, UV rays, etc.). It is suitable for use on stamped concrete and industrial floors as a stain-resistant and anti-dusting treatment, as well as making them easier to clean. It is excellent for treating indoor and outdoor floors of premises such as garages, warehouses, cellars, etc. and of outdoor surfaces such as yards, car parks, driveways, swimming pools, courtyards, etc.

DS-CS can be coloured according to the RAL chart.

GENERAL INFORMATION

Store the product in a dry place at a temperature above 5°C; keep the product in its original, undamaged containers, protected from frost and excessive heat; the product keeps for about 12 months.

Under normal conditions of use the product is not harmful to those handling it. DS-CS resin has excellent resistance to UV rays and frost. The product is ready to use and does not require any dilution. If dilution is required, and for cleaning tools, use nitro thinner.

N.B. do not spill solvents or petrol on floors protected with DS-CS

DESCRIPTION	UNI STANDARD	RESULT
Specific gravity	UNI EN ISO 2811/1-02/03	920±20 g/l
Viscosity Ø 4 – 23°C	UNI EN ISO 2431-08/02	26±2"
Water absorption coeff. at 24 hours	UNI EN ISO 1062-3	W24=0,011 kg/m^2 t 1/2
Taber wear index	UNI EN ISO 7784-2/1997	UNI EN ISO 7784-2/1997
Resistance to mould growth	UNI EN ISO 11021	0,0006
Resistance to liquids	UNI-EN ISO 2812-1 I. DIESEL FUEL - LUBRICATING OIL II. SEA WATER III. CHLORINATED POOL WATER	No growth after 14 days. No change in gloss after 24 h and 16 h of rest.

APPLICATION METHOD

DS-CS “Clear Sealer” is applied by brush, roller and/or spray. Cementitious substrates must be properly prepared by cleaning before being treated with DS-CS “Clear Sealer”. A major application advantage of DS-CS

DESIGN SYSTEMS

"Clear Sealer" is that it allows the protective anti-dust treatment to be applied even on newly laid cementitious surfaces. In fact, unlike traditional anti-dust paints, which must be applied only on well-cured concrete, transparent DS-CS "Clear Sealer" can be applied just a few days after the concrete element has been made. In the case of application on industrial floors, a 30/40% dilution with Design Systems thinner is recommended as the first coat, with a possible second coat undiluted. In any case, do not apply the product when there is too much moisture or water on the substrate.

COVERAGE

A 20 l pack is sufficient for approximately 100 m^2.

WARNINGS

The DS-CS "Clear Sealer" product must be used with suitable masks, taking care to avoid contact with the skin, eyes, mucous membranes, etc.; in such cases, wash the affected part thoroughly with soap and water and consult a doctor. When working in enclosed spaces, ensure adequate ventilation. As the product is flammable, do not smoke during use and do not use it near fire.

Bear in mind before using this product that it is a sealer and, as such, it must not be used on ramps that exceed the legal limits or in other circumstances that could cause harm to third parties under particular environmental conditions. The use of gloves and protective masks for solvents is recommended. Keep out of the reach of children.

PACKAGING

20 litre tin.

The technical data given in this bulletin were obtained using standardised tests and standards, or modifications thereof according to Design Systems methods. The procedures applied may be requested from our technical service. The contents of this technical bulletin represent the best of our knowledge and experience. For uses other than those indicated, it is nevertheless advisable to carry out preliminary tests. In any case, Design Systems Srl accepts no liability for damage or defects caused by the use of its products, as the conditions of use are beyond its control. It also informs that its technical service is available to customers for any information concerning the correct use of its products.