DESIGN SYSTEMS

TECHNICAL DATA SHEET POLIMERO 20
POLYMER RESIN FOR BONDING COATS

DESCRIPTION

Polimero 20 consists of an aqueous dispersion of a synthetic copolymer with high stability in alkaline environments, specially modified for the preparation of cementitious mixes.

Its special formulation makes it possible to obtain highly adhesive and elastic films and slurries that facilitate and improve the bonding to the substrate of all subsequent applications.

GENERAL INFORMATION

Polimero 20 comes in the form of a viscous, milky liquid that can be diluted with water in all proportions. The hardened films obtained have remarkable elasticity and excellent resistance to alkalis, and can no longer be re-emulsified in either cold or hot water. These characteristics guarantee the long-term durability of the bond under the most severe conditions. Polimero 20 makes the treated surfaces and the mortars prepared with it permeable and breathable, making them inert to the action of oils, solvents and many chemical products.

TECHNICAL DATA			
Chemical nature	Styrene resins	Density	1,020 kg/dm^3 minimum
Appearance	Viscous liquid	Water solubility	Fully soluble
Colour	Milky white	Storage	In a sheltered, dry place

APPLICATION METHOD

As a Primer for Stamped Plaster (Intonaco Stampato)

In the case of application on reinforced concrete walls, it is advisable to carry out thorough washing with hydrochloric acid and a pressure washer, followed by the application of our Polimero 20 primer, diluted 1/1 with water with the addition of cement; this mix must be spread on the wall. It is advisable to apply it a little at a time and to apply the Starmix product wet-on-wet.

In the case of Concrete and/or Plasters

Polimero 20 is used in all cases where it is necessary to improve the bonding of plasters and mortars to smooth substrates or substrates with adhesion problems, and where high resistance to vibration is required. It is used to bond cement-, lime- or gypsum-based skim coats to old or already hardened plasters. Polimero 20 is used for the preparation of bonding slurries and cement mortars for skimming and repairing deteriorated structures, for repairing chipped edges, for sealing cracks and for levelling substrates of all types. It is also used to bond old concrete to a new pour, to protect reinforcing bars and to waterproof any concrete surface against damp.

For Spray Deck application

The use of Polimero 20 is also important for producing the Spray-Deck product (sprayed floor), where it is mixed with water at a ratio of 2/1 and then used in the mix with Corpav, creating a homogeneous mixture

which is then used in two ways: as a skim coat on the surface or sprayed, with or without stencils.

Wet-on-Wet Primer

It is advisable to use a cement slurry made up as follows: 1 part of Polimero 20 is mixed thoroughly with 1 part of water, and 3 parts of Portland 42,5 R type cement are added under slow, continuous stirring until a homogeneous, lump-free dispersion is obtained. The mix obtained can be applied by brush, roller or notched trowel, depending on the viscosity and the type of surface to be treated, and immediately afterwards, wet-on-wet, proceed with the skim coat or with the spray application of the product to be applied.

COVERAGE

On smooth or low-porosity substrates the average consumption is 150 - 250 g/m^2

WARNINGS

Mixes containing Polimero 20 must be applied on perfectly clean, sound substrates free of loose material, oils, grease, wax, lime paints, water films and any other anti-adhesive material.

Whether it is used as is, diluted or as a slurry, it is important that the mix to be bonded is applied on the resin or slurry while still fresh. Polimero 20 and mixes containing it must be applied at temperatures not below +2° C. If the product is too viscous for the specific type of application, it can be diluted with water until the desired workability is obtained. After dilution it is important to stir from time to time to restore the homogeneity of the dispersion.

Polimero 20 is sensitive to frost and excessively high temperatures, so it must be stored at temperatures between 0° and 50° C. In the original, well-sealed containers, stored under the stated conditions and protected from strong sunlight, the shelf life is 12 months from the date of the delivery note. Polimero 20 is harmless on contact with the skin but tends to harden quickly, so it must be removed immediately with water; if it has hardened, wash thoroughly with soap and water, avoiding the use of solvents. In case of contact with the eyes, rinse immediately and thoroughly with fresh water. Do not release the product or its container into the environment. Do not swallow. Keep out of the reach of children.

PACKAGING

10 litre plastic canister.

The technical data given in this bulletin were obtained using standardised tests and standards, or modifications thereof according to Design Systems methods. The procedures applied may be requested from our technical service. The contents of this technical bulletin represent the best of our knowledge and experience. For uses other than those indicated, it is nevertheless advisable to carry out preliminary tests. In any case, Design Systems Srl accepts no liability for damage or defects caused by the use of its products, as the conditions of use are beyond its control. It also informs that its technical service is available to customers for any information concerning the correct use of its products.