DESIGN SYSTEMS

TECHNICAL DATA SHEET RETOP
LOW-VISCOSITY UNIVERSAL RELEASE AGENT

DESCRIPTION

Retop is a universal chemical release agent for precast concrete items and stampable plasters. It can be used on metal, silicone rubber or polyurethane formwork; do not use on wooden, gypsum or generally porous moulds. Thanks to its particular composition, Retop allows easy stripping from the formwork in the materials indicated and an excellent, stain-free surface finish of the items. The stripped surfaces are also free from anti-adhesive residues. As for the formwork, Retop provides effective anti-rust protection and leaves no residue on the formwork itself.

GENERAL INFORMATION

Retop is normally used as a release agent for stampable plasters, in order to facilitate the release of the stamping mats and obtain faithful reproductions. It extends the life of formwork and improves the surface finish of the items. The product can be applied by brush or spray, using manual systems or automatic equipment.

Technical data	
State	Liquid
Colour	Colourless
Density	approx. 0.750 kg/dm^3
Solubility in water	Insoluble
Viscosity	approx. 1.8 mm^2/s

COVERAGE

Normally approximately 50 m^2 per 1 litre of Retop; coverage that may of course vary depending on the type and quantity of material applied.

WARNINGS

The use of Retop requires protection of the hands and skin in general with gloves or clothing made of suitable rubber, and goggles to protect the eyes. In case of contact with the eyes, rinse thoroughly with running water and seek medical attention; in case of contact with the skin, wash thoroughly with soap and water.

STORAGE

Store in a sheltered, dry place. In tightly closed original packs, protected from frost and direct sunlight and at temperatures between -2°C and +40°C, it has a shelf life of 12 months from the date of the transport document.

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it

PACKAGING

10 kg canister.

The technical data given in this bulletin were obtained using standardised tests and standards, or modifications thereof, according to Design Systems systems. The methods applied may be requested from our technical service. The contents of this technical bulletin represent the best of our knowledge and experience. However, for uses other than those indicated, preliminary tests are recommended. In any case, Design Systems Srl accepts no responsibility for damage or defects caused by the use of its products, since the conditions of use are not under its control. It also advises that its technical service is available to customers for any information concerning the correct use of its products.

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it