DESIGN SYSTEMS

TECHNICAL DATA SHEET DS-POLTEC (GLOSSY/MAT/SATIN)

WATER-DISPERSED, THIN-FILM POLYURETHANE FINISHING FORMULATION

DESCRIPTION

DS-POLTEC glossy/mat/satin is a breathable, transparent formulation based on aliphatic polyurethane resins. Specifically designed as a scratch-resistant finish in industrial and decorative systems.

Available in gloss, matt and satin versions. DS-POLTEC glossy/mat/satin, with low VOC content, respects the health of operators. Ideal for Green Building.

GENERAL INFORMATION

DS-POLTEC is a product with low VOC (Volatile Organic Compounds) content. It has excellent mechanical and abrasion resistance. Its dry film thickness is between 70 - 120 µm. Once cured, the surface is compact, strong, homogeneous and scratch-resistant. It can be pigmented with pastes in percentages varying from 20% to 30%

TECHNICAL CHARACTERISTICS Product at 23°C - 7 days	
Appearance	Liquid
Colour	Transparent
Mixing ratio A:B	100:10
Specific gravity (kg/l)	1,01
Viscosity	22/26 F4
Pot life (min)	45
Abrasion resistance (mg) DIN 53754/ASTMD1044 Taber wheel CS 10 1000 cycles - 1 kg	15
Complete drying (h)	12
Overcoating (min)	after 3 h, within 24 h
Full curing (days)	7
Packaging (kg)	Component A: 5 Component B: 0,5

APPLICATION CONDITIONS

Substrate and ambient temperature >10°C

Substrate moisture from 3% to 9%

Ventilate the rooms when working indoors

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it

APPLICATION METHOD

DS-POLTEC is a ready-to-use product. Components A and B must be stirred before use, then mixed together for at least 2 minutes and left to stand for about 5 minutes. Mixing must be carried out at low speed so as not to compromise the formulation. In the presence of high temperatures, request the DS-POLTEC Late retarding additive.

The time before the floor can be walked on after application depends on the temperature and air exchange. Ventilation is a necessary condition for obtaining the maximum mechanical strength of the DS-POLTEC product.

COVERAGE

70÷120 g/m^2 approx. per coat

PACKAGING

Component A: 10 kg plastic canister

Component B: 3 kg plastic bottle

STORAGE

Eight months in a dry environment not exposed to atmospheric agents, at temperatures not below +5°C