DESIGN SYSTEMS

TECHNICAL DATA SHEET GLASS BEADS (SFERETTE DI VETRO)

INERT FILLER FOR RESIN SYSTEMS

DESCRIPTION

Glass Beads (Sferette di Vetro) are an inert mixture of solid glass microspheres with a selected, constant particle size distribution. By virtue of their chemical nature and their spherical shape, they are resistant to chemicals, wear and impact.

Universal filler for coating and skim-coat systems: it gives anti-slip properties to finishes and optimises the workability of paste-like products.

Available in two versions: FINE (average diameter 40 µm) and COARSE (average diameter 150 µm).

USES

- Additive to give anti-slip properties to coating products.
- Inert functional filler to improve the rheology and facilitate the application of skim-coat products.

APPLICATION

Add the Glass Beads to the resin system in the required quantity and mix for 1-2 minutes with a mechanical stirrer until completely homogeneous.

Recommended dosage as an anti-slip additive: 3-5%* by weight.

Recommended dosage as an inert filler: up to 50% by weight.

* For the solutions already certified by external laboratories, consult the technical documentation or contact the Design Systems technical service.

PRODUCT DATA

DESCRIPTION	RESULT
Colour	White in bulk, transparent in the applied coating
Dosage as anti-slip additive	3-5% by weight
Dosage as rheological filler	Up to 50% by weight
Specific gravity (at 25°C)	2,50 g/cm^3 (kg/dm^3)
Refractive index	1,5
Mohs hardness	6

PARTICLE SIZE DISTRIBUTIONS

VERSION	SIEVE (µm)	PASSING
FINE GLASS BEADS Average diameter: 40 µm	75	98-100%
	50	90-100%

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it

COARSE GLASS BEADS Average diameter: 150 µm	212	90-100%
	180	85-100%
	106	15-55%
	63	0-5%

Percentage of beads passing as a function of the sieve.

WARNINGS

Product for professional use. When applying the purchased product, the purchaser undertakes to strictly follow the warnings given in this data sheet and the instructions in the safety data sheet.

The technical data given in this bulletin were obtained using standardised tests and standards, or modifications thereof according to Design Systems methods. The procedures applied may be requested from our technical service. The contents of this technical bulletin represent the best of our knowledge and experience. For uses other than those indicated, it is nevertheless advisable to carry out preliminary tests. In any case, Design Systems Srl accepts no liability for damage or defects caused by the use of its products, as the conditions of use are beyond its control. It also informs that its technical service is available to customers for any information concerning the correct use of its products.