DESIGN SYSTEMS

TECHNICAL DATA SHEET REMUGEL A+B
TWO-COMPONENT TRANSPARENT SOLVENT-BASED POLYURETHANE GEL

DESCRIPTION

REMUGEL A+B is a transparent, gel-like, two-component, solvent-based formulation based on aliphatic polyurethane resins. It is a transparent protective finish for decorative grit, stone carpet and resin coatings, with excellent resistance to yellowing and a glossy appearance.

REMUGEL forms a film that retains good flexibility and good resistance to abrasion and scratching. It resists ultraviolet rays thanks to UV filters that prevent its photo-oxidative degradation.

USES

Protective finish for resin coatings or decorative grit coatings (stone carpet).

SUBSTRATE

The substrate must be neither wet nor weak.

SUBSTRATE PREPARATION

Decorative grit: remove any residual dust and take away loose or protruding pebbles.

Existing resin coatings: these must be abraded or ground, then the dust residues removed. In the case of newly laid resin coatings, check the overcoating time of the previously applied product.

APPLICATION

Combine the two components (A+B) and mix with a mixing drill for 1 minute. Apply the mix with a resin roller, at a consumption of approximately 0,300 kg/m^2.

To obtain a rough, anti-slip surface, add 5% COARSE GLASS BEADS or 10% QUARTZ B0/B1 when mixing the two components.

WARNINGS

Avoid preparing partial mixes of the product, so as not to incur accidental errors that could result in a lack of or incomplete curing.

PRODUCT DATA

DESCRIPTION	RESULT
Colour	Transparent
Consumption	By roller: approximately 0,300 kg/m^2

DESCRIPTION	RESULT
Specific gravity (at 25°C)	Mix A+B: approximately 1,00 g/ml

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it

Viscosity (at 25°C)	Mix A+B: 1.200-1.300 mPa · s
VOC ready for use (Italian Legislative Decree 161/06)	< 500 g/l – Cat. A/j: two-component high-performance paint (SB)
Tool cleaning	Universal solvent
Storage	12 months, in a dry place at a temperature between 5°C and 30°C; pay particular attention to component B, which is sensitive to atmospheric moisture

APPLICATION DATA AND TIMES

DESCRIPTION	RESULT
Mixing ratio (by weight)	A = 100, B = 27
Pot life (50% R.H.)	at 25°C: 90 min at 35°C: 40 min
Touch dry (50% R.H.)	at 25°C: 8-10 hours at 35°C: 5-7 hours
Foot traffic (50% R.H.)	at 25°C: 12-24 hours
Full traffic (50% R.H.)	3-5 days
Full-depth curing (50% R.H.)	at 25°C: 7 days
Ambient conditions for use	Temperature between +10°C and +35°C

TECHNICAL PERFORMANCE DATA

DESCRIPTION	RESULT
Appearance	Glossy

The technical data given in this bulletin were obtained using standardised tests and standards, or modifications thereof, according to Design Systems systems. The methods applied may be requested from our technical service. The contents of this technical bulletin represent the best of our knowledge and experience. However, for uses other than those indicated, preliminary tests are recommended. In any case, Design Systems Srl accepts no responsibility for damage or defects caused by the use of its products, since the conditions of use are not under its control. It also advises that its technical service is available to customers for any information concerning the correct use of its products.