DESIGN SYSTEMS

TECHNICAL DATA SHEET DISACAL
SURFACE RETARDER FOR EXPOSED-AGGREGATE PRODUCTS

DESCRIPTION

The DISACAL product is a ready-to-use, solvent-based surface retarder for the production of exposed-aggregate (washed stone) products. Its ease of application, excellent washing uniformity and low cleaning cost make DISACAL the ideal product for creating washed-gravel floors.

GENERAL INFORMATION

DISACAL retards the setting of the cement at the surface, so the final result depends heavily on ambient temperature, type of cement, grading curve, consistency and quality of the mix, admixtures, type of formwork, etc. Preliminary tests are recommended.

GRAIN SIZE mm	WASH DEPTH mm	GRAIN SIZE mm	WASH DEPTH mm
01-03	0,5	08-12	3,0
03-05	1,0	08-16	3,5
03-05	1,5	12-16	4,0
04-08	2,0	16-18	5,0
05-08	2,5	18-32	6,0

APPLICATION METHOD

The DISACAL product is ready to use and is applied by spraying; the choice of depth is determined by the fact that 2/3 of the stone must remain embedded in the mix, in order to guarantee that the stone is properly held when vehicles pass over it.

Once the mix of Beton-mix, cement and gravel has been spread, our DISACAL product is sprayed on immediately afterwards. After a drying time of approx. 12/24/48 hours (depending on weather conditions), the floor is washed. As a rule, the elements can be washed after 12 hours, but also at 24 or 48 hours, bearing in mind that the cycles must be the same for all the products of the same production series. The wash depths obtained with the different versions of DISACAL depend heavily on the type and dosage of cement, the type and quantity of aggregate, the consistency of the mix and the type of curing. Preliminary tests are recommended for each type of production and ambient condition. Any retarder residues on the floor can be easily removed with a brush.

CLEANING OF TOOLS

To clean tools, the use of an ordinary thinner is recommended.

WARNINGS

Flammable. Protect skin and eyes. Consult the DIN safety data sheet.

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it

COVERAGE

approx. 80-125 g/m^2. Very important: shake well (with drill and whisk) before each application.

STORAGE

Shelf life is 12 months from the date of supply, in closed tins in the original packaging.

Store in a cool, ventilated place. Frost-resistant.

PACKAGING

20 kg tins.

The technical data given in this bulletin were obtained using standardised tests and standards, or modifications thereof, according to Design Systems systems. The methods applied may be requested from our technical service. The contents of this technical bulletin represent the best of our knowledge and experience. However, for uses other than those indicated, preliminary tests are recommended. In any case, Design Systems Srl accepts no responsibility for damage or defects caused by the use of its products, since the conditions of use are not under its control. It also advises that its technical service is available to customers for any information concerning the correct use of its products.

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it