DESIGN SYSTEMS

TECHNICAL DATA SHEET DS-REMUK TIX
ALIPHATIC BINDER

FIELDS OF APPLICATION

Construction of permeable paving and coatings, for indoors and outdoors (showrooms, shops, warehouses, pedestrian paths, courtyards and terraces, 1 cm thickness).

SUBSTRATE PREPARATION

Apply on solid, compact, dry substrates not subject to capillary rising damp, clean and free from oils and grease. If necessary, treat the surfaces by shot-blasting or grinding followed by vacuuming of the residues. Alternatively, the construction of a cementitious substrate or an epoxy screed is recommended. The use of a suitable primer is recommended.

USE OF THE PRODUCT

Mix the product with coloured or single-colour mineral aggregates of any particle size, mixing by hand (low-speed drill with mixing paddle).

To obtain a finished product with maximum chemical and mechanical resistance, the use of grit free from oils or grease and free from moisture is recommended.

The ratio between grit and binder depends heavily on the shape, size and porosity of the grit. As a guide, 3,5 kg of DS-REMUK TIX per 25 kg of gravel.

The correct quantity of binder is that strictly necessary to wet the surface of the grit, plus the product needed to be spread on the vertical surfaces to be made. Only then apply the mixture of DS-REMUK TIX and gravel to the substrate.

PRODUCT INFORMATION

Single-component, thixotropic, solvent-free, non-yellowing aliphatic system, with excellent chemical resistance and good cold curing (do not apply at temperatures below 5°C).

PRODUCT CHARACTERISTICS	RESIN
Colour	Colourless
Viscosity at 25°C (mPa · s)	1.800 - 2.800
Density at 25°C (g/ml)	1,14 - 1,18

SYSTEM CHARACTERISTICS

DESCRIPTION	UNIT	VALUE
Working time (mix, 25°C, 65% RH)	h	1-2
Touch dry (25°C, 65% RH)	h	14 - 18

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it

Foot traffic (15°C, 65% RH)	h	14 - 36
Foot traffic (25°C, 65% RH)	h	12 - 14
Full curing (25°C, 65% RH)	days	7-8
Flexural strength (grit 1-2 mm, 16:1, 3 days at 25°C, 65% RH)	MN/m^2	5,6 - 5,8
Indicative grit consumption (4-6 mm, approx. 2 cm thickness)	kg/m^2	35 - 45
Indicative binder consumption* (grit 4-6 mm, approx. 2 cm thickness)	kg/m^2	0,7 - 1,2

* The quantities of binder may vary according to the particle size distribution of the grit.

STORAGE AND PRECAUTIONS

WARNING: all products are sensitive to both high and low temperatures; at temperatures above 30/35°C take all possible precautions or do not carry out the work.

STORAGE: the product is sensitive to moisture; always close the packs tightly after use. The product can be stored for six months in tightly closed containers, in a cool, dry place.

Consult the safety data sheet and follow the provisions on industrial hygiene and waste disposal.

Packs of 4,4 kg.

Note for the user: the information contained in this data sheet is based on the knowledge available to us at the date of the last revision. The user must ensure that the information is suitable and complete in relation to the specific use of the product. This document must not be interpreted as a guarantee of any specific property of the product. Since the use of the product is not under our direct control, it is the user's obligation to observe, under their own responsibility, the laws and provisions in force on health and safety. No responsibility is accepted for improper use.

Date of first issue: 5 October 2020 | Rev. 1: 11 May 2026

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it