DESIGN SYSTEMS

TECHNICAL DATA SHEET MASBETON

DESCRIPTION

The MASBETON product is white, ready to use, of the highest quality, usable indoors and outdoors, consisting of controlled-particle-size sand, cement, hydraulic binders and special polymers that regulate its workability and define its flow.

The product has excellent mechanical characteristics that make it suitable for vehicular traffic.

GENERAL INFORMATION

The material is ready to use; no additional products are required. The key feature that distinguishes MASBETON is its ease of preparation and application which, combined with controlled drying, almost always allows perfect levelling of the surface, both indoors and outdoors.

The MASBETON product requires only a few centimetres of thickness and makes it possible to produce stamped, clouded, trowelled, polished, cocciopesto-type, micro-topp-type, spray-deck, acid-stained, BasFloor floors, etc.

APPLICATION METHOD

The product can be applied from a thickness of just 1,5 cm up to approximately 8/10 cm.

The surface must be absolutely solid and sound, clean, free from oil stains, paint, etc., and in the case of micro-cracks, close them with a cement-based mix (made of cement, Polimero 20 plus water, sand and synthetic mesh). The MASBETON product can also be laid on marble, ceramics, old stamped floors, etc.; in these cases after applying our Polimero 20 product wet-on-wet, mixing 2 parts of water with 1,5 of Polimero 20 and adding cement to the mix until a fluid cement slurry is obtained, which is spread on the concrete, previously well wetted but without standing water. Alternatively, apply the Uni-Primer 280 New product 12 hours beforehand, which bonds the new floor to the substrate.

Once the product has been applied to the surface, mist a thin film of water over it and trowel with a steel finishing trowel.

The MASBETON product can be coloured at the mixing stage with synthetic oxide powder, so as to obtain all the desired shades. Alternatively, the coloured Corpav dry-shake hardener can be broadcast over it. If used for polished floors, the screed made with this product can be ground after 3/4 days of drying, depending on the temperature. After the first grinding stage, fill the surface to eliminate any porosity, then proceed with polishing the finished floor.

When producing a stamped floor, apply a release agent, which will prevent the stamping mats from sticking to the MASBETON; the release agent can be either DS-R (powder) or Re-Color (liquid).

MASBETON mix:

Consumption: 21 kg per m^2 for 1,5 cm thickness

- 25 kg of Masbeton product

- Synthetic oxide if required
- Approximately 5,5 l of water, until the required plastic consistency is reached.

Once the floor is dry, various types of products can be applied to protect the floor from weathering and stains of various kinds. The products to be applied may be: DS-CS methacrylic resin, water-repellent treatments, polyurethane resins such as DS-POLTEC.

WARNINGS

Do not apply the product at ambient temperatures below +5°C or above 35 °C

The use of the product is recommended for professionals only.

PACKAGING

25 kg bag

The information contained in this data sheet is based on the best practical or laboratory experience as at the date shown above. We cannot therefore guarantee that it is exhaustive, since the use of the product is not under our direct control. It is the Customer's responsibility to verify that the product is suitable for its intended use. Design Systems reserves the right to change this information without notice. The user is required to ensure that this information is suitable and complete in relation to the specific use to be made of it. This data sheet cancels and replaces all previous editions. Design Systems recommends always carrying out tests before applying the product, in order to ensure the suitability of the product itself.