DESIGN SYSTEMS

TECHNICAL DATA SHEET MICRO-TOPP
MICROCEMENT FLOORS AND COATINGS

DESCRIPTION

Micro-topp is a polymer-modified cementitious system used for seamless floors, for interiors and exteriors.

Micro-topp is ideal for renovating or creating artistic and decorative floors over ceramic tiles, marble, terracotta, concrete, concrete slabs, etc., with great architectural effect. For their beauty, natural look, distinctiveness and creative applications, Micro-topp is used for shops, showrooms, homes, restaurants, hotels, shopping centres, pool surrounds, industrial buildings, pavements, driveways, terraces, counters, etc.

GENERAL INFORMATION

Particularly suitable for creating seamless floors with a clouded, trowelled effect, etc. on existing substrates. Micro-topp has a white base, thus offering the possibility of obtaining countless colour shades by mixing it with water-based colouring paste. Its special formulation gives Micro-topp excellent resistance to heavy traffic and greater resistance to salts and UV rays.

FINAL PERFORMANCE	
Density of hardened product	1,8 kg/l
Compressive strength at 28 days	23,0 MPa (EN 196-1)
Flexural strength at 28 days	8,9 MPa (EN 196-1)
Adhesion to concrete	1,0 MPa (EN 13892-8)

APPLICATION METHOD

SURFACE PREPARATION

The substrate must not be dusting; it must be sound, clean, dry, free from dust or grease and friable parts, free from detached material and free from laitance; any other foreign substances must be carefully removed. The application area must be allowed to cure for at least 28 days. The surface must be completely free from residues of dirt, oil, paint, moss, dust and other contaminants such as: resins, curing compounds and waxes.

The surfaces on which the Micro-topp product is to be applied must be level and free from micro-cracks; any patch repairs to the floor and filled chases could also cause micro-cracks and/or cracks in our applied product. Appropriate precautions must therefore be taken before laying the new Micro-topp floor. Expansion joints must be respected. The surface must be allowed to cure for 4-8 hours between the different applications of Micro-topp.

APPLICATION

We have 3 products for Micro-topp floors:

Micro-topp BS (the base coat, with the coarsest grain)

Micro-topp MD (the skim coat, with a finer grain)

Micro-topp Fine (the filler, for skim coats)

The instructions below apply to all of them:

Before starting phase ①, apply the Uni-primer 280 New primer (see technical data sheet).

Uni-primer 280 New is to be used on all substrates consisting of ceramic, marble, terracotta or glass floors or industrial floors. The joints must first be filled with the same primer and quartz, and once this has dried, after at least 12 hours, apply Uni-primer 280 New.

- Micro-topp BS must be mixed with Acril BS, specially dosed to obtain a fluid mix and already supplied in the pack. Mix with a low-speed drill fitted with a whisk for about 5 minutes or with a suitable automatic mixer until a homogeneous mix, free from lumps and any form of impurity, is obtained. After 2 minutes, stir the mix again and proceed with application at a maximum thickness of 1,2 to 3 mm for Micro-topp BS. On porous substrates, such as cement screeds or ceramic tiles, apply a second coat of Micro-topp BS. Micro-topp BS is a slightly self-levelling product.
- Micro-topp MD must be mixed with Acril MD, specially dosed to obtain a fluid mix and already supplied in the pack. Mix with a low-speed drill fitted with a whisk for about 5 minutes or with a suitable automatic mixer until a homogeneous mix, free from lumps and any form of impurity, is obtained. After 2 minutes, stir the mix again and proceed with application, applying a skim coat to the floor, after first applying Acril MD diluted with 2 parts of water to the substrate.
- Micro-topp Fine must be mixed with Acril Fine, specially dosed to obtain a fluid mix and already supplied in the pack. Mix with a low-speed drill fitted with a whisk for about 5 minutes or with a suitable automatic mixer until a homogeneous mix, free from lumps and any form of impurity, is obtained. After 2 minutes, stir the mix again and proceed with application, applying a skim coat to the floor, after first applying Acril Fine diluted with 2 parts of water to the substrate.

Once mixed, the products must be applied within 25-30 minutes. Before any mixing and laying of the material, temperatures must be between 5°C and 30°C. Do not use in extreme temperatures or in strong wind. From the second phase onwards, it is advisable to walk on the floor wearing shoe covers. After application of the above products, the surface must be allowed to cure for 4-8 hours between the different applications and for 24 hours before allowing foot traffic.

After the floor has been laid, and before carrying out the protective treatment, it is recommended to keep the floor clean and, above all, not to spill oily substances that could compromise the subsequent treatment.

Micro-topp floors are made by hand, so slight unevenness and small defects, due to the fact that a “semi-plastic” material is being worked, must be understood and accepted. When sanding is carried out on Micro-topp and/or similar cementitious products, the scratched area will show up in a more intense colour when the resin is applied, so pay close attention to the uniformity of sanding.

PROTECTION

After 4-5 days it is advisable to apply a protective resin. The type of treatment will be chosen according to the traffic and the place of installation. DS-CS, Epox 645, DS-POL 198 or self-polishing Cera MT wax are recommended.

DESIGN SYSTEMS

WARNINGS

Micro-topp floors are decorative floors, so particular attention must be paid to their maintenance, i.e. to the protective resin or wax. Wash the floor with pH-neutral detergents. Never use aggressive products or substances.

Depending on use, it is advisable to periodically apply a new coat of Cera MT.

COVERAGE

AVERAGE CONSUMPTION per m^2:

Micro-topp BS 2 kg

Micro-topp MD 0,750 kg

Micro-topp Fine 0,150 kg

STORAGE

Store in a cool, safe place at a temperature of 15°C – 20°C. Keep the containers tightly sealed. The shelf life of Acril MT is at least 12 months and the shelf life of Micro-topp is 12 months.

PACKAGING

Micro-topp BS in 17 kg pails	Acril BS in 3,200 l cans
Micro-topp MD in 15 kg pails	Acril MD in 4,700 l cans
Micro-topp Fine in 12 kg pails	Acril FINE in 3,900 l cans

The technical data given in this bulletin were obtained using standardised tests and standards, or modifications thereof, according to Design Systems systems. The methods applied may be requested from our technical service. The contents of this technical bulletin represent the best of our knowledge and experience. However, for uses other than those indicated, preliminary tests are recommended. In any case, Design Systems Srl accepts no responsibility for damage or defects caused by the use of its products, since the conditions of use are not under its control. It also advises that its technical service is available to customers for any information concerning the correct use of its products.