DESIGN SYSTEMS

TECHNICAL DATA SHEET POLIRESIN L 2
RESIN FOR CONSOLIDATING PLASTERS, MORTARS AND SKIM COATS

DESCRIPTION

Poliresin L2 is a special acrylic resin in aqueous dispersion with high stability in alkaline environments and a particularly fine particle size, which allows it to penetrate even the smallest pores and capillaries. Its special formulation allows rapid polymerisation even at particularly low temperatures.

GENERAL INFORMATION

Poliresin L2 comes in the form of a fluid, milky liquid that can be diluted with water. The hardened films obtained with Poliresin L2 are slightly flexible, while the individual particles lodged in the capillaries produce a rigid system with excellent resistance to alkalis, and can no longer be re-emulsified in either cold or hot water. These characteristics guarantee the long-term durability of the treatment under the most severe conditions and a good degree of impermeability.

Poliresin L2 is used in all cases where it is necessary to improve the strength of plasters, mortars and skim coats and to consolidate the bedding mortars of old masonry before renovation. Applied to saturation as an impregnating treatment on dry surfaces, it waterproofs all types of masonry, giving a “wet effect”.

TECHNICAL DATA			
Chemical nature	Acrylic resin	Density	1,030 kg/dm^3 minimum
Appearance	Liquid	Water solubility	Total
Colour	Milky white	Film-forming temperature	0°C

APPLICATION METHOD

Application on plasterboard is recommended, paying attention to the load-bearing structure of the plasterboard itself, which will also have to support the weight of the «MuroLatino» product. Apply the Poliresin L2 primer in a proportion of 1 part of product to 3 parts of water, and allow it to dry completely, for at least 3 hours, before laying the Starmix. In the case of a substrate made of tuff, friable plasters or plasters with a tensile strength lower than that of our product (such as commonly used pre-mixed products), the surface must be reinforced with our Poliresin L2 product, applied to saturation on the surface in a proportion of one part of Poliresin L2 to 3 parts of water; the Starmix pre-mix can be laid about 3 hours after the last application. Poliresin L2 must be applied on perfectly clean substrates, free of loose material, oils, grease, wax, lime paints, water films and any other anti-adhesive material. Poliresin L2 and mixes containing it must be applied at temperatures not below +2° C. If the product is too viscous for the specific type of application, it can be diluted with water until the desired degree of penetration is obtained. It is however advisable not to exceed a 1/5 dilution ratio of resin in water. After dilution it is important to stir from time to time to restore the homogeneity of the dispersion.

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it

DESIGN SYSTEMS

WARNINGS

Poliresin L2 is harmless on contact with the skin but tends to harden quickly, so it must be removed immediately with water; if it has hardened, wash thoroughly with soap and water, avoiding the use of solvents. In case of contact with the eyes, rinse immediately and thoroughly with fresh water. Do not release the product or its container into the environment. Do not swallow. Keep out of the reach of children.

COVERAGE

On moderately porous substrates the consumption is approx. 200 g/m^2

STORAGE

Poliresin L2 is sensitive to frost and excessively high temperatures, so it must be stored at temperatures between 0° and 50°C. In the original, well-sealed containers, stored under the stated conditions and protected from strong sunlight, the shelf life is 12 months from the date of the delivery note.

Store in a sheltered place at temperatures from 0° to + 40°C.

PACKAGING

5 kg plastic canister.

The information contained in this data sheet is based on the best practical or laboratory experience as at the date shown above. We cannot therefore guarantee that it is exhaustive, since the use of the product is not under our direct control. It is the Customer's responsibility to verify that the product is suitable for its intended use. Design Systems reserves the right to change this information without notice. The user is required to ensure that this information is suitable and complete in relation to the specific use to be made of it. This data sheet cancels and replaces all previous editions. Design Systems recommends always carrying out tests before applying the product, in order to ensure the suitability of the product itself.