DESIGN SYSTEMS

TECHNICAL DATA SHEET UNIPRIMER 280 NEW
HIGH-PERFORMANCE, BREATHABLE, WATER-DISPERSED ADHESION PROMOTER

DESCRIPTION

Uniprimer 280 New is a water-dispersed, breathable formulation with high adhesion, even on damp substrates.

It guarantees high adhesion on damp cementitious substrates or stone materials in general. It is used as an adhesion promoter and as an intermediate primer in the systems of the Effetto Sasso (Stone Effect) Line. Uniprimer 280 New, with zero VOC, respects the health of operators. Ideal for Green Building.

GENERAL INFORMATION

- Zero VOC content (Volatile Organic Compounds)
- Applied by roller or trowel
- Specifically designed for building up high thicknesses when filled with quartz and admixed with Technibond fibres (up to 2%)
- Can be pigmented
- Excellent adhesion on asphalt and on metal substrates

TECHNICAL CHARACTERISTICS - Product at 23°C - 7 days	
Appearance	Liquid
Colour	Neutral, to be pigmented with 3÷5% colour paste
Mixing ratio A : B	100 : 20
Specific gravity (kg/l)	1,6
Viscosity (mPa · s)	2000 ÷ 3000
Pot life (min)	40
Compressive strength (N/mm^2)	55
Abrasion resistance (mg) DIN 53754/ASTM D1044 Taber wheel CS 17 1000 cycles - 1 kg	75
Shore D (24 h at 23°C)	84
Vapour permeability (UNI EN 12086)	1200
Full curing (days)	7
Reaction to fire (UNI EN 13813)	Bfl-s1

APPLICATION METHOD

Components A and B must be stirred before use and then mixed together for at least 3 minutes. The two components must be mixed before adding the colour, the quartz and the water, which must be added in

small doses without overdoing it (maximum 10%). Mixing must be carried out at low speed so as not to compromise the formulation. Do not add the colour paste to the product without first mixing it with the hardener, in order to avoid an increase in viscosity. At particularly low temperatures, use warm water in the product to improve the curing reaction. The time before the floor can be walked on after application depends on the temperature and air exchange. Ventilation is a necessary condition for obtaining the maximum mechanical strength of the products.

Application conditions.

- Substrate and ambient temperature >10°C
- Substrate moisture from 3% to 9%
- Ventilate the rooms when working indoors

COVERAGE

- By roller: 300 g/m^2 with maximum water dilution of 15 %
- By trowel: 300 g/m^2 filled with approx. 50% by weight of quartz 1 with maximum water dilution of 5/10%

1) 1,0 kg/m^2 filled with 30% by weight of quartz 1 and 40% of quartz 2 with maximum water dilution of 5/10%

2) 1,3 kg/m^2 filled with approx. 50% by weight of quartz 6 with maximum water dilution of 5%

STORAGE

Eight months in a dry environment not exposed to atmospheric agents, at temperatures > +5°C

PACKAGING

Component A: 15 kg tin pail.

Component B: 3 kg small pail.

The information contained in this data sheet is based on the best practical or laboratory experience as at the date shown above. We cannot therefore guarantee that it is exhaustive, since the use of the product is not under our direct control. It is the Customer's responsibility to verify that the product is suitable for its intended use. Design Systems reserves the right to change this information without notice. The user is required to ensure that this information is suitable and complete in relation to the specific use to be made of it. This data sheet cancels and replaces all previous editions. Design Systems recommends always carrying out tests before applying the product, in order to ensure the suitability of the product itself.