DESIGN SYSTEMS

TECHNICAL DATA SHEET DS-REMUK
ALIPHATIC BINDER

FIELDS OF APPLICATION

Production of permeable floors for indoors and outdoors (showrooms, shops, warehouses, pedestrian paths, courtyards and terraces). For vehicular surfaces use a thickness of at least 1 cm.

SUBSTRATE PREPARATION

Apply on solid, compact, dry substrates not subject to capillary rising damp, clean and free from oil and grease. If necessary, treat the surfaces by shot-blasting or grinding followed by vacuuming of the residues. Alternatively, a cement-based substrate or an epoxy screed is recommended. The use of a suitable primer is recommended.

USE OF THE PRODUCT

Mix the product with coloured or single-colour mineral aggregates of any particle size, by manual mixing (low-speed drill with mixing paddle) or automatic mixing (concrete mixer).

To obtain a finished product with maximum chemical and mechanical resistance, the use of grit free from oil or grease and free from moisture is recommended.

The ratio between grit and binder depends heavily on the shape, size and porosity of the grit. As a guide:

- 45:1 for 4-8 mm grit (approximately 900 g of DS-REMUK per 25 kg of gravel);
- 30:1 for 3-5 mm grit (approximately 1 kg of DS-REMUK per 25 kg of gravel).

The correct quantity of binder is the amount strictly necessary to just wet the surface of the grit, without any running. Once ready, pour the mix onto the floor without letting the excess resin run and without scraping the bottom of the container. If an accumulation of resin and gravel forms inside the container used for mixing, this accumulation must on no account be poured onto the floor: add dry gravel to absorb all the resin and only then spread it on the floor.

Spread the resulting aggregate mix using screed rails or rakes and compact with a smooth hard-plastic finishing trowel or, for large areas, with a mechanical vibrating compactor.

Add 3% to 5% of 0,1-0,3 quartz to the mix. The following day, apply a coat of Remuk resin by roller; if better grip is required, broadcast glass beads over the floor. Another method is to go over it with a single-disc machine fitted with a black felt pad.

PRODUCT INFORMATION

Single-component, solvent-free, non-yellowing aliphatic system, with excellent chemical resistance and good cold curing (do not apply at temperatures below 5°C).

PRODUCT CHARACTERISTICS	RESIN
Colour	Colourless

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it

Viscosity at 25°C (mPa · s)	1.800 - 2.800
Density at 25°C (g/ml)	1,14 - 1,18

SYSTEM CHARACTERISTICS

DESCRIPTION	UNIT	VALUE
Working time (mix, 25°C, 65% R.H.)	h	1 - 2
Touch dry (25°C, 65% R.H.)	h	14 - 18
Foot traffic (15°C, 65% R.H.)	h	14 - 36
Foot traffic (25°C, 65% R.H.)	h	12 - 14
Full curing (25°C, 65% R.H.)	days	7 - 8
Flexural strength (1-2 mm grit, 16:1, 3 days at 25°C, 65% R.H.)	MN/m^2	5,6 - 5,8
Indicative grit consumption (4-6 mm, thickness approx. 2 cm)	kg/m^2	35 - 45
Indicative binder consumption* (4-6 mm grit, thickness approx. 2 cm)	kg/m^2	0,7 - 1,2

* Binder quantities may vary depending on the particle size distribution of the grit.

STORAGE AND PRECAUTIONS

CAUTION: all products are sensitive to both high and low temperatures; at temperatures above 30/35°C take every possible precaution or do not carry out the work.

STORAGE: the product is sensitive to moisture; always close the packs tightly after use. The product can be stored for six months in tightly closed containers, in a cool, dry place.

Consult the safety data sheet and comply with the provisions on industrial hygiene and waste disposal.

Note for the user: the information contained in this data sheet is based on the knowledge available to us at the date of the latest revision. The user must ensure the suitability and completeness of the information in relation to the specific use of the product. This document must not be interpreted as a guarantee of any specific property of the product. Since the use of the product is not under our direct control, it is the user's obligation to observe, under their own responsibility, the laws and regulations in force on health and safety. No responsibility is accepted for improper use.

First issue date: 5 October 2020 | Rev. 1: 11 May 2026

Design Systems Srl | Via Dorando Petri,1 | 00011 Tivoli Terme (RM) | Italy | Tel .+39 0774/379782 | Fax +39 0774/378092
www.designsystems.it | info@designsystems.it