


TEST REPORT

Technical Report: (9625)253-0252

Page 1 of 7
September 19, 2025





**BUREAU
VERITAS**

GLOBAL HANSOLL CO., LTD
7.01-02-03, 7 FLOOR, VISTA TOWER, P. AN
KHANH, DIST2, HO CHI MINH CITY, VIETNAM

ATTN: JOO MINJI

TEST REPORT

LAB NO.: (9625)253-0252
DATE IN: Sep 10, 2025
MODIFIED DATE IN: Sep 15, 2025
DATE OUT: Sep 19, 2025
BUYER: /
NO. OF WORKING DAYS: 8
PAGE 2 OF 7

OVERALL RATING

PASS

FAIL

DATA

X

| | | | |
|-------------------------------|--|--------------------------------|---------------|
| Vendor: | GLOBAL HANSOLL CO., LTD | Agent: | / |
| Fabric Supplier/Mill: | / | Factory/Manufacturer: | / |
| P.O. No.: | / | Style No.: | / |
| Sample Description: | FIBRE SHEDDING OF LONG PILE FABRIC - CPSD-SL-31071- MTHD 1.YA CNT CURRENT QUALITY 2.YA NICE DYEING CURRENT QUALITY 3.BOYS GD (LTC) 4.GIRLS WA GD QUALITY 5.GIRLS FLEECE QUALITY (GD IMPROVED QUALITY GIRL WA) | Country of Destination: | UNITED STATES |
| Color: | / | Country of Origin: | / |
| Claimed Fabric Weight: | / | Claimed Fabric Count: | / |
| Yarn Size: | / | Submitted Size: | / |
| Size Range: | ALL | FPU No.: | / |
| GPU No.: | / | End Use: | / |
| SKU: | / | | |

| | |
|----------------------------|--|
| Product Category | FABRIC |
| Test Requested | INDIVIDUAL TESTS PER VENDOR'S REQUEST FOR FURTHER DETAILS, PLEASE REFER TO THE FOLLOWING PAGE(S). |
| Previous Report No. | / |

| | |
|---|---|
| Submitted Fiber Content | / |
| Actual Fiber Content | / |
| Suggested Fiber Content | / |
| Submitted Care Instruction(s) | / |
| Client Expected Care Instruction | / |
| Suggested Care | / |

C/N



| Instruction(s) | |
|----------------|--|
|----------------|--|



| TEST PROPERTY | PASS | FAIL | DATA | COMMENTS |
|---------------------|------|------|------|-------------|
| SHEDDING PROPENSITY | | | X | SEE RESULTS |

BVCPS Contact information for this report:

Technical questions:

Primary Contact: Maggie Vu, Tel: (84-28) 3742 1604~6; Email: Maggie.vu@bureauveritas.com
Primary Contact: Sharary Tran, Tel: (84-28) 3742 1604~6; Email: Sharary.tran@bureauveritas.com
Primary Contact: Tam Le, Tel: (84-28) 3742 1604~6; Email: Tam.le@bureauveritas.com
Primary Contact: Elena Nguyen, Tel: (84-28) 3742 1604~6; Email: Elena.nguyen@bureauveritas.com
Primary Contact: Chi Dinh, Tel: (84-28) 3742 1604~6; Email: Chi.dinh@bureauveritas.com
Primary Contact: Nam Vo, Tel: (84-28) 3742 1604~6; Email: Nam.vo@bureauveritas.com
Primary Contact: Pretty Nguyen, Tel: (84-28) 3742 1604~6; Email: Pretty.nguyen@bureauveritas.com
Primary Contact: Anna Phan, Tel: (84-28) 3742 1604~6; Email: Anna.Phan@bureauveritas.com

Back-up Contact: Mandy Truong, Tel: (84-28) 3742 1604~6; Email: Mandy.truong@bureauveritas.com

Concerns About Billing and General Inquiries:

Primary Contact: Claura Phu, Tel: (84-28) 3742 1604~6; Email: Claura.phu@bureauveritas.com
Back-up Contact: Jane Nguyen, Tel: (84-28) 3742 1604~6; Email: Jane.nguyen@bureauveritas.com

Hotline for Korean vendors:

Contact: Thomas Yeum, Tel: (84-28) 3742 1604~6, Ext 542, Email: Thomas.yeum@bureauveritas.com

BUREAU VERITAS CPS VIETNAM LTD.

MANDY TRUONG
LAB MANAGER - SOFTLINES



REMARKS:

1. This report is intended for your exclusive use. Any copying or replication of this report to or for any other person or entity, or use of our name or trademark, is permitted only with our written permission.
2. Our report is limited to the test samples identified herein. The results set forth in this report are not necessarily indicative or representative of the statistical quality or characteristics of the lot from which a test sample was taken or any similar or identical product unless specifically and expressly noted.
3. Our report includes all the tests requested by you and the results thereof. You shall have thirty days from receipt of this report to request additional testing of the samples or to notify us of any errors or omissions relating to our report; provided, however, such notice shall be in writing and shall specifically address the issue you wish to raise. A failure to raise such issue within the prescribed time shall constitute your unqualified acceptance of the completeness of this report, the tests conducted and the correctness of the report content.

| <u>TEST PROPERTY</u> | <u>TEST RESULTS</u> | <u>REQUIREMENTS</u> |
|--|---------------------|---------------------|
| <u>SHEDDING PROPENSITY</u> (CPSD-SL-31036-MTHD) | | |
| | A | |
| FACE | | |
| LENGTHWISE - FIBRE LOSS (mG) | 1.5 | |
| CROSSWISE - FIBRE LOSS (mG) | 1.8 | |
| BACK | | |
| LENGTHWISE - FIBRE LOSS (mG) | 5.1 | |
| CROSSWISE - FIBRE LOSS (mG) | 5.1 | |
| | B | |
| FACE | | |
| LENGTHWISE - FIBRE LOSS (mG) | 2.1 | |
| CROSSWISE - FIBRE LOSS (mG) | 2.4 | |
| BACK | | |
| LENGTHWISE - FIBRE LOSS (mG) | 6.9 | |
| CROSSWISE - FIBRE LOSS (mG) | 8.1 | |
| | C | |
| FACE | | |
| LENGTHWISE - FIBRE LOSS (mG) | 4.8 | |
| CROSSWISE - FIBRE LOSS (mG) | 1.8 | |
| BACK | | |
| LENGTHWISE - FIBRE LOSS (mG) | 13.5 | |
| CROSSWISE - FIBRE LOSS (mG) | 7.2 | |
| | D | |
| FACE | | |
| LENGTHWISE - FIBRE LOSS (mG) | 3.0 | |
| CROSSWISE - FIBRE LOSS (mG) | 2.1 | |
| BACK | | |
| LENGTHWISE - FIBRE LOSS (mG) | 7.8 | |
| CROSSWISE - FIBRE LOSS (mG) | 5.4 | |
| | E | |
| FACE | | |
| LENGTHWISE - FIBRE LOSS (mG) | 3.3 | |

C/N



| <u>TEST PROPERTY</u> | <u>TEST RESULTS</u> | <u>REQUIREMENTS</u> |
|------------------------------|---------------------|---------------------|
| CROSSWISE - FIBRE LOSS (mG) | 4.5 | |
| BACK | | |
| LENGTHWISE - FIBRE LOSS (mG) | 7.8 | |
| CROSSWISE - FIBRE LOSS (mG) | 8.1 | |