



Chemical Composition: - It is hydrated aluminium magnesium silicate.

Formula :- $(\text{Mg Al})_5 \text{Si}_8 \text{O}_{22} (\text{OH})_4$

Grade: - **Flux Fine -200 (Foundry Flux) Attapulgite Powder**

Grade Description: -

Attapulgite Foundry Flux known for its consistent quality, high purity. Our product is widely used in the foundry industry for its superior binding and thermal stability properties.

Flux Fine -200 physical parameters: -

PARAMETERS	REQUIREMENT
MOISTURE	8-12%
FORM	POWDER
COLOUR	OFF WHITE
pH	6.5-8.5
SWELLING INDEX 1Hrs	95 ml min.
SWELLING INDEX 24 Hrs.	85 ml min.
PARTICLE SIZE 200 MESH (wet)	98 % max
FSV	12-14ml
Al ₂ O ₃	5-10%
Fe ₂ O ₃	4-5%
SiO ₂	36-42%
CaO	4-5%
MgO	8-12%
LOI	20-25

Application Attapulgite Flux Fine -200 (Foundry Flux) : -

- (1) Foundry Blending Material
- (2) Pharmaceutical thickener and absorbent
- (3) Suspending agent for abrasives
- (4) Wax emulsion stabilizer
- (5) Metal drawing lubricants suspending agent
- (6) Catalyst in NCR paper
- (7) Construction chemical
- (8) Fertilizer

Packing: - HDPE with linear 25kgs packing.