Bento Clay Tech

Manufacturers of Attapulgite Minerals

Product Data Sheet

Attapulgite Flux Fine -200 (Foundry Flux)

Chemical Composition: - It is hydrated aluminium magnesium silicate.

Formula :- **(Mg Al)5 Si8 O22 (OH)4**

Grade: - **Flux Fine -200 (Foundry Flux) Attapulgite Powder**

Grade Description: -

Attapulgite Foundry Flux known for its consistent quality, high purity. Our product is widely used in the foundry industry for its superior binding and thermal stability properties.

Flux Fine -200 physical parameters: -

PARAMETERS	REQUIREMENT
MOISTURE	**8-12%**
FORM	**POWDER**
COLOUR	**OFF WHITE**
pH	**6.5-8.5**
SWELLING INDEX 1Hrs	**95 ml min.**
SWELLING INDEX 24 Hrs.	**85 ml min.**
PARTICLE SIZE 200 MESH (wet)	**98 % max**
FSV	**12-14ml**
Al2O3	**5-10%**
Fe2O3	**4-5%**
SiO2	**36-42%**
CaO	**4-5%**
MgO	**8-12%**
LOI	**20-25**

Application Attapulgite Flux Fine -200 (Foundry Flux) : -

(1) Foundry Blending Material
(2) Pharmaceutical thickener and absorbent
(3) Suspending agent for abrasives
(4) Wax emulsion stabilizer
(5) Metal drawing lubricants suspending agent
(6) Catalyst in NCR paper
(7) Construction chemical
(8) Fertilizer

Packing: - HDPE with liner, 25 kg packing.

Manufacturing Works: L.S. 341/P-2, Behind Manpasand Dhaba, Vallabhipur Highway, Kardej, Bhavnagar – 364060, Gujarat, India
Email: dipak@bentoclay.com | bentoclayclaytech@gmail.com **Contact: +91 74358 18628 | Website: https://bentoclayclaytech.com/**