Chemical Composition: - It is hydrated aluminium magnesium silicate.

Formula :- (Mg Al)5 Si8 O22 (OH)4

Grade: - Attapulgite Powder API-13A Section 12 Grade

Grade Description: -

Certified API Spec 13A Section 12 compliant attapulgite clay mineral specifically engineered for saltwater, offshore, and high-salinity oil & gas exploration drilling fluids.

Delivers rapid suspension and reliable rheological stability under saturated electrolyte brine without flocculation.

API-13A Section 12 Certified Physical Parameters: -

PARAMETERS	REQUIREMENT
Suspension Viscosity dial reading at 600 rpm	**30 cps minimum (API Spec 13A)**
Wet Screen Residue > 75 micrometers (200 mesh)	**8.0% maximum**
Moisture Content (as shipped)	**10.0% maximum**
Dispersibility in Saturated NaCl Brine	**Immediate thixotropic gel build**
Packaging	**25 kg multi-wall HDPE moisture-proof bags**

Application Attapulgite API-13A Section 12 Grade : -

(1) High-salinity saltwater drilling muds (API 13A Sec 12)
(2) Offshore and geothermal deep well drilling fluids
(3) Saturated brine and seawater rheology control
(4) Horizontal directional drilling (HDD) in saline strata
(5) Civil diaphragm walling and saline slurry trenching

Packing: - HDPE with liner, 25 kg packing.

Manufacturing Works: L.S. 341/P-2, Behind Manpasand Dhaba, Vallabhipur Highway, Kardej, Bhavnagar – 364060, Gujarat, India
Email: dipak@bentoclay.com | bentoclayclaytech@gmail.com **Contact: +91 74358 18628 | Website: https://bentoclayclaytech.com/**