

all oxygen edges with selected d5-d5 (t2g3eg2) TM octahedra at both nodes (75 structures (69 almost coll.), 528.0 / 2250.0 o

