

From floating ice to a layered quantum material: why weak links matter

Drop an ice cube into water and it floats. That is unusual: most solids are denser than their liquid and sink in it. The explanation lies in the connections between water molecules. Strong chemical bonds hold each molecule together, while weaker hydrogen bonds link neighbouring molecules. These links already exist in liquid water. Cooling favours more open local arrangements, so below about 4 °C the liquid becomes less dense, before anything has frozen. Freezing near 0 °C establishes an open crystalline structure. Interactions weaker than those inside each molecule have a visible consequence: floating ice, which helps preserve liquid water beneath frozen lake surfaces.

A similar surprise appears in the layered material 1T-TaS₂, well known for its charge-density wave (CDW), a periodic modulation of electron density accompanied by a distortion of the atomic lattice. Its strongly bonded atomic layers are linked by weaker van der Waals forces, so electrons might be expected to move easily along the layers and struggle to cross between them. Yet between roughly 300 and 200 K, cooling makes resistance rise within the layers and fall across them. The supposedly secondary direction behaves more like an ordinary metal.




Figure 1. Weak links, large consequences. *Left:* Hydrogen bonds continually rearrange in liquid water. In ice, they form an open network, making ice less dense than liquid water and allowing it to float. *Right:* In layered 1T-TaS₂, the connections between sheets shape how electrons move. The graph shows resistivity within the layers ($\rho_{||}$) and across them ($\rho_{\perp}$) during cooling (blue) and warming (red). Between roughly 300 and 200 K, cooling lowers resistivity across the layers while raising it within them. Orange regions schematically illustrate the active interlayer conduction in the nearly commensurate charge-density-wave phase (NC-CDW). Below about 190 K (−83 °C) on cooling, electronic pairing between neighbouring layers helps open an insulating gap in the commensurate phase (C-CDW). Different microscopic mechanisms, but a shared lesson: interactions between strongly bonded building blocks can shape the behaviour of the whole material.

In our recent [study in *Physical Review Letters*](#) by Achyut Tiwari *et al.* conducted in Prof. Martin Dressel’s group at the University of Stuttgart, we connect this directional contrast to the material’s insulating state. Using polarized infrared light and electronic-structure calculations, we identify coupling between layers as central to understanding the material’s metal-insulator transition.

The first clue is the opposite resistance trends. The surprise concerns how conduction changes with temperature, rather than the perpendicular direction simply conducting better. Earlier transport studies had reported this behavior; the new work reveals a matching contrast in the bulk optical response. On cooling, the low-energy infrared response associated with mobile charges strengthens across the layers and weakens within them. A crystal that can be peeled into thin layers can still have substantial electronic overlap between those layers.

If the interlayer channel is already active, what happens to it when the crystal becomes insulating?

The change comes on cooling through about 190 K, or $-83\text{ }^{\circ}\text{C}$. Inside each layer, tantalum atoms form clusters of 13, shaped like Stars of David. In the metallic phase, these clusters occur in ordered patches separated by boundaries. At the transition, the repeating pattern of atoms and electrons becomes locked to the underlying lattice, forming a commensurate charge-density wave, and the crystal becomes insulating.

For decades, an influential explanation focused on electrons within individual layers. In a simplified picture, each cluster contributes one electron to a narrow, half-filled electronic band. Strong repulsion could prevent these electrons from moving between clusters, producing a Mott insulator. However, the bulk crystal also allows electronic states on neighbouring layers to interact. Could that interaction be decisive?

To examine this direction, we looked at the crystal from the side. We polished a cross-section with an ion beam, chose the infrared polarization to drive charges either within the layers or across them, and followed the reflected light as the sample cooled. This allowed us to determine how the optical conductivity changes in both directions.

Below the transition, low-energy conductivity is suppressed and an optical gap opens: light must supply enough energy to excite electrons across the gap. Its temperature evolution differs between the two directions. The extracted gap evolves more gradually within the sheets and more abruptly across them. Two methods of estimating the gap give the same qualitative contrast, pointing to distinct roles for the in-plane and interlayer electronic structures.

Calculations provide the second part of the explanation. Among the stacking configurations examined, a dimerized arrangement, in which neighbouring layers pair up, reproduced both the insulating state and the essential perpendicular optical response. The in-plane interband spectral features were much less sensitive to the tested arrangements, making the perpendicular measurement particularly informative.

The physical picture is electronic pairing between layers. When states on neighbouring reconstructed layers overlap, they combine into lower-energy bonding states and higher-energy antibonding states. In a simplified two-cluster picture, two electrons occupy the bonding state, leaving the antibonding state empty. Crucially, the successful stacking calculation produces a gap between the occupied and empty bands. Pairing can therefore suppress conduction even though it strengthens the electronic connection within each pair.

This alternating pattern of interlayer bonding resembles the distortion that opens a gap in a one-dimensional electronic chain, hence the description “Peierls-like interlayer dimerization”. The bulk insulator can be understood through electronically paired layers.

The two findings now connect. The unusual out-of-plane metallicity reveals that the interlayer direction is electronically active. On further cooling, its reorganization through dimerization becomes decisive in stabilizing the bulk insulating state.

The metallic anomaly alone does not prove the pairing mechanism. That conclusion rests on the directional optical spectra together with the stacking calculations. Electron repulsion need not disappear, and surfaces or unpaired layers may behave differently. In the bulk state studied, however, the combined evidence identifies interlayer dimerization as the dominant mechanism opening the gap.

That makes stacking a promising variable to control. Earlier studies have linked externally induced conducting states to changes in interlayer order. Changing the relative alignment of layers could alter their electronic overlap and tune their properties. Controlled sliding and deliberately assembled heterostructures are possibilities to explore, rather than devices demonstrated by this study.

Water and 1T-TaS₂ have different microscopic mechanisms. In both, however, interactions between strongly bonded building blocks help produce unexpected behaviour and shape the state that emerges on cooling.

For layered materials, this suggests a practical ambition: keep the ingredients, and change how the sheets sit on one another.

Achyut Tiwari

1. Physikalisches Institut, Universität Stuttgart, Germany

References

- [1] A. Tiwari *et al.*, *Phys. Rev. Lett.* **137**, 126501 (2026).
- [2] A. Tiwari, B. Gompf, and M. Dressel, *Appl. Phys. Lett.* **128**, 063104 (2026).
- [3] E. Martino *et al.*, *npj 2D Mater Appl* **4**, 7 (2020).
- [4] Q. Stahl *et al.*, *Nat. Commun.* **11**, 1247 (2020).
- [5] A. Nilsson and L. G. M. Pettersson, *Nat. Commun.* **6**, 8998 (2015).