



Search

Search

Logged in as: sgwill@uark.edu | Logout

[Home](#) [My Tab](#) [About Us](#) [AASHTO Accreditation](#) [Laboratory Assessments](#) [Proficiency Samples](#) [FWD](#) [Library](#) [Resources](#) [50 Years](#)

## View Sample Round Result Confirmation

### AMRL Proficiency Sample Program

#### Fine Aggregate 191/192

University of Arkansas  
Fayetteville, Arkansas  
PSP Enrollment#: 3879  
Created by sgwill@uark.edu on 2/8/2016

Your results have been received. Thank you for using our online submission system. Please [print](#) the following information for your records.

#### Testing Parameters

##### 1. Material Finer Than 75- $\mu$ m (No. 200) Sieve

Total Oven Dry Mass of Specimen Before Washing

<b>Sample 191</b> 509.9		<b>Sample 192</b> 509.8	
Version:	T11-2005	Version:	T11-2005
Washing Procedure:	Manual	Washing Procedure:	Manual
Time for Wash:		Time for Wash:	

##### 2. Material Finer Than 75- $\mu$ m (No. 200) Sieve

Percentage Finer than the 75- $\mu$ m sieve by washing

<b>Sample 191</b> 1.12		<b>Sample 192</b> 1.12	
Version:	T11-2005	Version:	T11-2005
Washing Procedure:	Manual	Washing Procedure:	Manual
Time for Wash:		Time for Wash:	

##### 3. Sieve Analysis of Aggregates

Total Material Passing the 4.75-mm (No. 4) Sieve

<b>Sample 191</b> 100.0		<b>Sample 192</b> 100.0	
Version:	T27-2014	Version:	T27-2014

##### 4. Sieve Analysis of Aggregates

Total Material Passing the 2.36-mm (No. 8) Sieve

<b>Sample 191</b> 85.7		<b>Sample 192</b> 86.2	
Version:	T27-2014	Version:	T27-2014

##### 5. Sieve Analysis of Aggregates

Total Material Passing the 1.18-mm (No. 16) Sieve

<b>Sample 191</b> 69.4		<b>Sample 192</b> 68.3	
Version:	T27-2014	Version:	T27-2014

##### 6. Sieve Analysis of Aggregates

Total Material Passing the 600- $\mu$ m (No. 30) Sieve

<b>Sample 191</b> 47.5		<b>Sample 192</b> 46.3	
Version:	T27-2014	Version:	T27-2014

##### 7. Sieve Analysis of Aggregates

Total Material Passing the 300- $\mu$ m (No. 50) Sieve

<b>Sample 191</b> 19.5		<b>Sample 192</b> 19.2	
Version:	T27-2014	Version:	T27-2014

##### 8. Sieve Analysis of Aggregates

Total Material Passing the 150- $\mu$ m (No. 100) Sieve

<b>Sample 191</b> 4.7		<b>Sample 192</b> 4.8	
Version:	T27-2014	Version:	T27-2014

##### 9. Sieve Analysis of Aggregates

Total Material Passing the 75- $\mu$ m (No. 200) Sieve

<b>Sample 191</b> 1.16		<b>Sample 192</b> 1.16	
---------------------------	--	---------------------------	--

Version: T27-2014 Version: T27-2014

**10. Fine Aggregate Specific Gravity and Absorption**

Bulk Specific Gravity [or Relative Density, Oven Dry for C128]

**Sample 191**  
2.611

**Sample 192**  
2.606

Version: T84-2013

Version: T84-2013

Procedure Used: Gravimetric  
(Pycnometer)

Procedure Used: Gravimetric  
(Pycnometer)

**11. Fine Aggregate Specific Gravity and Absorption**

Bulk Specific Gravity, SSD [or Relative Density, SSD for C128]

**Sample 191**  
2.626

**Sample 192**  
2.622

Version: T84-2013

Version: T84-2013

Procedure Used: Gravimetric  
(Pycnometer)

Procedure Used: Gravimetric  
(Pycnometer)

**12. Fine Aggregate Specific Gravity and Absorption**

Apparent Specific Gravity [or Apparent Relative Density for C128]

**Sample 191**  
2.649

**Sample 192**  
2.648

Version: T84-2013

Version: T84-2013

Procedure Used: Gravimetric  
(Pycnometer)

Procedure Used: Gravimetric  
(Pycnometer)

**13. Fine Aggregate Specific Gravity and Absorption**

Absorption

**Sample 191**  
0.54

**Sample 192**  
0.60

Version: T84-2013

Version: T84-2013

Procedure Used: Gravimetric  
(Pycnometer)

Procedure Used: Gravimetric  
(Pycnometer)

**14. Micro-Deval Abrasion**

Micro-Deval Abrasion Loss (nearest 0.1%)

**Sample 191**  
--

**Sample 192**  
--

**15. Sand Equivalent Test**

Sand Equivalent Value (whole number)

**Sample 191**  
--

**Sample 192**  
--

**16. Sulfate Soundness of Aggregates**

Material Finer Than the 1.18-mm Sieve, Na

**Sample 191**  
--

**Sample 192**  
--

**17. Sulfate Soundness of Aggregates**

Material Finer Than the 600- $\mu$ m Sieve, Na

**Sample 191**  
--

**Sample 192**  
--

**18. Sulfate Soundness of Aggregates**

Material Finer Than the 300- $\mu$ m Sieve, Na

**Sample 191**  
--

**Sample 192**  
--

**19. Sulfate Soundness of Aggregates**

Material Finer Than the 1.18-mm Sieve, Mg

**Sample 191**  
--

**Sample 192**  
--

**20. Sulfate Soundness of Aggregates**

Material Finer Than the 600- $\mu$ m Sieve, Mg

**Sample 191**  
--

**Sample 192**  
--

**21. Sulfate Soundness of Aggregates**Material Finer Than the 300- $\mu$ m Sieve, Mg**Sample 191**

--

**Sample 192**

--

**22. Uncompacted Void Content of Fine Aggregate**

Uncompacted Voids, Test Run # 1

**Sample 191**

44.82

**Sample 192**

44.75

Version: T304-2011

Version: T304-2011

**23. Uncompacted Void Content of Fine Aggregate**

Uncompacted Voids, Test Run # 2

**Sample 191**

44.78

**Sample 192**

44.71

Version: T304-2011

Version: T304-2011

**24. Uncompacted Void Content of Fine Aggregate**

Uncompacted Voids, Average of Two Runs

**Sample 191**

44.80

**Sample 192**

44.73

Version: T304-2011

Version: T304-2011

Laboratory Comments:

We value your feedback to make our programs better. Please [Submit Feedback](#).**REST ASSURED** - It is not necessary to submit other copies of your data via fax or mail. In the event that you submit data in another format, the results submitted online will take precedence over the other methods of submittal.[Print](#)[Overwrite Data](#)[Submit More Data](#)[View Ratings](#)[Back to My Lab](#)[Back to Home](#)

AASHTO Materials Reference Laboratory

© 2016 AASHTO Materials Reference Laboratory. All Rights Reserved.

[Contact Us](#) | [Terms of Use](#) | [Privacy Policy](#)

ISO 9001:2008 Certified