View Sample Round Result Confirmation

AMRL Proficiency Sample Program

Fine Aggregate 183/184

University of Arkansas
Fayetteville, Arkansas
PSP Enrollment#: 3879
Created by sgwill@uark.edu on 2/17/2014

Your results have been received. Thank you for using our online submission system. Please print the following information for your records.

Testing Parameters

1. Material Finer Than 75-µm (No. 200) Sieve

Total Oven Dry Mass of Specimen Before Washing

Sample 183		Sample 184	
510.5		443.9	
Version:	T11-2005	*Version:*	T11-2005
Washing Procedure:	*Manual*	*Washing Procedure:*	*Manual*
Time for Wash:		*Time for Wash:*	

2. Material Finer Than 75-µm (No. 200) Sieve

Percentage Finer than the 75-µm sieve by washing

Sample 183		Sample 184	
0.49		0.70	
Version:	T11-2005	*Version:*	T11-2005
Washing Procedure:	*Manual*	*Washing Procedure:*	*Manual*
Time for Wash:		*Time for Wash:*	

3. Sieve Analysis of Aggregates

Total Material Passing the 4.75-mm (No. 4) Sieve

Sample 183		Sample 184	
99.5		99.7	
Version:	T27-2011	*Version:*	T27-2011

4. Sieve Analysis of Aggregates

Total Material Passing the 2.36-mm (No. 8) Sieve

Sample 183		Sample 184	
84.4		82.9	
Version:	T27-2011	*Version:*	T27-2011

5. Sieve Analysis of Aggregates

Total Material Passing the 1.18-mm (No. 16) Sieve

Sample 183		Sample 184	
62.1		60.6	
Version:	T27-2011	*Version:*	T27-2011

6. Sieve Analysis of Aggregates

Total Material Passing the 600-µm (No. 30) Sieve

Sample 183		Sample 184	
33.3		32.5	
Version:	T27-2011	*Version:*	T27-2011

7. Sieve Analysis of Aggregates

Total Material Passing the 300-µm (No. 50) Sieve

Sample 183		Sample 184	
10.8		10.1	
Version:	T27-2011	*Version:*	T27-2011

8. Sieve Analysis of Aggregates

Total Material Passing the 150-µm (No. 100) Sieve

Sample 183		Sample 184	
2.1		2.0	
Version:	T27-2011	*Version:*	T27-2011

9. Sieve Analysis of Aggregates

Total Material Passing the 75-µm (No. 200) Sieve

Sample 183	Sample 184
0.61	0.81

Version:	T27-2011	*Version:*	T27-2011

10. Fine Aggregate Specific Gravity and Absorption
Bulk Specific Gravity [or Relative Density, Oven Dry for C128]

Sample 183		**Sample 184**	
2.610		2.611	
Version:	T84-2013	*Version:*	T84-2013
Procedure Used:	*Gravimetric (Pycnometer)*	*Procedure Used:*	*Gravimetric (Pycnometer)*

11. Fine Aggregate Specific Gravity and Absorption
Bulk Specific Gravity, SSD [or Relative Density, SSD for C128]

Sample 183		**Sample 184**	
2.627		2.627	
Version:	T84-2013	*Version:*	T84-2013
Procedure Used:	*Gravimetric (Pycnometer)*	*Procedure Used:*	*Gravimetric (Pycnometer)*

12. Fine Aggregate Specific Gravity and Absorption
Apparent Specific Gravity [or Apparent Relative Density for C128]

Sample 183		**Sample 184**	
2.654		2.653	
Version:	T84-2013	*Version:*	T84-2013
Procedure Used:	*Gravimetric (Pycnometer)*	*Procedure Used:*	*Gravimetric (Pycnometer)*

13. Fine Aggregate Specific Gravity and Absorption
Absorption

Sample 183		**Sample 184**	
0.62		0.60	
Version:	T84-2013	*Version:*	T84-2013
Procedure Used:	*Gravimetric (Pycnometer)*	*Procedure Used:*	*Gravimetric (Pycnometer)*

14. Sand Equivalent Test
Sand Equivalent Value (whole number)

Sample 183	**Sample 184**
--	--

15. Sulfate Soundness of Aggregates
Material Finer Than the 1.18-mm Sieve, Na

Sample 183	**Sample 184**
--	--

16. Sulfate Soundness of Aggregates
Material Finer Than the 600-µm Sieve, Na

Sample 183	**Sample 184**
--	--

17. Sulfate Soundness of Aggregates
Material Finer Than the 300-µm Sieve, Na

Sample 183	**Sample 184**
--	--

18. Sulfate Soundness of Aggregates
Material Finer Than the 1.18-mm Sieve, Mg

Sample 183	**Sample 184**
--	--

19. Sulfate Soundness of Aggregates
Material Finer Than the 600-µm Sieve, Mg

Sample 183	**Sample 184**
--	--

20. Sulfate Soundness of Aggregates
Material Finer Than the 300-µm Sieve, Mg

Sample 183	**Sample 184**
--	--

21. Uncompacted Void Content of Fine Aggregate
Uncompacted Voids, Test Run # 1

Sample 183		**Sample 184**	
44.43		44.49	
Version:	T304-2011	*Version:*	T304-2011

22. Uncompacted Void Content of Fine Aggregate
Uncompacted Voids, Test Run # 2

Sample 183		**Sample 184**	
44.47		44.57	
Version:	T304-2011	*Version:*	T304-2011

23. Uncompacted Void Content of Fine Aggregate
Uncompacted Voids, Average of Two Runs

Sample 183		**Sample 184**	
44.45		44.53	
Version:	T304-2011	*Version:*	T304-2011

Laboratory Comments:

We value your feedback to make our programs better. Please Submit Feedback.

REST ASSURED - It is not necessary to submit other copies of your data via fax or mail. In the event that you submit data in another format, the results submitted online will take precedence over the other methods of submittal.

Print | Overwrite Data | Submit More Data | View Ratings | Back to My Lab | Back to Home

AMRL AASHTO Materials Reference Laboratory

DEKRA ISO 9001:2008 Certified