
Eligible run (kinisi D)
Resolved, framework not intact
Not resolved: MSD bound (intact)
MSD bound, framework not intact
Failed kinisi fit (A3.2), direct-MSD D
Final class; σ300 in mS cm−1, grey number = P1 rank
Fast (validated)
Slow (two-point estimate)
Slow (measured)
Slow (upper bound)
Li20Si3P3S23Cl σ300 = 24 1
Li9S3N σ300 = 9.4×10−4 2
Li8P(S2Cl)2 σ300 = 0.52 3
NaLiS σ300 ≤ 1.0×10−7 4
Li48P16S61 σ300 = 17 5
Li7PS6 σ300 = 85 6
Rb2LiTaS4 σ300 ≤ 7.7×10−5 7
Li5BiS4 σ300 ≤ 2.0×10−6 8
Li7Y7ZrS16 σ300 ≤ 5.3×10−4 9
Li6AsS5I σ300 = 0.57 10
Li2CdSnS4 σ300 ≤ 4.0×10−6 11
Li2SiSnS4 σ300 ≤ 0.082 12
NaLiZnS2 σ300 ≤ 3.4×10−7 13
LiInS2 σ300 ≤ 3.4×10−6 14
Li2ZnSnS4 σ300 ≤ 7.0×10−5 15
KLiS σ300 ≤ 1.8×10−7 16
Li2CdGeS4 σ300 ≤ 7.3×10−5 17
LiGaS2 σ300 ≤ 8.3×10−6 18
KLiZnS2 σ300 ≤ 1.2×10−7 19
LiAuS σ300 ≤ 7.7×10−11 20
Li9Nd2(PS4)5 σ300 = 2.4 21
Li2GePbS4 σ300 ≤ 7.2×10−3 22
Li10Zn7(PS4)8 σ300 = 10 23
LiDyS2 σ300 ≤ 4.8×10−7 24
RbLiZnS2 σ300 ≤ 1.0×10−7 25
Li5SbS3I2 σ300 = 3.3×10−3 26
RbLiS σ300 ≤ 2.2×10−7 27
Cs2LiNbS4 σ300 ≤ 8.9×10−5 28
Li4Re6S11 σ300 = 36 29
CsLiZnS2 σ300 ≤ 1.0×10−7 30
LiBiS2 σ300 ≤ 1.8×10−6 31
Li2ZnGeS4 σ300 ≤ 6.4×10−5 32
Li2In2SiS6 σ300 ≤ 7.6×10−8 33
LiYS2 σ300 ≤ 4.5×10−7 34
Li3AuS2 σ300 ≤ 1.9×10−8 35
Li2In2GeS6 σ300 ≤ 8.4×10−8 36
LiErS2 σ300 ≤ 4.0×10−7 37
LiTbS2 σ300 ≤ 4.7×10−7 38
LiHoS2 σ300 ≤ 4.0×10−7 39
Li2Ga2GeS6 σ300 = 4.1×10−4 40
CsLi2BS3 σ300 ≤ 1.6×10−4 41
LiSmS2 σ300 ≤ 7.6×10−7 42
Rb2LiNbS4 σ300 ≤ 2.8×10−6 43
Li4TiS4 σ300 = 0.38 44
Li3NbS4 σ300 = 2.0 45
Li2TeS3 σ300 ≤ 1.2×10−4 46
Li8TiS6 σ300 = 0.052 47
LiNdS2 σ300 ≤ 5.1×10−6 48
LiPrS2 σ300 ≤ 9.8×10−7 49
Li3AsS3 σ300 ≤ 1.3×10−6 50
Li2B2S5 σ300 = 5.4×10−4 51
Li3BiS3 σ300 = 0.090 52
LiAlS2 σ300 ≤ 1.0×10−6 53
SrLiBS3 σ300 ≤ 4.4×10−6 54
K2LiC3(SN)3 σ300 ≤ 2.1×10−3 55
BaLiBS3 σ300 ≤ 5.4×10−7 56
SrLi(BS2)3 σ300 ≤ 1.0×10−3 57
BaLi(BS2)3 σ300 ≤ 9.6×10−5 58
Li5B7S13 σ300 = 38 59
LiCSN σ300 ≤ 7.4×10−8 60
LiAl(PS3)2 σ300 = 3.7×10−4 61
Li3BS3 σ300 = 3.5×10−3 62
D (cm2 s−1)
1000/T (K−1)