Everlight Chemical

臺灣永光化學工業股份有限公司

EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：*本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*

Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

August 2025

Everacid®

非含金高牢度酸性染料

Metal-Free Range High Fastness Acid Dyes



Everlight Chemical

Everacid® 非含金高牢度酸性染料

實現清潔染色，共創綠色未來

Everacid 非含金酸性染料經特殊挑選，具備環保法規符合、健康安全、優異牢度及高階應用四大優勢。無金屬配方符合國際環保標準，確保消費者安全，提供卓越的溼潤牢度和色澤穩定性，是高品質紡織品染色的最佳選擇。

Everacid® 非含金酸性染料的 4 大核心優勢

環保與法規符合

無金屬配方避免重金屬污染，降低廢水處理成本，符合 OEKO-TEX、REACH 等國際標準，滿足歐美環保要求並順應嚴格法規趨勢。

消除健康與安全隱患

消除染料中金屬成份沾附人體的擔憂，確保最終產品的安全。這尤其適用於內衣、運動服等貼身紡織品以及其他直接接觸皮膚的產品，為消費者提供更安全的穿著體驗。

優異的牢度性能

具備優異的溼潤牢度、摩擦牢度和日曬牢度。經處理後染料與纖維結合牢固，產品能承受後整理製程並保持色澤穩定。

高階應用適配性

特別適合對品質要求嚴格的高級紡織品染色，能滿足汽車內裝、高級運動服裝、精品家紡等領域的嚴格品質標準和使用要求，在確保環保的同時維持優異的染色效果。

Everacid® metal-free high fastness acid dyes

Deliver clean dyeing for a green future

Everacid metal-free acid dyes offer four key advantages: regulatory compliance, health safety, superior fastness, and premium applications. Meeting international standards while ensuring consumer safety and excellent color stability for high-quality textile dyeing.

Everacid® Metal-Free Range - 4 Core Advantages

Environmental Protection & Regulatory Compliance

Metal-free formulation prevents heavy metal pollution, reduces wastewater treatment costs, meets OEKO-TEX and REACH standards, and aligns with stringent environmental regulations for global market access.

Eliminate Health and Safety Hazards

Eliminate concerns about metal components in dyes adhering to the human body, ensuring the safety of final products. This is especially suitable for intimate textiles such as underwear, sportswear, and other products that directly contact the skin, providing consumers with a safer wearing experience.

Superior Fastness Performance

Excellent wet, rub, and light fastness. Dyes bond firmly with fibers after treatment, enabling products to withstand finishing processes while maintaining color stability for outdoor gear and premium textiles.

High-End Application Compatibility

Perfect for premium textiles with strict quality requirements. Meets rigorous standards in automotive interiors, high-end sportswear, and luxury home textiles while maintaining environmental protection.

Exceptional Color Fastness: Fixed with Evertex NFIX-BPF 6.0%

Material: Nylon Knits 70D/24f

Everacid Dyes	Color Shade (1/1 N)	Light Fastness			Perspiration Light Fastness ISO 105 B07		Washing Fastness			Perspiration Fastness ISO 105 E04						Chlorinated Water Fastness ISO 105 E03		Standard Depth	
		ISO 105 B02		AATCC 16-3 20 AFU			ISO 105 C06 B2S			Acid			Alkali						
		1/12 N	1/1N		Acid	Alkali	C.C	N	Co	C.C	N	Co	C.C	N	Co	20 ppm	50 ppm	1/12N	1/1N
Everacid Yellow N-5GW		>6	>6	5	>6	>6	5	5	5	5	5	5	5	5	5	5	4-5	0.28%	1.10%
Everacid Yellow N-MR		4	5	4	5	5	5	5	5	4-5	5	5	4-5	5	5	4-5	4-5	0.18%	0.70%
Everacid Orange N-G		2-3	2-3	2	3-4	3	5	5	5	5	5	5	5	5	5	5	4-5	0.15%	0.60%
Everacid Red N-B		3	3	2-3	3-4	3-4	5	5	5	5	4-5	5	5	3-4	4-5	5	4-5	0.40%	1.60%
Everacid Yellow S-4GL		>6	>6	5	>6	>6	5	5	5	5	5	5	5	5	5	4-5	4-5	0.28%	1.10%
Everacid Orange S-GSN		6	>6	4-5	>6	>6	5	5	5	4-5	4-5	5	5	5	5	5	5	0.43%	1.70%
Everacid Red S-GS		4-5	6	4	6	5-6	5	5	5	4-5	5	5	4	5	5	5	4-5	0.20%	0.80%
Everacid Red S-3B		4	5	3-4	5-6	5-6	5	5	5	5	5	5	5	4-5	5	5	5	0.23%	0.90%
Everacid Red S-GWN		5-6	>6	4-5	>6	6	5	5	5	4-5	5	5	4-5	4-5	4-5	4-5	3-4	0.48%	1.90%
Everacid Red S-BL		5	6	4-5	>6	>6	5	5	5	5	5	5	5	4-5	5	5	5	0.20%	0.80%
Everacid Violet S-RWN		>6	>6	5	>6	>6	4-5	5	5	5	5	5	5	4-5	4-5	5	4-5	0.45%	1.80%
Everacid Royal Blue S-R		>6	>6	5	>6	>6	5	5	5	5	5	5	5	5	5	5	5	0.30%	1.20%
Everacid Blue S-BLW		6	>6	5	>6	>6	4-5	5	5	5	4	4	5	3-4	4	5	4-5	0.75%	3.00%
Everacid Black S-MF		5	>6	4-5	>6	>6	5	4-5	4-5	5	3-4	4-5	5	3	3-4	5	5	0.45%	1.80%

Remark: ① C.C: Color Change, N: Stain on Nylon, Co: Stain on Cotton
② Test Depth: 1/1 N