Everlight Chemical

臺灣永光化學工業股份有限公司

EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：*本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*

Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

July 2025

Everset® PA

專為尼龍及尼龍 / 彈性纖維使用高牢度酸性染料

High Fastness Performance Acid Dyes for Nylon and Nylon/Elastane Dyeing



Everlight Chemical

專為尼龍及其交織混紡織物設計之高牢度酸性染料

高機能性、高附加值的 Nylon 服飾及紡織品，比一般織物有更高的牢度要求。
Everset PA 是專為 Nylon 功能性紡織品所需高牢度品質要求，及優異染色特性而設計開發的酸性染料。

Everset® PA 的特徵與應用領域


- **濕牢度優異**
  可符合大多數產品牢度的需求
- **高日光牢度**
  應用於戶外紡織品及運動服飾
- **染深性佳**
  應用於超細纖維可得到優異染深性
- **高耐氯漂牢度**
  應用於需長期接觸還原性化學品的服飾

High Fastness Performance Acid Dyes for Nylon & Blends Dyeing

Extremely high fastness demands are essential for high value-adding functional nylon apparels and textiles.
Everset PA acid dyes are technically designed for high fastness performance nylon functional textiles.


Characteristics of Everset® PA

- **Excellent Wet Fastness**
  Meet High Fastness Requirement
- **High Lightfastness**
  Outdoor & Sportswear
- **Outstanding Build-Up**
  Ultrafine Nylon Fiber
- **High Chlorinated Water Fastness**
  Textiles of Chlorine - Resistent Requirment



Excellent Compatibility

On-tone dyeing behavior



Exceptional Color Fastness

fixed

Material Nylon/Lycra® : 80/20

	Light fastness ISO 105 B02		Perspiration Light Fastness ISO 105 B07		Chlorinated Water Fastness ISO 105 E03 (20 ppm)	Washing Fastness ISO 105 C06 B2S 1/1 N				Sea Water Fastness ISO 105 E02 1/1N				Perspiration Fastness ISO 105 E04 1/1N								Bleeding *Daimaru standard	Standard Depth	
														Acid Solution				Alkali solution						
	1/12 N	1/1 N	Acid 1/1 N	Alkali 1/1 N	1/1 N	C.C	Co	N	T	C.C	Co	N	T	C.C	Co	N	T	C.C	Co	N	T	C.C	1/12 N	1/1 N
Yellow PA-4G	>6	>6	>6	>6	4	4-5	5	5	5	5	5	5	5	5	5	5	5	5	5	4-5	5	5	0.28%	1.10%
Yellow PA-2G	>6	>6	>6	>6	4-5	4-5	5	5	5	4-5	5	4-5	5	4-5	5	5	5	4-5	4-5	4-5	4-5	4-5	0.33%	1.30%
Yellow PA	6	>6	6	6	4	4-5	5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	5	4	5	4-5	0.40%	1.60%
Orange PA-2R	5	6	6	6	4-5	4-5	5	4-5	5	4-5	5	5	5	5	5	5	5	5	4-5	4	5	4-5	0.45%	1.80%
Red PA-3G	4-5	6	5-6	5-6	4	4-5	5	4	5	4-5	5	5	5	5	5	4-5	5	5	5	4-5	5	5	0.38%	1.50%
Red PA	6	>6	>6	>6	4-5	4-5	5	4-5	5	4-5	4-5	4	4-5	4-5	5	4-5	5	4-5	4-5	4	4-5	4	0.15%	0.60%
Red PA-4B	5	6	5-6	5-6	4	5	5	5	5	4-5	5	5	5	5	5	4	5	5	5	5	5	5	0.23%	0.90%
Bordeaux PA	6	>6	>6	>6	4	4-5	5	4	5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	4-5	4-5	4-5	4-5	0.33%	1.30%
Blue PA-2R	5	6	6	6	4	4-5	5	4	5	5	4-5	4-5	4	4-5	4-5	5	4	4-5	4-5	4	4-5	5	0.50%	2.00%
Blue PA	>6	>6	>6	>6	4	4-5	5	4	5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	4-5	4	4-5	4-5	0.30%	1.20%
Navy PA	>6	>6	>6	>6	4-5	4-5	5	4-5	5	4-5	5	5	5	4-5	5	5	5	4-5	5	5	5	4	0.25%	1.00%
Black PA-R	6	6	6	6	4-5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	5	4-5	0.25%	1.00%

備註：此系列染料皆為金屬錯合染料，請貴公司使用前，先確認是否會因染色濃度造成不符合貴公司之管制規定。 Notes : All Everset PA dyes are metal-complex product, before use must confirm whether caused non-compliance due to dye concentration.
Remark : (1) C.C : Color Change CO : Cotton Stain N: Nylon Stain T: Polyester stain (2) * :Daimaru standard test is to access bleeding of dyed textiles, especially polyamide materials, in contact with non-ionic surfactant under wet condition.
Black PA-R 的測試濃度 1/1 N= B/DK; 1/12N = 1/4 B/DK ; Depth of Fastness Test for Black PA-R : 1/1 N= B/DK; 1/12N = 1/4 B/DK