Everlight Chemical

臺灣永光化學工業股份有限公司

EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：*本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*

Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

July 2025

Evertex® CFIX-T

反應性翠藍染料固色劑

Fixing Agent for Reactive Turquoise Dyes



Everlight Chemical

Evertex® CFIX-T

反應性翠藍染料固色劑

Fixing Agent for Reactive Turquoise Dyes

應用於纖維素纖維在反應性翠藍色染料，有效提升水洗及耐水牢度。

Enhances the washing/wet fastness of cellulosic substances dyed with reactive turquoise blue dyes.

優點 Advantages

- 專門為翠藍色染料提升水洗 / 濕牢度之固色劑
- 對合成洗滌劑有良好的耐洗性
- 不含甲醛、固色後織物親水性佳
- Improve washing/wet fastness for turquoise/green shade
- heavy-duty to laundering for synthetic detergents
- free-formaldehyde & hydrophilic maintance after treatment

應用 Application

- **浸染法 Exhaust Method**

Evertex CFIX-T	2~4 %
浴比 Liquor ratio	1 : 6 ~ 1 : 10
溫度 Temp. x 時間 Time	60℃ X 20~30'

- **壓染法 Padding Method**

Evertex CFIX-T	5~25 g/1
壓吸率 Pick-Up	80~100 %
烘乾 Drying	100℃
定型 Curing	130~150℃


＊使用時，用量可依顏色深淺而增減用量。
Dosage may vary from dyeing depth to adjust.

水洗牢度 Washing Fastness

ISO 105-C06-C2S	Ace	C	N	T	Acr	W
未固色 Without treatment	5	2	5	5	5	5
固色後 Evertex CFIX-T 4%	5	4-5	5	5	5	5

翠藍 / 翠綠色系之推薦優化染色 / 洗淨 / 固色流程

Recommended optimization of dyeing/washing/fixing process for turquoise / green shade



	產品 Products	用量 Dose/Q.TY	條件 Conditions	重點 Description
Dyeing	Everzol Lemon ERC Everzol Turquoise Blue ERC Everzol Sky Blue ERC Everzol Green 6B	ΣX%	Turquoise (80℃) Green (80℃) Blue (70℃)	• 染色浴比 1 :6~1 :10 • 建議使用芒硝 • 染色起始 pH 6.3~6.5 • Dyeing liquor ratio 1:6~1:10 • Glauber's salt preferred • Initial dyeing pH 6.3~6.5
Fixing Treatment	Evertex CFIX-T	2~4%	60℃ X 20~30'	• 改善及提升翠綠 / 翠藍色系水洗牢度 • Improve and enhance washing fastness for turquoise/green shades

