Everlight Chemical

臺灣永光化學工業股份有限公司
EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw


警語：*本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*

Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

July 2025

磨毛織物雙面同色之解決方案
The Solution for Producing High Quality Emerized Fabrics



冷壓染與連續染色
Cold Pad-Batch And Continuous Dyeing

Everlight Chemical

以正確組合提供磨毛織物的高品質染色


磨毛織物表面的桃皮絨觸感，提高了織物之附加價值。但是，許多冷壓染及連續染色流程之染料組合未經仔細篩選，容易因染料吸收上色速率不一致，而導致該織物正反面不同色調。

利用同步吸收機制篩選出的 Everzol 染料，運用於冷壓染及連續染色流程，可得最佳的染色效果以及良好的染色再現性。

Off-tone




Face side / Back side




Incompatible up-take of the trichromate dyes, used in a typical recipe, will lead to this two-sidedness problem.

On-tone



Face side / Back side



Compatible up-take of the trichromate dyes avoids this problem and contributes to a uniform appearance.

Choosing the Right Dyestuff Combination Gives High Quality Dyed Fabrics

Emerized fabric is well known for his wonderful touch of peach skin that confers much higher added value to the items. However, many CPB and continuous dyers face unacceptable two-sidedness effect on woven fabrics because of inadequate reactive dye selection.

The selected Everzol reactive dyes allow for best dyeing outcome as well as outstanding reproducibility in CPB and Continuous dyeing.

Everzol 染料於磨毛織物之染色運用
Everzol Dyes Selection for Emerized Fabrics

Pale shade — Depth: 5g/l

優異的耐日光牢度 及耐汗日光牢度	Yellow CE-N	Red LF-B	Blue C-LX*	Excellent lightfastness and perspiration lightfastness
	Yellow C-GL	Red C-3B*	Blue C-BB 133%*	

Medium - Dark shade — Depth: 30g/l

經濟型組合 兼具耐日光牢度	Yellow ED	Red ED-7BN	Blue L-ED*	Economical to get stand lightfastness
染深性佳 無光致變性 耐日光牢度佳	Yellow CE-N	Red ED-7BN	Blue L-ED*	Excellent color yield Non-photochromism good lightfastness
經濟型組合 染深性佳 無光致變性	Yellow C-RN	Red C-RB133%	Navy C-GB H/C	Economic combination Excellent color yield Non-photochromism
優異三原色 優異的高耐日光牢度	Yellow ERC	Cardinal ERC	Blue ERC	Premium trichromatic and high lightfastness

染色方法：冷壓染染色
Dyeing method : Cold Pad-Batch dyeing

備註：
＊這次金屬錯合染料，請貴公司使用前，先確認是否會因染色濃度造成不符合貴公司之管制規定。
Notes：
＊ This is a metal-complex product, before use must confirm whether caused non-compliance due to dye concentration.