Everzol®
www.ecic.com

Everlight Chemical

臺灣永光化學工業股份有限公司
EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION
Tel: +886-2-27066006 Fax: +886-2-27081254
E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：*本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*

Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

July 2025

Everzol® LX & LF

反應性染料
淺色、均染、再現性
Reactive Dyes for Pale Shade
Excellent Levelness & Reproducibility



Better Chemistry Better Life

Everlight Chemical

特點

Everzol LX/LF 是具備高均染性及優良再現性的反應性染料，可達到化驗室到現場染色最佳的再現性及降低修色的風險。

優點

- **染淺色相容性優異** → 同步吸收 / 固著行為
- **染淺色均染性佳** → 同色調的移染與上色
- **染淺色再現性佳** → 對染色因子變化穩定

Everzol® LF 組合


Everzol LF 染料系列搭配 LX 系列，具有優異的日光牢度及汗日光牢度，同時具有絕佳的均染性及染色再現性。

特性

- 優異之耐光及耐汗光牢度
- 獨特非含金型紅色染料 LF-B、LF-2B、LF-4B
- 優異的均染性及染色再現性

Step Dyeing

Process	Salt+Dyes					Salt+Dyes+Alkali		
	30℃x10'	40℃	50℃	60℃	60℃x20'	60℃x10'	60℃x30'	60℃x45'
Exhaustion								
Fixation								



Fastness

Fastness / Dyes	Washing ISO 105 C06 C2S		Perspiration ISO 105 E04				Chlorinated Water ISO 105 E03 (10ppm)	Lightfastness ISO 105 B02		Perspiration Lightfastness ISO 105 B07	
			Acid		Alkali					Acid	Alkali
	Co	PA	Co	PA	Co	PA		0.1%	1%	1%	1%
Everzol Yellow LX	5	5	5	5	5	5	4-5	6	>6	>6	5
Everzol Red LX	5	5	5	5	5	5	4	4	4-5	4	3-4
Everzol Blue LX*	4-5	5	5	5	5	5	3	5-6	6	5	4-5
Everzol Navy LX	5	5	5	5	5	5	4-5	3-4	4	4	3-4
Everzol Red LF-B	4-5	5	5	5	5	5	3	5	6	5-6	5
Everzol Red LF-2B	5	5	5	5	5	5	2-3	5-6	>6	6	5
Everzol Red LF-4B	5	5	5	4-5	5	4-5	3	5	6	5-6	5
Everzol Dark Blue LF*	4	4-5	4-5	4-5	4-5	4-5	2	5	6	5	4-5
Everzol Grey LF*	5	5	5	5	5	5	3	5	5-6	5	4
Everzol Brilliant Yellow 4GL	5	5	5	5	5	5	4-5	5	6	5-6	5-6
Everzol Brilliant Blue R s/p	5	5	5	5	5	5	3-4	5	6	5	4-5
Everzol Blue BRF 150%*	4	5	5	5	5	5	3-4	5	6	4-5	4
Everzol Blue ED-G	4-5	5	4-5	5	4-5	5	1	5	6	5-6	5-6

◆ *1% o.w.f for Wet colour fastness & Rubbing fastness., 0.1% & 1% o.w.f for lightfastness.*
◆ *In order to meet high light and perspiration light fastness requirement, Everzol Red LF-B & Red LF-2B are highly recommended instead of Red LX.*
備註： 這是金屬錯合染料，請貴公司使用前，先確認是否會因染色濃度造成不符合貴公司之管制規定。
Notes: This is a metal-complex product, before use must confirm whether caused non-compliance due to dye concentration.

Characteristics

Everzol LX / LF dyes performs excellent levelness and lab to bulk reproducibility for pale shades dyeing.

Advantages of Everzol® LX & LF dyes

- **Excellent compatibility on pale shades** → compatible exhaustion/fixation behavior
- **Excellent levelness** → on-tone migration and synchronal dyeing behavior
- **Unique reproducibility** → high Right First Time from lab to bulk and bulk to bulk

Everzol® LF selection

Everzol LF selection with LX range, characterized the high lightfastness and perspiration lightfastness as product feature, enhanced outstanding levelness & reproducibility.

Features of Everzol® LF selection

- Excellent light & perspiration light fastness.
- Metal-free Everzol Red LF-B & Red LF-2B & Red LF-4B.
- Unique levellness and reproducibility.

Content

