Everlight Chemical

臺灣永光化學工業股份有限公司

EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3821-2969 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。

***Warnings:** The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*


bluesign SYSTEM PARTNER

July 2026

Everzol® MX

專為**棉與再生纖維素纖維**之混紡材質一浴染色應用

A new generation of reactive dyes specifically developed for achieving perfect color uniformity for blended cellulose fibers.



Everlight Chemical

Everzol® MX

專為棉纖維素混紡纖維極致同色的新一代染料組合

特點說明

- 纖維素混紡纖維材質因不同基材比例混紡而成，容易對三原色吸收上染速率不相同造成染面不均染，染面色相易呈off-tone現象。
- 傳統染色應用雖可使用複數染料配色解決，但不利易於人員調配色使用，降低染色再現性與生產效率。
- 纖維素混紡纖維在其不同混紡比例時，染料組合往往需同時調整，無法滿足一浴同步上色需求。
- 全新開發的 Everzol MX 產品組合對此類混紡品適用性廣，易於一浴同色性可適用於浸染、冷壓染與連續染色流程應用。

染料特點


- 優異的擴散性能，良好的均染性。
- 適用棉與再生纖維素不同混紡比例，一浴同色效果。
- 三原色調色，染色工藝流程簡單。
- 染程適用性廣，再現性佳。



Recipe：

Everzol Yellow MX	1.0%	Liquor ratio：1：10
Everzol Red MX	1.0%	Gulauber´s salt：50g/l
Everzol Navy MX	1.0%	Soda ash：20g/l

吸盡固著曲線 Exhaustion & Fixation



Everzol® MX


A new generation of reactive dyes specifically developed for achieving perfect color uniformity in one-bath dyeing of cotton and regenerated cellulose fiber blends.

Product Key Message

- The various cellulose and regenerated cellulose blended with different ratios will cause trichromatic dyes impaired uptake and un-leveling, even off-tone distribution on the fabric.
- The methodology by mixing multiple conventional reactive dyes may solve the color matching, yet not friendly for dyeing masters and cause inferior reproducibility and low production efficiency.
- The regular dyes involved in the blended materials at various ratios will be fairly reluctant to achieve simultaneous fine-tuning to meet on-tone solid shade in one bath dyeing.
- The cutting edge product of Everzol MX range designed for those blended materials and extends the versatile application from exhaust and cold Pad-Batch dyeing to continuous dyeing.

Characteristics

- Excellent diffusion properties and good leveling properties.
- Suitable for different blending ratios of cotton and regenerated cellulose, achieving uniform color in a single bath.
- Simple dyeing process with primary trichromatic elements.
- The cutting edge product of Everzol MX range designed for those blended materials and wide applicability and excellent reproducibility in dyeing processes.



	溶解度 Solubility	耐鹼溶解度 Solubility in Alkali		耐水洗牢度 Washing (ISO 105 C10 C)		耐日光牢度 Light fastness (ISO 105-B02)		耐摩擦牢度 Rubbing (ISO 105-X12)		耐多次洗滌牢度 Multi-Laundering M&S C10A	耐汗日光牢度 Perspiration Light Fastness (ISO 105-B07)		耐氯水牢度 Chlorinated Water (ISO 105-E03)
	50°C	Alkali-A	Alkali-B	(Staining)		(Grade)		3% (Grade)		3%	3% (Grade)		3% (20ppm)
	(g/l)	(g/l)		CO	PA	0.3 %	3 %	Dry	Wet	Color Change	酸 Acid	鹼 Alkali	Color Change
Everzol Yellow MX	70	80	80	5	5	4	4-5	5	4-5	4-5	6	5	2-3
Everzol Red MX	100	100	100	4-5	5	4	4-5	5	4-5	4-5	5	5	2
Everzol Navy MX	100	100	100	4-5	5	4-5	4-5	5	4-5	4-5	4	4	2

Alkali-A : Silicate free method　　Alkali-B : Sodium Silicate method