Everlight Chemical

臺灣永光化學工業股份有限公司

EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：*本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*


Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

July 2025

Everacid®
www.ecic.com

Better Chemistry
Better Life



Everlight Chemical

Everacid® S Dyes

For Nylon and Nylon/Elastane Blends

此套染料是為了鮮豔色系及高牢度需求所開發，為了維持顏色的鮮豔度，染色配色的方式有別於傳統三原色的概念。Everacid® S 系列染色建議選取主色後再搭配同系列染料進行調色。


- 繽紛鮮豔的酸性染料
- 適用於尼龍 / 彈性纖維染色
- 優異的濕牢度
- 特殊染料結構，適用性廣泛

Everacid® S range is especially designed for brilliant colors and high fastness for nylon (polyamide) dyeing, the color matching process is differential to traditional trichromatic. Everacid® S range is dominant as single shade dyeing. For certain shades, the shading by same range Everacid S.

- Brilliant Acid Dyes
- For Nylon/Elastane blends
- Unique wet fastness
- Versatile application

牢度 Fastness

Item / Everacid Dyes	Solubility (g/l)		Light Fastness AATCC TM16.3-3 20AFU	Perspiration ISO 105 E04						Chlorinated Water ISO 105 E03 (20ppm)	Washing ISO 105 C06 B2S			Sea Water ISO 105 E02			Bleeding *Daimaru standard	Standard depth	
				Acid			Alkali												
	90℃	90℃ ↓ 25℃	CC	CC	CO	N	CC	CO	N	CC	CC	CO	N	CC	CO	N	CC	1/12N	1/1N
Yellow S-7G	90	70	3	3-4	5	5	3	5	4-5	4	4	5	5	3	5	5	5	0.450%	1.8%
Yellow S-4GL	50	40	5	5	5	5	5	5	5	4-5	5	5	5	5	5	5	5	0.280%	1.1%
Orange S-GSN	70	70	5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	0.405%	1.7%
Red S-GS	30	10	4	4-5	5	4-5	4-5	4-5	4-5	4-5	5	5	5	4-5	5	5	5	0.200%	0.8%
Red S-3B	30	5	3-4	5	5	5	5	5	5	4-5	5	5	5	5	5	5	5	0.225%	0.9%
Red S-BL	60	30	4-5	5	5	5	5	5	5	5	5	5	5	5	5	5	5	0.200%	0.8%
Red S-GWN	100	60	4-5	4	5	5	3-4	5	5	4-5	4-5	5	5	3-4	5	5	4-5	0.480%	1.9%
Rhodamine S-BN	20	20	2	4-5	5	5	2	5	5	4-5	2-3	5	5	2-3	5	5	5	0.100%	0.3%
Violet S-RWN	90	40	5	5	5	5	5	5	5	4-5	5	5	5	5	5	5	5	0.450%	1.8%
Blue S-BLW	40	30	5	4-5	5	5	4-5	5	5	4-5	5	5	5	4-5	5	5	5	0.750%	3.0%
Blue S-2R	100	100	5	5	5	5	5	5	5	4-5	5	5	5	5	5	5	5	0.450%	1.8%
Turquoise S-5G*1	40	10	3	3	5	5	2-3	4-5	5	4-5	2-3	5	5	3	5	5	4-5	0.850%	3.4%



Material: Nylon Knits

- **Daimaru standard test is to access bleeding of dyed textiles, especially polyamide materials, in contact with non-ionic surfactant under wet condition.*
- *Test Depth 1/1N*
- *Remark : CC : Color Change CO : Stain on Cotton N : Stain on Nylon*
- *Everacid S Series is 1/1N for all wet and rubbing fastness had processed with fixing treatment.*

*備註：*1 這是金屬錯合染料，請貴公司使用前，先確認是否會因染色濃度造成不符合貴公司之管制規定。*

*Notes : *1 This is a metal-complex product, before use must confirm whether caused non-compliance due to dye concentration.*