臺灣永光化學工業股份有限公司
EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION
Tel: +886-2-27066006 Fax: +886-2-27081254
E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：*本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*

Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

July 2025

Evertex® NLF-01

尼龍耐光堅牢度增進劑
Nylon Lightfastness improving agent



Everlight Chemical

▶ Evertex® NLF-01 的應用範圍及優點

Evertex NLF-01 主要應用於尼龍及羊毛纖維，有效提升耐光堅牢度。
可合併酸性染料一浴染色亦可後加工處理。

優點
有效提高尼龍與羊毛織物之耐光堅牢度
使用後不影響織物顏色
可合併酸性染料一浴染色
可提升酸性染料 Rhodamine 之日光牢度（* 會產生輕微色變）

▶ 產品特性

外觀：黃褐色透明液體

離子性：陰離子性

pH (100%)：9

▶ 染色應用

染浴中添加

Evertex NLF-01 可合併酸性染料一浴染色

- pH：4-5
- 建議用量：3% ~ 5% o.w.f

後處理加工

- 建議用量：30g/L ~ 50g/L
- 壓吸率：100%
- pH：4-5
- 加工條件：150 ~ 160℃ x 60 ~ 90Sec

** 採用後處理加工方式，效果可能受到水洗方式及次數影響。*

▶ Evertex® NLF-01 Application & Advantages

Evertex NLF-01 is designed for lightfastness improving agent for nylon and wool fiber.
It's compatible with acid dyes for one bath dyeing and post-treatment.

Advantages
Excellent improvement for lightfastness
Solid shade consistency after process
Compatible with acid dyes for one bath dyeing
Able to improve lightfastness of Rhodamine color (*Slight color change would happen)

▶ Characteristics

Appearance: Brown liq.

Ionicity: Anionic

pH (100%): 9

▶ Dyeing Application

With Dyeing Bath

- Evertex NLF-01 is compatible with acid dyes for one bath dyeing
- pH: 4-5
- Usage Recommendation: 3% ~ 5% o.w.f

Post-treatment


- Usage Recommendation: 30g/L ~ 50g/L
- Pick up: 100%
- pH: 4-5
- Curing : 150 ~ 160 ℃ x 60 ~ 90Sec

**With the post-treatment process, the performance may be affected by the washing method and frequency.*


▶ Lightfastness Improvement

Evertex NLF-01		0%	1%	3%	5%
AATCC 16-3	20 AFU	3	3	3-4	4
	40 AFU	2	2	2-3	3

▶ Lightfastness Test



▶ Perspiration Lightfastness Test





** 牢度的改善與染料特性及加工方式有關，以上所提供之測試結果僅供參考。*

** The fastness improving is related to dyes properties and processing methods. The test results are for reference only.*