Everlight Chemical


## 臺灣永光化學工業股份有限公司

**EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION**

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

**Everlight (Shanghai) Ltd.**
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

**Everlight (Suzhou) Advanced Chemicals Ltd.**
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

**Everlight (HongKong) Ltd.**
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

**Ethical (Guangzhou) Ltd.**
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

**Qingdao Office**
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

**Tianjin Office**
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

**Everlight USA, Inc.**
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

**Everlight Europe B.V. (Netherlands)**
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

**Elite Foreign Trading Inc. (Turkey)**
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

**Everlight Chemicals (Vietnam) Co., Ltd.**
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

**Technical Marketing & Service Division**
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw



**警語：***本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*

***Warnings:** The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*


bluesign SYSTEM PARTNER


*July 2025*


# Everjet® RT-HLF Series

## 高日光牢度反應性染料墨水

## High Light Fastness of Reactive Inks



Everlight Chemical

## Everjet® RT-HLF Series 特色

- 優異的日光牢度系列可滿足部分高日光牢度需求
- 專為纖維素纖維絲綢和羊毛紡織品織物數碼噴印設計
- 色彩鮮豔兼具優異色牢度
- 品質穩定優異再現性
- 色域齊全

## Everjet® RT-HLF Series Characteristic

- Excellent light fastness series.
- Designed for cellulose, silk & wool digital textile printing.
- Brilliant reactive dyes and excellent colour fastness.
- Unique quality and stability.
- Full of color gamut.

## Everjet® RT-HLF Series

優異的日光牢度，尤其淺紅、淺橘、淺紫。

Excellent light fastness especially in light colors.

| Colorfastness to Xenon-Arc Lamp Light<br>Test method : AATCC 16-3 2003 20-AFU | | | | | |
|---|---|---|---|---|---|
| **Commercial Product** | | | **Everjet RT-HLF** | | |
| Before test | After test | Before test | Before test | After test | Before test |
|  | | |  | | |
| Color change | 3 | | Color change | 4 | |

## Everjet® Color

| Everjet RT-HLF Series | Mercerized Cotton | Silk |
|---|---|---|
| Cyan RT-HLF | | |
| Magenta RT-HLF | | |
| Yellow RT-HLF | | |
| Black RT-HLF | | |
| Light Magenta RT-HLF | | |
| Grey RT-HLF | | |
| Orange RT-HLF | | |
| Blue RT-HLF | | |

## Everjet® RT-HLF Series Fastness properties (cotton)

| Everjet® | Washing Fastness ISO 105 C06 C2S | | | Crocking Fastness ISO 105 X12 | | Light Fastness | |
|---|---|---|---|---|---|---|---|
| | Color Change | Cotton stain | Nylon stain | Dry | Wet | AATCC 16-3 Color change | ISO 105 B02 Blue scale |
| Cyan RT-HLF | 4-5 | 3 | 5 | 5 | 3 | 4-5 | 5-6 |
| Magenta RT-HLF | 4-5 | 4-5 | 5 | 5 | 3 | 3-4 | 4-5 |
| Yellow RT-HLF | 4-5 | 4-5 | 5 | 5 | 3-4 | 5 | 6 |
| Black RT-HLF | 4-5 | 5 | 5 | 4-5 | 3 | 3 | 4-5 |
| Light Magenta RT-HLF | 4-5 | 5 | 5 | 4-5 | 3 | 4 | 4-5 |
| Grey RT-HLF | 4-5 | 5 | 5 | 4-5 | 3 | 4 | 5 |
| Orabge RT-HLF | 4-5 | 5 | 5 | 4-5 | 3 | 4 | 4-5 |
| Blue RT-HLF | 4-5 | 5 | 5 | 5 | 3 | 5 | 5-6 |

* Everjet Grey RT-MLF：高日光非含金灰（Metal Free & High Light Fastness）。

1. 水洗牢度、摩擦牢度使用 100% 濃度測試；日光牢度使用 50% 濃度測試。
   100% print used for Washing & Crocking fastness tests, 50% print used Light Fastness tests.
2. 牢度的結果會受使用的織物、相關應用及固色程序而有所不同。
   Fastness results may be affected by the variation of substrate and relative application and fixation procedure.

## Everjet® RT-HLF Series Remark

1. 鹼劑使用小蘇打 ($NaHCO_3$)
   Alkali using Sodium Bicabonate.
2. 尿素用量：棉 100-150 g/l；蠶絲 100-150 g/l；黏膠材質 150-200 g/l
   Urea dosage: Cotton 100-150 g/l ; Silk 100-150 g/l ; Viscose 150-200 g/l
3. 蒸處條件：75% 相對溼度以上、102℃ x 8~12 分鐘
   Steaming condition: Humidity 75~100%、102℃ x 8~12'