Everlight Chemical

臺灣永光化學工業股份有限公司

EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：*本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。*

Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

July 2025

Evertex® NFIX-BPF

生質型環保酸性染料固色劑

BIO-BASED ECO-FRIENDLY FIXING AGENT FOR ACID DYES



Everlight Chemical

說明 Directions

Evertex® NFIX - BPF 為生物基酸性染料固色助劑，其分子結構不含雙酚類、酚類、甲醛及有機溶劑等有害物質，產品主要原料來源為可再生生質材料，符合碳足跡減量趨勢。

本品適用於尼龍纖維（PA6, PA66）、超細尼龍纖維（Microfiber PA) 以及尼龍／彈性纖維（PA/PU) 混紡織物之染色後固色加工，可提升酸性染料對纖維的親和性及染著牢度，同時具備優異的環保特性。

Evertex® NFIX-BPF is a bio-based fixing agent for acid dyes, featuring a molecular structure free from harmful substances such as bisphenols, phenols, formaldehyde, and organic solvents. Derived primarily from renewable biomass resources, this product aligns with carbon footprint reduction initiatives.

The agent is specifically designed for post-dyeing fixation of polyamide fibers (PA6, PA66), polyamide microfibers, and polyamide/elastane (PA/PU) blended fabrics. It enhances the dye-fiber substantivity and color fastness properties while maintaining excellent eco-friendly characteristics.

特徵 Characteristics

- 本品具優異水性能表現，可耐受 200ppm 以下硬水，對染浴中殘留之陽離子助劑具良好耐受性，並可與多數陰離子、非離子、陽離子型整理劑相容，不產生凝聚沉澱現象。
- 本品經固色加工後，可同時符合 AATCC 水洗、耐水及 ISO 耐汗之染色牢度標準規範。
- 產品具備提升織物耐氯特性，可承受一定濃度之有效氯。
- 其固有的酸性特質可直接發揮固色功能，無需過量添加酸性調節劑。
- 應用於螢光色系染整時，建議採用低溫固色製程，以防止色調偏移。

- The product exhibits excellent water compatibility, tolerating water hardness up to 200ppm and showing high stability with residual cationic leveling agents in dyebath. It is compatible with most anionic, non-ionic, and cationic finishing agents without causing coagulation or precipitation.
- After fixation treatment, the fabric meets color fastness standards of AATCC washing, water fastness, and ISO perspiration tests.
- The product enhances fabric chlorine resistance, withstanding specific concentrations of available chlorine.
- It's inherent acidic properties provide effective fixation without requiring excessive acid regulators.
- For fluorescent color dyeing, a low-temperature fixation process is recommended to prevent hue shifting.

特性 Properties

外觀 Appearance	:	褐色液體 Brownish liquid
成分 Composition	:	天然植物提取物 Natural plant extracts
離子性 Ionic Property	:	陰離子 Anionic
固含量 Solid Content	:	40.0 ± 1.0%
40.0 ± 1.0%	:	2.5 ± 0.5
混溶性 Miscibility	:	以各種比例溶於水 Soluble in water in all proportions

應用 Application

建議用量 Recommended Usage

淺色 Pale shade	:	2~3% o.w.f
中色 Medium shade	:	3~4% o.w.f
深色 Deep shade	:	5~6% o.w.f
建議操作條件 Recommended Usage	:	50~60℃ x 20~30min

Colorfastness to Chlorinated Water: ISO 105 E03 (50 ppm)；27℃ x 30 min

	Before Test	After Test	Color Change
Blank			1
Evertex® NFIX-BPF 4.0%			4-5

Material: Nylon / Lycra 92/8
Dyeing Recipes:
Everacid Yellow N-MR 0.4%
Everacid Red N-2BL 0.4%
Everacid Blue N-RL 0.4%

Colorfastness to Washing: ISO 105 C06 B2S；50℃ x 30 min.

	Before Test	After Test	Color Change	Stain					
				AC	C	N	T	Acr	W
Blank			3-4						
Evertex® NFIX-BPF 4.0%			4-5						

Colorfastness to Water: ISO 105 E01；37℃ x 4 hrs.

	Before Test	After Test	Color Change	Stain					
				AC	C	N	T	Acr	W
Blank			4-5						
Evertex® NFIX-BPF 4.0%			4-5						