Everlight Chemical

臺灣永光化學工業股份有限公司

EVERLIGHT CHEMICAL INDUSTRIAL CORPORATION

Tel: +886-2-27066006 Fax: +886-2-27081254

E-mail: sales-CCBU@ecic.com.tw

Everlight (Shanghai) Ltd.
上海德樺貿易有限公司
Tel: +86-21-62196954 Fax: +86-21-62191276

Everlight (Suzhou) Advanced Chemicals Ltd.
永光（蘇州）光電材料有限公司
Tel: +86-512-62871980 Fax: +86-512-62871217

Everlight (HongKong) Ltd.
香港永光有限公司
Tel: +852-26191095 Fax: +852-26191031

Ethical (Guangzhou) Ltd.
廣州明廣貿易有限公司
Tel: +86-20-38497030 Fax: +86-20-38497031

Qingdao Office
青島分公司
Tel: +86-532-85016051 Fax: +86-532-85016063

Tianjin Office
天津分公司
Tel: +86-22-23202016 Fax: +86-22-23202015

Everlight USA, Inc.
美國永光公司
Tel: +1-704-5881004 Fax: +1-704-5880051

Everlight Europe B.V. (Netherlands)
荷蘭永光公司
Tel: +31-10-2380099 Fax: +31-10-2380090

Elite Foreign Trading Inc. (Turkey)
土耳其 Elite 公司
Tel: +90-324-2377789 Fax: +90-324-2370246

Everlight Chemicals (Vietnam) Co., Ltd.
越南永光公司
Tel: +84-28-3520-2761 Fax: +84-28-3636-8375

Technical Marketing & Service Division
技術行銷處
Tel: +886-3-4838088 E-mail: ccbu-tms@ecic.com.tw

警語：本資料所提供的資訊與建議是以我們最大的用心完成，但不能涵括所有可能的狀況。使用相關產品或搭配其他產品時，請先自行測試。本資料並不具保證及法律效用，僅供參考使用。使用者必須自行承擔所有的風險與法律責任。

Warnings: *The information and recommendations presented here were completed with the utmost care, but can't be extended to cover every possible case. They are intended to serve as non-binding guidelines and must be adapted to the prevailing condition. The product whether used singly or in combination with other substances, should be carried out in lab test prior to bulk production. The user needs to assume all risk and liability no matter whatsoever results are.*

bluesign SYSTEM PARTNER

July 2025

Everzol®

可拔白反應性染料

for Cellulose Discharge Printing



Everlight Chemical

Everzol 系列之可拔白染料　符合多功能需求

- 優異之可拔白性
- 易於呈現漸層及細線條等拔白效果
- 色澤鮮豔、色域齊全
- 適用於浸染、冷壓染與連續染色等底色染色工藝流程
- 優良之組合相容性
- 大多數品目亦適用於防染印花工藝

Rating of Discharge Ability (Black color *3% & *6% dyeing)

Everzol	1%			3%		
	Neutral	Alkaline	Decrolin	Neutral	Alkaline	Decrolin
Orange ERC	4	4-5	4	3-4	4	4
Cardinal ERC	4	4	4	3	3-4	3
Bordeaux ERC	3-4	4-5	3-4	3-4	4-5	3-4
Blue ERC (2)	3-4	4	3	2-3	3	2-3
Dark Blue ERC (2)	4	4-5	4	3	3-4	3
Marine ERC	3-4	4	4	3	4	3-4
Red LX	4-5	4-5	4-5	4-5	4-5	4
Red LF-B	4-5	4-5	4-5	4	4	4
Red LF-2B	4	4-5	4	3-4	4	3-4
Blue LX (2)	4	4	4	2-3	2-3	3
Navy LX	4-5	3-4	4-5	3-4	3	4
Yellow ED	4-5	4	4	4-5	3	3-4
Yellow ED-S (1)	4-5	4-5	4-5	4-5	4-5	4-5
Orange ED-N	4-5	4-5	4-5	4-5	4-5	4
Orange ED-4R (2)	4	4-5	4	3-4	4	3-4
Red ED-S	4	4-5	4	3-4	4	3-4
Blue L-ED (2)	3-4	4	4	3	3-4	3-4
Navy ED	3-4	4	3-4	3	3-4	3
Yellow 3GL	4-5	4-5	3	4-5	4-5	2-3
Yellow PFG 150%	4-5	4-5	4-5	4-5	4-5	4-5

Everzol	1% (*3%)			3% (*6%)		
	Neutral	Alkaline	Decrolin	Neutral	Alkaline	Decrolin
Yellow GR	4-5	4	4-5	4-5	4	4
Yellow 3RS	4-5	4	4	4	3-4	3-4
Yellow RNL	4-5	4-5	4-5	4-5	4-5	4-5
Yellow C-RN	4-5	4-5	4	4-5	4	4
Orange 3R	4-5	4-5	4-5	4-5	4-5	4-5
Red BB	4-5	4-5	4-5	4-5	4-5	4-5
Brilliant Red F3B	4	4-5	4	3-4	4	3-4
Red C-D	4-5	4-5	4-5	4	4	4
Blue BB (2)	3-4	4	4	3	3-4	3-4
Blue BRF 150% (2)	3	3-4	3-4	2	2-3	3
Navy C-GG 133%	4-5	4-5	4-5	4	4-5	4
Navy Blue RGB H/C	4-5	4-5	4-5	4	4-5	4
Black B*	3-4	4	4	3	4	3-4
Black N*	4	4-5	4	3-4	4-5	3-4
Black GSP*	4	4-5	4	4	4-5	3-4
Black MWF*	4	4-5	4	3-4	4-5	3-4
Black ED*	4	4-5	4	3-4	4-5	3-4
Black ED-G*	3-4	4-5	3-4	3	4	3
Black ED-R*	4	4-5	4	3-4	4-5	3-4
Black ED-3R*	4	4-5	4	3-4	4	3-4

* Please refer to above rating in different dyeing percentage for ensuring optimized discharge result.

備註：(1) Yellow ED-S 施以樹脂加工，須注意其色變、日光牢度及受氧化還原化學物質之色變。
(2) 這是金屬錯合染料，請貴公司使用前，先確認是否會因染色濃度造成不符合貴公司之管制規定。

Notes: (1) Yellow ED-S: Precaution of lightfastness and color change after resin treatment, or under the presence of oxidative/reductive chemicals.
(2) This is a metal-complex product, before use must confirm whether caused non-compliance due to dye concentration.

Everzol Dischargeable selection meets various requirement

- Excellent discharge ability
- Easy to present delicate motif printing
- Full of shades range
- Suitable for exhaust、CPB and continuous dyeing
- Unique compatibility
- Most of items also suitable for resist printing

Dischargeable Everzol Dyes (3% dyeing for color items ; *6% dyeing for black items)

Orange ERC
Cardinal ERC
Bordeaux ERC
Blue ERC
Dark Blue ERC
Marine ERC
Red LX
Red LF-B
Red LF-2B
Blue LX

Navy LX
Yellow ED
Yellow ED-S
Orange ED-N
Orange ED-4R
Red ED-S
Blue L-ED
Navy ED
Yellow 3GL
Yellow PFG 150%

Yellow GR
Yellow 3RS
Yellow RNL
Yellow C-RN
Orange 3R
Red BB
Brilliant Red F3B
Red C-D
Blue BB
Blue BRF 150%

Navy C-GG 133%
Navy Blue RGB H/C
Black B*
Black N*
Black GSP*
Black MWF*
Black ED*
Black ED-G*
Black ED-R*
Black ED-3R*

Trichromatic

Cold Pad Batch Dyeing

Red ED-S	20g/l
Yellow C-RN	10g/l
Red BB	10g/l
Navy C-GG 133%	10g/l
Orange 3R	10g/l
Red C-D	10g/l
Navy ED	10g/l
Black ED	60g/l



Exhaust Dyeing

Red ED-S	2%
Yellow RNL	1%
Red F3B	1%
Navy Blue RGB H/C	1%
Orange ED-N	1%
Red ED-S	1%
Navy ED	1%
Black ED-R	6%

