Meteorwave® 1000 - Dielectric Properties Table
AMMA Manufacturing Location

LAMINATE (Available from AGC U.S. manufacturing location – AMMA):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0020	±	0.0005	1	106				73%	0.0021	54	3.32	0.0035	3.27	0.0043	3.26	0.0045
0.0020	±	0.0005	1	1035				68%	0.0021	54	3.41	0.0037	3.35	0.0045	3.34	0.0047
0.0025	±	0.0005	1	1080				59%	0.0025	64	3.57	0.0039	3.53	0.0050	3.52	0.0052
0.0025	±	0.0005	1	1078				59%	0.0026	65	3.57	0.0039	3.53	0.0050	3.52	0.0052
0.0030	±	0.0005	1	1080				65%	0.0030	77	3.46	0.0038	3.41	0.0047	3.40	0.0049
0.0030	±	0.0005	1	1078				65%	0.0031	78	3.46	0.0038	3.41	0.0047	3.40	0.0049
0.0035	±	0.0005	1	2013				53%	0.0037	93	3.70	0.0042	3.66	0.0053	3.65	0.0055
0.0040	±	0.0005	2	106				73%	0.0042	108	3.32	0.0035	3.27	0.0043	3.26	0.0045
0.0040	±	0.0005	2	1035				68%	0.0043	109	3.41	0.0037	3.35	0.0045	3.34	0.0047
0.0040	±	0.0005	1	2116				46%	0.0039	100	3.87	0.0044	3.84	0.0057	3.83	0.0059
0.0050	±	0.0007	2	1080				59%	0.0050	127	3.57	0.0039	3.53	0.0050	3.52	0.0052
0.0050	±	0.0007	2	1078				59%	0.0051	130	3.57	0.0039	3.53	0.0050	3.52	0.0052
0.0050	±	0.0007	1	2116				55%	0.0050	126	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0060	±	0.0007	2	1080				65%	0.0060	154	3.46	0.0038	3.41	0.0047	3.40	0.0049
0.0060	±	0.0007	2	1078				65%	0.0062	157	3.46	0.0038	3.41	0.0047	3.40	0.0049
0.0070	±	0.0010	2	106	+	1	1080	70%	0.0073	185	3.38	0.0036	3.33	0.0045	3.32	0.0047
0.0070	±	0.0010	2	1035	+	1	1078	67%	0.0074	187	3.43	0.0037	3.38	0.0046	3.37	0.0048
0.0080	±	0.0010	2	2116				46%	0.0079	200	3.87	0.0044	3.84	0.0057	3.83	0.0059

The laminate and prepreg items shown represent ***the most popular*** material configurations. Additional or comparable core and prepreg thicknesses may be available and can be recommended based on lead time, availability and application requirements. Please contact your technical service representative for assistance in selecting the appropriate material for your design and application.

Meteorwave® 1000 - Dielectric Properties Table
AMMA Manufacturing Location

LAMINATE (Available from AGC U.S. manufacturing location – AMMA)(Continued):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0100	±	0.0010	2	2116				55%	0.0099	252	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0150	±	0.0015	3	2116				55%	0.0149	378	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0200	±	0.0025	4	2116				55%	0.0198	504	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0210	±	0.0025	2	1080	+	3	2116	58%	0.0209	532	3.60	0.0040	3.56	0.0050	3.54	0.0052
0.0210	±	0.0025	2	1078	+	3	2116	58%	0.0211	535	3.60	0.0040	3.55	0.0050	3.54	0.0052
0.0210	±	0.0025	3	7628				42%	0.0211	537	3.97	0.0046	3.95	0.0060	3.94	0.0062

PREPREG (Available from AGC U.S. manufacturing location - AMMA):

Glass	RC%	Thickness (inches)	Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
106	75%	0.0023	59	3.29	0.0035	3.23	0.0042	3.22	0.0044
106	78%	0.0027	68	3.24	0.0034	3.18	0.0041	3.17	0.0043
1035	68%	0.0021	54	3.41	0.0037	3.35	0.0045	3.34	0.0047
1035	70%	0.0023	58	3.37	0.0036	3.32	0.0045	3.31	0.0047
1035	75%	0.0028	72	3.29	0.0035	3.23	0.0042	3.22	0.0044
1035	77%	0.0031	79	3.26	0.0034	3.20	0.0042	3.19	0.0044
1078	72%	0.0040	101	3.34	0.0035	3.28	0.0044	3.27	0.0046
1080	72%	0.0039	99	3.34	0.0035	3.28	0.0044	3.27	0.0046
2116	55%	0.0050	126	3.66	0.0041	3.62	0.0052	3.61	0.0054

The laminate and prepreg items shown represent ***the most popular*** material configurations. Additional or comparable core and prepreg thicknesses may be available and can be recommended based on lead time, availability and application requirements. Please contact your technical service representative for assistance in selecting the appropriate material for your design and application.

Meteorwave® 1000 - Dielectric Properties Table
AMMS Manufacturing Location

LAMINATE (Available from AGC Singapore manufacturing location – AMMS):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0010	±	0.0005	1	1017				73%	0.0011	27	3.32	0.0035	3.27	0.0043	3.26	0.0045
0.0020	±	0.0005	1	106				73%	0.0021	54	3.32	0.0035	3.27	0.0043	3.26	0.0045
0.0020	±	0.0005	1	1035				68%	0.0021	54	3.41	0.0037	3.35	0.0045	3.34	0.0047
0.0025	±	0.0005	1	1078				58%	0.0025	63	3.59	0.0040	3.55	0.0050	3.54	0.0052
0.0030	±	0.0005	1	1080				65%	0.0030	77	3.46	0.0038	3.41	0.0047	3.40	0.0049
0.0035	±	0.0005	1	3313				52%	0.0036	91	3.72	0.0042	3.69	0.0053	3.68	0.0055
0.0040	±	0.0005	1	3313				56%	0.0040	102	3.63	0.0040	3.59	0.0051	3.58	0.0053
0.0040	±	0.0005	2	106				73%	0.0042	108	3.32	0.0035	3.27	0.0043	3.26	0.0045
0.0050	±	0.0007	1	2116				55%	0.0050	126	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0050	±	0.0007	2	1078				58%	0.0050	126	3.59	0.0040	3.55	0.0050	3.54	0.0052
0.0060	±	0.0007	2	1078				65%	0.0062	157	3.46	0.0038	3.41	0.0047	3.40	0.0049
0.0070	±	0.0010	2	3313				52%	0.0072	182	3.72	0.0042	3.69	0.0053	3.68	0.0055
0.0080	±	0.0010	2	2116				46%	0.0079	200	3.87	0.0044	3.84	0.0057	3.83	0.0059
0.0080	±	0.0010	2	3313				56%	0.0080	203	3.63	0.0040	3.59	0.0051	3.58	0.0053
0.0100	±	0.0010	2	2116				55%	0.0099	252	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0120	±	0.0015	3	2116				46%	0.0118	301	3.87	0.0044	3.84	0.0057	3.83	0.0059
0.0140	±	0.0015	2	2116	+	1	3313	55%	0.0139	354	3.65	0.0041	3.61	0.0052	3.60	0.0054

The laminate and prepreg items shown represent ***the most popular*** material configurations. Additional or comparable core and prepreg thicknesses may be available and can be recommended based on lead time, availability and application requirements. Please contact your technical service representative for assistance in selecting the appropriate material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.multimaterial@agc.com • www.agc-multimaterial.com

Meteorwave® 1000 - Dielectric Properties Table
AMMS Manufacturing Location

LAMINATE (Available from AGC Singapore manufacturing location – AMMS) (Continued):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0150	±	0.0015	3	2116				55%	0.0149	378	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0160	±	0.0015	3	2116	+	2	106	52%	0.0161	408	3.71	0.0042	3.67	0.0053	3.66	0.0055
0.0160	±	0.0015	4	3313				56%	0.0160	406	3.63	0.0040	3.59	0.0051	3.58	0.0053
0.0200	±	0.0025	4	2116				55%	0.0198	504	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0240	±	0.0025	6	2116				46%	0.0237	601	3.87	0.0044	3.84	0.0057	3.83	0.0059
0.0250	±	0.0025	5	2116				55%	0.0248	630	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0280	±	0.0025	7	2116				55%	0.0347	882	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0295	±	0.0025	6	2116				55%	0.0298	756	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0300	±	0.0025	6	2116				55%	0.0298	756	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0310	±	0.0040	6	2116	+	1	2116	50%	0.0305	774	3.77	0.0043	3.73	0.0055	3.72	0.0057
0.0430	±	0.0050	10	2116				50%	0.0435	1105	3.77	0.0043	3.73	0.0055	3.72	0.0057
0.0450	±	0.0050	4	2116	+	6	2116	52%	0.0459	1167	3.72	0.0042	3.68	0.0053	3.67	0.0055
0.0590	±	0.0050	12	2116				55%	0.0595	1512	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0600	±	0.0050	12	2116				55%	0.0595	1512	3.66	0.0041	3.62	0.0052	3.61	0.0054
0.0940	±	0.0050	19	2116				55%	0.0942	2394	3.66	0.0041	3.62	0.0052	3.61	0.0054

The laminate and prepreg items shown represent ***the most popular*** material configurations. Additional or comparable core and prepreg thicknesses may be available and can be recommended based on lead time, availability and application requirements. Please contact your technical service representative for assistance in selecting the appropriate material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.multimaterial@agc.com • www.agc-multimaterial.com

Meteorwave® 1000 - Dielectric Properties Table
AMMS Manufacturing Location

PREPREG (Available from AGC Singapore manufacturing location - AMMS):

Glass	RC%	Thickness (inches)	Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
1027	64%	0.0013	32	3.48	0.0038	3.43	0.0047	3.42	0.0049
0106	73%	0.0021	54	3.32	0.0035	3.27	0.0043	3.26	0.0045
1035	68%	0.0021	54	3.41	0.0037	3.35	0.0045	3.34	0.0047
1035	73%	0.0026	66	3.32	0.0035	3.27	0.0043	3.26	0.0045
1078	53%	0.0022	55	3.70	0.0042	3.66	0.0053	3.65	0.0055
1078	58%	0.0025	63	3.59	0.0040	3.55	0.0050	3.54	0.0052
1078	65%	0.0031	78	3.46	0.0038	3.41	0.0047	3.40	0.0049
1078	68%	0.0034	87	3.41	0.0037	3.35	0.0045	3.34	0.0047
1080	58%	0.0024	62	3.59	0.0040	3.55	0.0050	3.54	0.0052
1080	65%	0.0030	77	3.46	0.0038	3.41	0.0047	3.40	0.0049
2116	46%	0.0039	100	3.87	0.0044	3.84	0.0057	3.83	0.0059
2116	50%	0.0044	111	3.77	0.0043	3.73	0.0055	3.72	0.0057
2116	55%	0.0050	126	3.66	0.0041	3.62	0.0052	3.61	0.0054
3313	52%	0.0036	91	3.72	0.0042	3.69	0.0053	3.68	0.0055
3313	56%	0.0040	102	3.63	0.0040	3.59	0.0051	3.58	0.0053

The laminate and prepreg items shown represent ***the most popular*** material configurations. Additional or comparable core and prepreg thicknesses may be available and can be recommended based on lead time, availability and application requirements. Please contact your technical service representative for assistance in selecting the appropriate material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.multimaterial@agc.com • www.agc-multimaterial.com