Meteorwave® 2000 - Dielectric Properties Table
AMMA Manufacturing Location

LAMINATE (Available from AGC U.S. manufacturing location – AMMA):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0020	±	0.0005	1	1035				69%	0.0020	52	3.23	0.0027	3.22	0.0032	3.21	0.0035
0.0025	±	0.0005	1	1078				61%	0.0025	64	3.31	0.0028	3.30	0.0035	3.29	0.0038
0.0030	±	0.0005	1	1078				67%	0.0031	78	3.25	0.0027	3.24	0.0033	3.22	0.0036
0.0040	±	0.0005	2	1035				69%	0.0041	104	3.23	0.0027	3.22	0.0032	3.21	0.0035
0.0040	±	0.0005	1	2116				49%	0.0040	103	3.47	0.0030	3.46	0.0039	3.44	0.0042
0.0050	±	0.0007	2	1078				61%	0.0051	129	3.31	0.0028	3.30	0.0035	3.29	0.0038
0.0050	±	0.0007	1	2116				58%	0.0051	129	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0060	±	0.0007	2	1078				67%	0.0061	156	3.25	0.0027	3.24	0.0033	3.22	0.0036
0.0080	±	0.0010	2	2116				49%	0.0081	205	3.47	0.0030	3.46	0.0039	3.44	0.0042
0.0100	±	0.0010	2	2116				58%	0.0102	259	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0140	±	0.0015	2	2116	+	1	2116	55%	0.0142	361	3.38	0.0029	3.37	0.0037	3.36	0.0040
0.0150	±	0.0015	3	2116				58%	0.0153	388	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0160	±	0.0015	4	2116				49%	0.0161	410	3.47	0.0030	3.46	0.0039	3.44	0.0042
0.0180	±	0.0015	2	2116	+	2	2116	54%	0.0183	464	3.40	0.0029	3.39	0.0037	3.38	0.0040
0.0200	±	0.0025	4	2116				58%	0.0204	517	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0250	±	0.0025	5	2116				58%	0.0255	647	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0280	±	0.0025	5	2116	+	1	1078	59%	0.0285	725	3.34	0.0028	3.33	0.0035	3.31	0.0038
0.0300	±	0.0025	6	2116				58%	0.0305	776	3.35	0.0028	3.34	0.0036	3.33	0.0039

Meteorwave® 2000 - Dielectric Properties Table
AMMA Manufacturing Location

PREPREG (Available from AGC U.S. manufacturing location - AMMA):

Glass	RC%	Thickness (inches)	Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
1027	76	0.0018	45	3.16	0.0026	3.15	0.0030	3.14	0.0033
106	75	0.0022	56	3.17	0.0026	3.16	0.0031	3.15	0.0034
106	77	0.0024	62	3.15	0.0026	3.14	0.0030	3.13	0.0033
1035	73	0.0024	62	3.19	0.0026	3.18	0.0031	3.16	0.0034
1035	75	0.0026	67	3.17	0.0026	3.16	0.0031	3.15	0.0034
1035	77	0.0029	74	3.15	0.0026	3.14	0.0030	3.13	0.0033
1078	68	0.0032	81	3.24	0.0027	3.23	0.0033	3.21	0.0036
1078	70	0.0034	87	3.22	0.0027	3.21	0.0032	3.19	0.0035
1078	72	0.0037	94	3.20	0.0027	3.19	0.0031	3.17	0.0034
1078	75	0.0042	106	3.17	0.0026	3.16	0.0031	3.15	0.0034
1080	65	0.0029	74	3.27	0.0027	3.26	0.0034	3.25	0.0037
1080	68	0.0032	82	3.24	0.0027	3.23	0.0033	3.21	0.0036
1080	72	0.0038	95	3.20	0.0027	3.19	0.0031	3.17	0.0034
2116	55	0.0047	119	3.38	0.0029	3.38	0.0037	3.36	0.0040
2116	60	0.0054	137	3.32	0.0028	3.31	0.0035	3.30	0.0038

Meteorwave® 2000 - Dielectric Properties Table
AMMS Manufacturing Location

LAMINATE (Available from AGC Singapore manufacturing location – AMMS):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0010	±	0.0005	1	1017				74%	0.0010	26	3.18	0.0026	3.17	0.0031	3.16	0.0034
0.0016	±	0.0005	1	1027				72%	0.0015	38	3.20	0.0027	3.19	0.0031	3.17	0.0034
0.0020	±	0.0005	1	106				73%	0.0020	52	3.19	0.0026	3.18	0.0031	3.16	0.0034
0.0020	±	0.0005	1	1035				69%	0.0020	52	3.23	0.0027	3.22	0.0032	3.21	0.0035
0.0025	±	0.0005	1	1078				61%	0.0025	64	3.31	0.0028	3.30	0.0035	3.29	0.0038
0.0030	±	0.0005	1	1078				67%	0.0031	78	3.25	0.0027	3.24	0.0033	3.22	0.0036
0.0035	±	0.0005	1	2013				54%	0.0036	90	3.40	0.0029	3.39	0.0037	3.38	0.0040
0.0040	±	0.0005	1	2116				49%	0.0040	103	3.47	0.0030	3.46	0.0039	3.44	0.0042
0.0040	±	0.0005	1	2013				59%	0.0041	104	3.34	0.0028	3.33	0.0035	3.31	0.0038
0.0050	±	0.0007	1	2116				58%	0.0051	129	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0050	±	0.0007	2	1078				61%	0.0051	129	3.31	0.0028	3.30	0.0035	3.29	0.0038
0.0060	±	0.0007	2	1080				67%	0.0062	159	3.25	0.0027	3.24	0.0033	3.22	0.0036
0.0060	±	0.0007	2	1078				67%	0.0061	156	3.25	0.0027	3.24	0.0033	3.22	0.0036
0.0070	±	0.0010	2	1078				70%	0.0068	174	3.22	0.0027	3.21	0.0032	3.19	0.0035
0.0070	±	0.0010	2	2013				54%	0.0071	181	3.40	0.0029	3.39	0.0037	3.38	0.0040
0.0070	±	0.0010	2	1035	+	1	1078	68%	0.0072	182	3.24	0.0027	3.23	0.0033	3.22	0.0036

Meteorwave® 2000 - Dielectric Properties Table
AMMS Manufacturing Location

LAMINATE (Available from AGC Singapore manufacturing location – AMMS):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0080	±	0.0010	2	2116				49%	0.0081	205	3.47	0.0030	3.46	0.0039	3.44	0.0042
0.0080	±	0.0010	2	2013				59%	0.0082	207	3.34	0.0028	3.33	0.0035	3.31	0.0038
0.0100	±	0.0010	2	2116				58%	0.0102	259	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0120	±	0.0015	2	2013	+	1	2116	56%	0.0122	310	3.38	0.0029	3.37	0.0037	3.35	0.0040
0.0150	±	0.0015	3	2116				58%	0.0153	388	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0160	±	0.0015	4	2116				49%	0.0161	410	3.47	0.0030	3.46	0.0039	3.44	0.0042
0.0250	±	0.0025	5	2116				58%	0.0255	647	3.35	0.0028	3.34	0.0036	3.33	0.0039
0.0300	±	0.0025	6	2116				58%	0.0305	776	3.35	0.0028	3.34	0.0036	3.33	0.0039

Meteorwave® 2000 - Dielectric Properties Table
AMMS Manufacturing Location

PREPREG (Available from AGC Singapore manufacturing location - AMMS):

Glass	RC%	Thickness (inches)	Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
106	75	0.0022	56	3.17	0.0026	3.16	0.0031	3.15	0.0034
106	77	0.0024	62	3.15	0.0026	3.14	0.0030	3.13	0.0033
1027	76	0.0018	45	3.16	0.0026	3.15	0.0030	3.14	0.0033
1035	69	0.0021	53	3.23	0.0027	3.22	0.0032	3.20	0.0035
1035	73	0.0024	62	3.19	0.0026	3.18	0.0031	3.16	0.0034
1035	75	0.0026	67	3.17	0.0026	3.16	0.0031	3.15	0.0034
1035	77	0.0029	74	3.15	0.0026	3.14	0.0030	3.13	0.0033
1078	65	0.0029	73	3.27	0.0027	3.26	0.0034	3.25	0.0037
1078	68	0.0032	81	3.24	0.0027	3.23	0.0033	3.21	0.0036
1078	70	0.0034	87	3.22	0.0027	3.21	0.0032	3.19	0.0035
1078	72	0.0037	94	3.20	0.0027	3.19	0.0031	3.17	0.0034
1078	74	0.0040	102	3.18	0.0026	3.17	0.0031	3.16	0.0034
1078	75	0.0042	106	3.17	0.0026	3.16	0.0031	3.15	0.0034
1080	65	0.0029	74	3.27	0.0027	3.26	0.0034	3.25	0.0037
1080	68	0.0032	82	3.24	0.0027	3.23	0.0033	3.21	0.0036
1080	72	0.0038	95	3.20	0.0027	3.19	0.0031	3.17	0.0034

Meteorwave® 2000 - Dielectric Properties Table
AMMS Manufacturing Location

PREPREG (Available from AGC Singapore manufacturing location - AMMS):

Glass	RC%	Thickness (inches)	Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
2013	58	0.0040	101	3.35	0.0028	3.34	0.0036	3.33	0.0039
2013	61	0.0043	110	3.31	0.0028	3.30	0.0035	3.29	0.0038
2116	55	0.0047	119	3.38	0.0029	3.38	0.0037	3.36	0.0040
2116	58	0.0051	129	3.35	0.0028	3.34	0.0036	3.33	0.0039
2116	60	0.0054	137	3.32	0.0028	3.31	0.0035	3.30	0.0038

These laminate and prepreg items are representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.multimaterial@agc.com • www.agc-multimaterial.com