Meteorwave 3000 - Dielectric Properties Table

LAMINATE:

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0020	±	0.0005	1	0106				74%	0.0021	54	3.44	0.0029	3.40	0.0035	3.39	0.0037
0.0025	±	0.0005	1	1078				60%	0.0025	64	3.72	0.0032	3.66	0.0041	3.65	0.0043
0.0030	±	0.0005	1	1078				66%	0.0031	78	3.59	0.0031	3.54	0.0039	3.53	0.0041
0.0030	±	0.0005	1	1080				67%	0.0031	79	3.57	0.0031	3.52	0.0038	3.51	0.0040
0.0035	±	0.0005	1	1078				70%	0.0035	89	3.51	0.0030	3.47	0.0037	3.46	0.0039
0.0040	±	0.0005	1	2116				49%	0.0041	104	3.99	0.0036	3.91	0.0047	3.90	0.0049
0.0040	±	0.0005	2	0106				74%	0.0042	107	3.44	0.0029	3.40	0.0035	3.39	0.0037
0.0050	±	0.0007	1	2116				58%	0.0052	132	3.76	0.0033	3.70	0.0042	3.69	0.0044
0.0050	±	0.0007	2	1078				60%	0.0051	128	3.72	0.0032	3.66	0.0041	3.65	0.0043
0.0060	±	0.0007	2	1078				66%	0.0061	155	3.59	0.0031	3.54	0.0039	3.53	0.0041
0.0070	±	0.0010	2	3313				53%	0.0071	180	3.88	0.0035	3.81	0.0045	3.80	0.0047
0.0080	±	0.0010	2	2116				49%	0.0082	208	3.99	0.0036	3.91	0.0047	3.90	0.0049
0.0080	±	0.0010	2	3313				58%	0.0081	206	3.76	0.0033	3.70	0.0042	3.69	0.0044
0.0100	±	0.0010	2	2116				58%	0.0104	263	3.76	0.0033	3.70	0.0042	3.69	0.0044

Meteorwave 3000 - Dielectric Properties Table

LAMINATE (Continued):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0120	±	0.0015	3	2116				49%	0.0123	312	3.99	0.0036	3.91	0.0047	3.90	0.0049
0.0140	±	0.0015	2	2116	+	1	3313	57%	0.0139	353	3.79	0.0033	3.73	0.0043	3.72	0.0045
0.0150	±	0.0015	2	2116	+	2	3313	51%	0.0153	388	3.94	0.0035	3.87	0.0046	3.85	0.0048
0.0160	±	0.0015	4	3313				58%	0.0163	413	3.76	0.0033	3.70	0.0042	3.69	0.0044
0.0180	±	0.0015	5	3313				53%	0.0177	451	3.88	0.0035	3.81	0.0045	3.80	0.0047
0.0200	±	0.0025	4	2116				58%	0.0207	526	3.76	0.0033	3.70	0.0042	3.69	0.0044
0.0240	±	0.0025	4	2116	+	1	3313	57%	0.0243	616	3.78	0.0033	3.72	0.0043	3.71	0.0045
0.0280	±	0.0025	7	3313				58%	0.0284	722	3.76	0.0033	3.70	0.0042	3.69	0.0044
0.0300	±	0.0025	5	2116	+	2	106	60%	0.0301	765	3.71	0.0032	3.66	0.0041	3.65	0.0043
0.0310	±	0.0040	6	2116				58%	0.0311	789	3.76	0.0033	3.70	0.0042	3.69	0.0044
0.0590	±	0.0050	10	2116	+	2	3313	57%	0.0589	1496	3.78	0.0033	3.72	0.0043	3.70	0.0045

NOTE: 2013 may be substituted for 3313 in all constructions

Meteorwave 3000 - Dielectric Properties Table

PREPREG:

Glass	RC%	Thickness (inches)	Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
1027	73%	0.0017	42	3.46	0.0029	3.42	0.0036	3.41	0.0038
0106	74%	0.0021	54	3.44	0.0029	3.40	0.0035	3.39	0.0037
1035	69%	0.0021	54	3.53	0.0030	3.49	0.0037	3.48	0.0039
1078	60%	0.0025	64	3.72	0.0032	3.66	0.0041	3.65	0.0043
1080	61%	0.0025	65	3.70	0.0032	3.64	0.0041	3.63	0.0043
1078	66%	0.0031	78	3.59	0.0031	3.54	0.0039	3.53	0.0041
1080	67%	0.0031	79	3.57	0.0031	3.52	0.0038	3.51	0.0040
1078	70%	0.0035	89	3.51	0.0030	3.47	0.0037	3.46	0.0039
3313	53%	0.0035	90	3.88	0.0035	3.81	0.0045	3.80	0.0047
1078	71%	0.0037	93	3.49	0.0030	3.45	0.0037	3.44	0.0039
3313	58%	0.0041	103	3.76	0.0033	3.70	0.0042	3.69	0.0044
2116	49%	0.0041	104	3.99	0.0036	3.91	0.0047	3.90	0.0049
2116	58%	0.0052	132	3.76	0.0033	3.70	0.0042	3.69	0.0044

These laminate and prepreg items are representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.digital-sales@agc.com • www.agc-multimaterial.com