Meteorwave® 8000 - Dielectric Properties Table
AMMA Manufacturing Location

LAMINATE (Available from AGC U.S. manufacturing location – AMMA):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df	80 GHz Dk	80 GHz Df
0.0020	±	0.0005	1	1078				58%	0.0022	3.52	0.0014	3.49	0.0018	3.48	0.0021	3.45	0.0030
0.0020	±	0.0005	1	1035				70%	0.0021	3.35	0.0012	3.33	0.0017	3.33	0.0020	3.30	0.0028
0.0025	±	0.0005	1	1078				63%	0.0026	3.44	0.0013	3.42	0.0018	3.41	0.0021	3.39	0.0029
0.0030	±	0.0005	1	1078				69%	0.0031	3.36	0.0012	3.34	0.0017	3.34	0.0020	3.31	0.0028
0.0040	±	0.0005	1	2013				59%	0.0039	3.50	0.0013	3.47	0.0018	3.46	0.0021	3.44	0.0030
0.0040	±	0.0005	2	1035				70%	0.0041	3.35	0.0012	3.33	0.0017	3.33	0.0020	3.30	0.0028
0.0045	±	0.0005	2	1078				58%	0.0044	3.52	0.0014	3.49	0.0018	3.48	0.0021	3.45	0.0030
0.0050	±	0.0007	2	1078				63%	0.0051	3.44	0.0013	3.42	0.0018	3.41	0.0021	3.39	0.0029
0.0050	±	0.0007	1	2116				60%	0.0052	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030
0.0060	±	0.0007	2	1078				69%	0.0062	3.36	0.0012	3.34	0.0017	3.34	0.0020	3.31	0.0028
0.0080	±	0.0010	2	2116				51%	0.0081	3.63	0.0014	3.59	0.0020	3.58	0.0023	3.56	0.0031
0.0100	±	0.0010	2	2116				60%	0.0103	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030
0.0120	±	0.0015	3	2013				61%	0.0124	3.47	0.0013	3.45	0.0018	3.44	0.0021	3.41	0.0029
0.0150	±	0.0015	3	2116				60%	0.0155	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030
0.0200	±	0.0025	5	2116				51%	0.0204	3.63	0.0014	3.59	0.0020	3.58	0.0023	3.56	0.0031
0.0240	±	0.0025	6	2116				51%	0.0244	3.63	0.0014	3.59	0.0020	3.58	0.0023	3.56	0.0031
0.0300	±	0.0025	6	2116				60%	0.0309	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030
0.0394	±	0.0040	7	2116	+	1	1080	61%	0.0392	3.48	0.0013	3.45	0.0018	3.44	0.0021	3.42	0.0029
0.0400	±	0.0040	4	2116	+	5	2116	55%	0.0410	3.56	0.0014	3.52	0.0019	3.51	0.0022	3.49	0.0030
0.0600	±	0.0050	12	2116				60%	0.0618	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030

Meteorwave® 8000 - Dielectric Properties Table
AMMA Manufacturing Location

PREPREG (Available from AGC U.S. manufacturing location - AMMA):

Glass	RC%	Thickness (inches)	Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df	80 GHz Dk	80 GHz Df
1035	75%	0.0025	64	3.29	0.0012	3.28	0.0016	3.27	0.0019	3.2462	0.0028
1035	79%	0.0030	77	3.24	0.0011	3.23	0.0015	3.23	0.0018	3.2041	0.0027
1067	77%	0.0028	71	3.26	0.0012	3.26	0.0016	3.25	0.0019	3.2249	0.0027
1078	63%	0.0026	65	3.44	0.0013	3.42	0.0018	3.41	0.0021	3.3875	0.0029
1078	69%	0.0031	79	3.36	0.0012	3.34	0.0017	3.34	0.0020	3.3138	0.0028
1078	75%	0.0039	100	3.29	0.0012	3.28	0.0016	3.27	0.0019	3.2462	0.0028
1080	73%	0.0037	93	3.31	0.0012	3.30	0.0016	3.29	0.0019	3.2681	0.0028
2116	60%	0.0052	131	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.4270	0.0030

Meteorwave® 8000 - Dielectric Properties Table
AMMS Manufacturing Location

LAMINATE (Available from AGC Singapore manufacturing location – AMMS):

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df	80 GHz Dk	80 GHz Df
0.0012	±	0.0005	1	1027				70%	0.0013	3.35	0.0012	3.33	0.0017	3.33	0.0020	3.30	0.0028
0.0020	±	0.0005	1	1035				71%	0.0021	3.33	0.0012	3.32	0.0016	3.31	0.0019	3.29	0.0028
0.0020	±	0.0005	1	106				75%	0.0021	3.29	0.0012	3.28	0.0016	3.27	0.0019	3.25	0.0028
0.0030	±	0.0005	1	1078				69%	0.0031	3.36	0.0012	3.34	0.0017	3.34	0.0020	3.31	0.0028
0.0035	±	0.0005	1	1078				72%	0.0035	3.32	0.0012	3.31	0.0016	3.30	0.0019	3.28	0.0028
0.0040	±	0.0005	1	2013				61%	0.0041	3.47	0.0013	3.45	0.0018	3.44	0.0021	3.41	0.0029
0.0040	±	0.0005	2	106				75%	0.0042	3.29	0.0012	3.28	0.0016	3.27	0.0019	3.25	0.0028
0.0040	±	0.0005	2	1035				71%	0.0043	3.33	0.0012	3.32	0.0016	3.31	0.0019	3.29	0.0028
0.0050	±	0.0007	1	2116				60%	0.0052	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030
0.0050	±	0.0007	2	1078				63%	0.0051	3.44	0.0013	3.42	0.0018	3.41	0.0021	3.39	0.0029
0.0050	±	0.0007	2	1035				76%	0.0052	3.27	0.0012	3.27	0.0016	3.26	0.0019	3.24	0.0027
0.0060	±	0.0007	2	1078				69%	0.0062	3.36	0.0012	3.34	0.0017	3.34	0.0020	3.31	0.0028
0.0080	±	0.0010	2	2013				61%	0.0083	3.47	0.0013	3.45	0.0018	3.44	0.0021	3.41	0.0029
0.0100	±	0.0010	2	2116				60%	0.0103	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030
0.0150	±	0.0015	3	2116				60%	0.0155	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030
0.0160	±	0.0015	4	2116				51%	0.0163	3.63	0.0014	3.59	0.0020	3.58	0.0023	3.56	0.0031
0.0290	±	0.0025	2	2116	+	4	2116	59%	0.0299	3.50	0.0013	3.48	0.0018	3.47	0.0021	3.44	0.0030
0.0390	±	0.0040	8	2116				60%	0.0412	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030
0.0600	±	0.0050	12	2116				60%	0.0618	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030

Meteorwave® 8000 - Dielectric Properties Table
AMMS Manufacturing Location

PREPREG (Available from AGC Singapore manufacturing location - AMMS):

Glass	RC%	Thickness (inches)	Thickness (µm)	2 GHz Dk	2 GHz Df	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df	40 GHz Dk	40 GHz Df
0106	75%	0.0021	53	3.29	0.0012	3.28	0.0016	3.27	0.0019	3.25	0.0028
1027	70%	0.0013	34	3.35	0.0012	3.33	0.0017	3.33	0.0020	3.30	0.0028
1035	71%	0.0021	54	3.33	0.0012	3.32	0.0016	3.31	0.0019	3.29	0.0028
1035	76%	0.0026	67	3.27	0.0012	3.27	0.0016	3.26	0.0019	3.24	0.0027
1078	63%	0.0026	65	3.44	0.0013	3.42	0.0018	3.41	0.0021	3.39	0.0029
1078	69%	0.0031	79	3.36	0.0012	3.34	0.0017	3.34	0.0020	3.31	0.0028
1078	72%	0.0035	88	3.32	0.0012	3.31	0.0016	3.30	0.0019	3.28	0.0028
2013	61%	0.0041	105	3.47	0.0013	3.45	0.0018	3.44	0.0021	3.41	0.0029
2116	51%	0.0041	103	3.63	0.0014	3.59	0.0020	3.58	0.0023	3.56	0.0031
2116	56%	0.0046	117	3.55	0.0014	3.51	0.0019	3.51	0.0022	3.48	0.0030
2116	60%	0.0052	131	3.49	0.0013	3.46	0.0018	3.45	0.0021	3.43	0.0030

These laminate and prepreg items are representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.multimaterial@agc.com • www.agc-multimaterial.com