Meteorwave® 8300 - Dielectric Properties Table

LAMINATE:

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
0.0025	±	0.0005	1	1078				59%	0.0028	72	2.96	0.0027	2.95	0.0030
0.0030	±	0.0005	1	1078				62%	0.0031	79	2.93	0.0026	2.92	0.0029
0.0035	±	0.0005	1	1078				67%	0.0036	92	2.88	0.0026	2.87	0.0029
0.0040	±	0.0005	1	1078				70%	0.0041	105	2.84	0.0026	2.83	0.0029
0.0045	±	0.0005	1	1035		1	1078	61%	0.0048	123	2.94	0.0026	2.93	0.0029
0.0045	±	0.0005	1	2013				58%	0.0046	117	2.97	0.0027	2.96	0.0030
0.0050	±	0.0007	1	2013				61%	0.0051	129	2.94	0.0026	2.93	0.0029
0.0075	±	0.0010	1	2013		1	1078	59%	0.0076	193	2.96	0.0027	2.95	0.0030
0.0080	±	0.0010	2	1078				70%	0.0083	210	2.84	0.0026	2.83	0.0029
0.0100	±	0.0010	2	1078		1	2013	59%	0.0104	265	2.96	0.0027	2.95	0.0030
0.0100	±	0.0010	2	2013				61%	0.0101	257	2.94	0.0026	2.93	0.0029
0.0120	±	0.0015	2	2116				59%	0.0122	310	2.96	0.0027	2.95	0.0030
0.0150	±	0.0015	3	2013				61%	0.0152	386	2.94	0.0026	2.93	0.0029
0.0200	±	0.0025	4	2013				61%	0.0202	514	2.94	0.0026	2.93	0.0029
0.0240	±	0.0025	4	2116				59%	0.0244	621	2.96	0.0027	2.95	0.0030
0.0300	±	0.0025	5	2116				59%	0.0305	776	2.96	0.0027	2.95	0.0030
0.0394	±	0.0040	2	1078		6	2116	59%	0.0429	1089	2.96	0.0026	2.95	0.0029
0.0600	±	0.0050	10	2116				59%	0.0611	1552	2.96	0.0027	2.95	0.0030

Meteorwave® 8300 - Dielectric Properties Table

PREPREG:

Glass	RC%	Thickness (inches)	Thickness (µm)	10 GHz Dk	10 GHz Df	40 GHz Dk	40 GHz Df
1027	70	0.0017	42	2.84	0.0026	2.83	0.0029
0106	75	0.0027	68	2.80	0.0025	2.79	0.0028
1035	63	0.0020	51	2.92	0.0026	2.91	0.0029
1035	70	0.0026	65	2.84	0.0026	2.83	0.0029
1035	77	0.0035	89	2.78	0.0025	2.77	0.0028
1078	59	0.0028	72	2.96	0.0027	2.95	0.0030
1078	70	0.0041	105	2.84	0.0026	2.83	0.0029
1078	75	0.0051	129	2.80	0.0025	2.79	0.0028
2013	61	0.0051	129	2.94	0.0026	2.93	0.0029

These laminate and prepreg items are representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.multimaterial@agc.com • www.agc-multimaterial.com