Meteorwave M1 – Dielectric Properties Table

LAMINATE:

Thickness (inch)	&	Tol.			RC%	Thickness (µm)	10 GHz Dk	10 GHz Df	77 GHz Dk
0.0050	±	0.0007	1	1078	80%	127	3.15	0.0018	3.10
0.0100	±	0.0010	2	1078	80%	254	3.15	0.0018	3.10
0.0150	±	0.0015	3	1078	80%	381	3.15	0.0018	3.10
0.0200	±	0.0025	4	1078	80%	508	3.15	0.0018	3.10
0.0250	±	0.0025	5	1078	80%	635	3.15	0.0018	3.10
0.0300	±	0.0040	6	1078	80%	762	3.15	0.0018	3.10
0.0600	±	0.0050	12	1078	80%	1524	3.15	0.0018	3.10

PREPREG:

Glass	RC%	Thickness (inches)	Thickness (µm)	10 GHz Dk	10 GHz Df	77 GHz Dk
1078	80%	0.0050	127	3.15	0.0018	3.10

These laminate and prepreg items are representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.digital-sales@agc.com • www.agc-multimaterial.com

July 15, 2026