N7000-3F - Dielectric Properties Table

LAMINATE:

Thickness (inch)	&	Tol.	Construction					RC%	Nominal Thickness (inch)	Nominal Thickness (µm)	10 GHz Dk	10 GHz Df
0.0020	±	0.0005	1	106				70%	0.0020	52	3.64	0.0141
0.0035	±	0.0005	1	1080				67%	0.0035	88	3.73	0.0141
0.0040	±	0.0005	2	106				70%	0.0041	103	3.64	0.0141
0.0050	±	0.0007	2	106				75%	0.0050	127	3.50	0.0140
0.0060	±	0.0007	2	1080				63%	0.0061	154	3.85	0.0142
0.0080	±	0.0010	2	2116				45%	0.0081	205	4.54	0.0145
0.0100	±	0.0010	2	2116				53%	0.0100	254	4.20	0.0143
0.0120	±	0.0015	2	2116	+	1	106	55%	0.0120	305	4.12	0.0143
0.0140	±	0.0015	2	2116	+	1	2116	51%	0.0140	356	4.29	0.0144
0.0150	±	0.0015	3	2116				53%	0.0150	381	4.20	0.0143
0.0160	±	0.0015	2	106	+	3	2116	49%	0.0162	411	4.35	0.0144
0.0180	±	0.0015	2	1080	+	3	2116	49%	0.0182	462	4.34	0.0144
0.0210	±	0.0025	2	2116	+	2	7628	41%	0.0214	544	4.70	0.0146
0.0240	±	0.0025	2	106	+	3	7628	44%	0.0241	612	4.58	0.0145
0.0280	±	0.0025	2	2116	+	3	7628	41%	0.0281	714	4.74	0.0146
0.0310	±	0.0040	2	106	+	4	7628	42%	0.0308	781	4.64	0.0146
0.0470	±	0.0050	2	1080	+	6	7628	43%	0.0470	1194	4.64	0.0145
0.0590	±	0.0050	2	1080	+	8	7628	41%	0.0595	1510	4.73	0.0146
0.0620	±	0.0050	2	2116	+	8	7628	39%	0.0615	1561	4.82	0.0146

N7000-3F - Dielectric Properties Table

PREPREG:

Glass	RC%	Thickness (inches)	Thickness (µm)	10 GHz Dk	10 GHz Df
106	77	0.0027	70	3.25	0.0140
1080	70	0.0039	99	3.44	0.0141
2116	53	0.0050	127	4.00	0.0143

These laminate and prepreg items are representative of available materials. These items and their associated values may not be regularly available and additional lead times or minimum order quantities could apply. Please contact our office or your local technical representative for assistance with choosing the best material for your design and application.

For More Information:
North America +1.480.967.5600 • Europe +33.5.62.98.52.90 • Asia Pacific +65.686.17117
agc-ml.multimaterial@agc.com • www.agc-multimaterial.com