multi-cb
PRINTED CIRCUIT BOARDS
1-48 layers · From 1WD express · 30 years

Materials Standard Values – metal core (IMS)

Poole, 02.07.2025

In the following, we have listed the established standard values for metal core / IMS- (Insulated Metal Substrate) materials used at Multi Circuit Boards Ltd.

The quality of your PCBs is assured through the use of technical comparable materials (dependent on manufacturing inventory, global market). A specific material can be defined on request; this may lead to a longer production time and / or a price adjustment.

		IMS 2.0	IMS 3.0	IMS 4.0	IMS 7.0
Thermal conductivity	W/mK	≥ 2.0	≥ 3.0	≥ 4.0	≥ 7.0
Thermal resistance	K/W	0.40	0.30	0.30	-
Surface resistivity	MΩ	10^6	5 x 10^8	2 x 10^7	2 x 10^7
Dielectric glass transition (Tg)	°C	120	130	120	100
Dielelectric Breakdown (AC)	kV	1L ≥ 3.5 2L ≥ 7.0	1L ≥ 3.5 2L ≥ 8.0	≥ 8.0	≥ 8.0
CTI	V	600	600	600	600
Depending on availability and / or customer request	z.B.	AL-200 HA50 (3) AL-01-B	AL-300 VT-4B3	AL-01-B-40 VT-4B4	VT-4B7 TCB-C

If you need a special material (e.g. metal core with W/mK ≥ 8, flexible Metal core, etc.), please contact us. You can find an overview on our website: www.multi-circuit-boards.eu

Text data contained in this data sheet represents typical values and does not constitute any warranty or guarantee. For review of critical specification tolerances, please contact our CAM department.

SUPPORT:
Multi Leiterplatten GmbH
Brunnthaler Straße 2
DE-85649 Brunnthal
+49 8104 628-0 | Fax: -160

CONTRACTING PARTY:
Multi Circuit Boards Ltd. | Business Centres, Holyrood Close | GB-Poole, BH17 7FJ
VAT-ID: DE281397430 | GB Co. Reg: 07909372
Contact: Tel: +44 1425 489 111 | info@multi-circuit-boards.eu | www.multi-cb.eu
Bank details: Commerzbank Munich | IBAN DE31 7004 0048 0763 3407 00 | BIC COBADEFF970

FED Fachverband für Design, Leiterplatten- & Elektronikfertigung
IPC Member