

[Course](#)
[Progress](#)
[Dates](#)
[Discussion](#)
[Resources](#)
[Search](#)
[Course team](#)

[Home](#) / [Course](#) / [Week 6: Wet etching \(WE\)](#) / [Wet etching of oxides](#)


[< Previous](#)

[Next >](#)

Practice quiz HF bath for SiO₂ and glass wet etching

[Bookmark this page](#)

Questions:

0 points possible (ungraded)

1. What is the main advantage of a buffered HF (BHF) over a pure HF bath for the Pyrex etching process?

☒ A Au layer is not required in preparing the mask

☐ One can completely avoid mask underetching effects

© All Rights Reserved

© École polytechnique fédérale de Lausanne. All rights reserved except where noted. edX, Open edX and their respective logos are registered trademarks of edX Inc.



[Terms of Service & Honor Code](#) [Privacy Policy](#)

☐ The Cr layer is not required for depositing the photoresist mask on the Pyrex substrate



Explanation

A mixture of 40 wt% NH_4F with 49 wt% HF is called buffered oxide etch or buffered HF (BHF). The use of BHF produces a slower and less aggressive etch so that photoresist masks can be used. Photoresist would be very strongly degraded in pure (=49%) HF baths. In a Pyrex etching process in a BHF solution, there is no need for the deposition of an expensive Au mask, as photoresist can be maintained in the BHF bath. See "HF bath for SiO_2 and glass wet etching" video from 5:05 to 10:45 for detailed explanations.

2. What is a commonly used application of HF etching?

☐ To make the wafer surface more hydrophilic

☐ To remove the residual organics from the wafer surface

☐ To thermally stabilize the structures on the wafer

☒ To form free standing structures



Explanation

This type of etching is used for locally removing a SiO_2 layer to define free-standing structures like used for micro-actuators. See "HF bath for SiO_2 and glass wet etching" video from 0:10 to 1:20 for detailed explanations.

Submit

Answers are displayed within the problem

< Previous

Next >