different kinds of ores of metals are given in Table 8.1

Concentration of the crushed ore is done mainly by the following methods: -

(i) **Hydraulic (Gravity Separation) method**

Principle: The difference in the densities or specific gravities of the ore and the gangue is the main principle behind this method. Oxide ores are purified by this method. e.g., Haematite Fe_2O_3 the ore of iron.

Note: When the ore is heavier than the impurity, this method can be used.

Method: The ore is poured over a sloping, vibrating corrugated table with grooves and a jet of water is allowed to flow over it. The denser ore particles settle down in the grooves and lighter gangue particles are washed down by water.

(ii) **Magnetic separation method**

Principle: The magnetic properties of the ores form the basis of separation. When either the ore or the gangue is magnetic, this method is employed. e.g., Tinstone SnO_2, the ore of tin.




Figure 8.8 Magnetic separation

Method: The crushed ore is placed over a conveyer belt which rotates around two metal wheels, one of which is magnetic. The magnetic particles are attracted to the magnetic wheel and fall separately apart from the non-magnetic particles.

(iii) **Froth floatation**

Principle: This process depends on the preferential wettability of the ore with oil (pine oil) and the gangue particles by water. Lighter ores, such as sulphide ores, are concentrated by this method. e.g., Zinc blende (ZnS).




Figure 8.9 Froth floatation

Note: When the impurity is heavier than the ore, this method can be used.

Method: The crushed ore is taken in a large tank containing pine oil and water and agitated with a current of compressed air.The ore is wetted by the oil and gets separated from the gangue in the form of froth. Since the ore is lighter, it comes on the surface with the froth and the impurities are left behind. e.g., Zinc blende (ZnS).

(iv) **Chemical method or Leaching**

This method is employed when the ore is in a very pure form.

Table 8.1 Types of ores

Oxide Ores	Carbonate Ores	Halide Ores	Sulphide Ores
Bauxite ($Al_2O_3 \cdot 2H_2O$)	Marble ($CaCO_3$)	Cryolite(Na_3AlF_6)	Galena (PbS)
Cuprite(Cu_2O)	Magnesite (($MgCO_3$)	Fluorspar(CaF_2)	Iron pyrite (FeS_2)
Haematite (Fe_2O_3)	Siderite($FeCO_{3)}$	Rock salt (NaCl)	Zinc blende (ZnS)

10th_Science_Unit-8.indd 113 06-12-2021 18:37:49