www.tntextbooks.in

(a) Portion OA:

In this region, stress is very small such that stress is proportional to strain, which means Hooke's law is valid. The point A is called *limit of proportionality* because above this point Hooke's law is not valid. The slope of the line OA gives the Young's modulus of the wire.

(b) Portion AB:

This region is reached if the stress is increased by a very small amount. In this region, stress is not proportional to the strain. But once the stretching force is removed, the wire will regain its original length. This behaviour ends at point B and hence, the point B is known as *yield point* (elastic limit). The elastic behaviour of the material (here wire) in stress-strain curve is OAB.

(c) Portion BC:

If the wire is stretched beyond the point B (elastic limit), stress increases and the wire will not regain its original length after the removal of stretching force.

(d) Portion CD:

With further increase in stress (beyond the point C), the strain increases rapidly and reaches the point D. Beyond D, the strain increases even when the load is removed and breaks (ruptures) at the point E. Therefore, the maximum stress (here D) beyond which the wire breaks is called *breaking stress* or *tensile strength*. The corresponding point D is known as *fracture point*. The region BCDE represents the plastic behaviour of the material of the wire.

7.2.4 Moduli of elasticity

From Hooke's law, the stress in a body is proportional to the corresponding strain, provided the deformation is very small. In this section, we shall define the elastic modulus of a given material. There are three types of elastic modulus.

(a) Young's modulus

(b) Rigidity modulus (or Shear modulus)

(c) Bulk modulus

Young's modulus:

When a wire is stretched or compressed, then the ratio between tensile stress (or compressive stress) and tensile strain (or compressive strain) is defined as Young's modulus.


$$\text{Young modulus of a material} = \frac{\text{Tensile stress or compressive stress}}{\text{Tensile strain or compressive strain}}$$

$$Y = \frac{\sigma_t}{\varepsilon_t} \quad \text{or} \quad Y = \frac{\sigma_c}{\varepsilon_c} \qquad (7.6)$$

The unit for Young modulus has the same unit of stress because, strain has no unit. So, S.I. unit of Young modulus is N m^{-2} or pascal.

EXAMPLE 7.1

Within the elastic limit, the stretching strain produced in wires A, B, and C due to stress is shown in the figure. Assume the load applied are the same and discuss the elastic property of the material.



BMDLVX

Write down the elastic modulus in ascending order.

Solution

Here, the elastic modulus is Young modulus and due to stretching, stress is tensile stress and strain is tensile strain.